



HAL
open science

Unveiling the potential of redox chemistry to form size tunable, high index silicon particles

Megan A Parker, Safa Khaddad, Nicolas Fares, Anissa Ghoridi, David Portehault, Sébastien Bonhommeau, Yacine Amarouchene, Patrick Rosa, Mathieu Gonidec, Glenna L. Drisko

► **To cite this version:**

Megan A Parker, Safa Khaddad, Nicolas Fares, Anissa Ghoridi, David Portehault, et al.. Unveiling the potential of redox chemistry to form size tunable, high index silicon particles. *Chemistry of Materials*, 2024, 36 (22), pp.10986-10993. 10.1021/acs.chemmater.4c01439 . hal-04693315

HAL Id: hal-04693315

<https://hal.science/hal-04693315v1>

Submitted on 10 Sep 2024

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.



Distributed under a Creative Commons Attribution - NonCommercial - NoDerivatives 4.0 International License

Unveiling the potential of redox chemistry to form size tunable, high index silicon particles

Megan A. Parker^a, Safa Khaddad^a, Nicolas Fares^b, Anissa Ghoridi^c, David Portehault^c, Sébastien Bonhommeau^d, Yacine Amarouchene^b, Patrick Rosa^{a,*}, Mathieu Gonidec^{a,*}, Glenna L. Drisko^{a,*}


^aUniv. Bordeaux, CNRS, Bordeaux-INP, ICMCB, UMR 5026, F-33600, Pessac, Fr

^bUniv. Bordeaux, CNRS, LOMA, UMR 5798, F-33405, Talence, Fr

^cSorbonne Université CNRS, Laboratoire de Chimie de la Matière Condensée de Paris (LCMCP), F-75005 Paris, France

^dUniv. Bordeaux, CNRS, Bordeaux-INP, ISM, UMR 5255, F-33400, Talence, Fr

ABSTRACT: Silicon particles of intermediate sizes (75-200 nm) scatter visible wavelengths, making them promising candidates for optical devices. The solution synthesis of silicon particles in this size range, however, has proved challenging for chemists over the past few decades. Here, a solution-phase synthesis provides a pathway toward reaching size tunability between 45-230 nm via changing the reactant ratio in the reaction between a silicon Zintl phase (Na_4Si_4) with an amidinate-stabilized Si (IV) coordination complex. Coherent domain sizes, determined from powder X-ray diffraction, show that the crystallite sizes are uniform across all particle sizes, perhaps indicating an aggregation mechanism for particle growth. The amidinate ligands act to stabilize the particle surface. Combined surface techniques (ToF-SIMS, FTIR, and XPS) confirm the presence of amidinate ligands, as well as primary amine and a passive oxidation layer on the surface of the particles. The refractive index is measured for an individual particle using holographic optical microscopy, displaying a refractive index of nearly 4.1 at a wavelength of 532 nm. Thus, these particles should scatter light intensely at visible wavelengths, making them promising candidates for optical manipulation.



INTRODUCTION:


Crystalline, non-porous Si particles have extraordinary optical properties thanks to the polarization oscillations within individual atoms known as Mie resonances, contributing to intense light scattering. Silicon particles of appropriate size can generate electric field enhancement, directional scattering, or structural coloration. The Purcell effect can also yield the spontaneous emission of nearby emitters when in close contact with Si structures.¹⁻³ When assembled, these particles have potential in the development of miniaturized, flat optical components.^{4,5} Although, the perspectives for these objects are expansive, few synthesis methods are able to produce the large quantities of Si particles, most of all the crystalline particles with size- and shape-control, needed for the fabrication of optical devices.

Moreover, a range of sizes is needed to cover the diversity of optoelectronic applications. The size of silicon particles is limited to a few nanometers for most solution routes.⁶⁻⁸ Decomposition under supercritical conditions produces particles that are amorphous and porous,⁹ yielding weak Mie resonances in the visible region. Disproportionation of silicon-rich oxides produces highly optically responsive particles, but yield is low, particularly after size-separation, and the synthesis requires the use of hazardous hydrofluoric acid to liberate the silicon particles.¹⁰⁻¹² Finally, nonthermal plasmas produce highly pure

spherical Si particles of controllable size, but these particles are then collected as a powder or loosely packed on a substrate, rather than as a dispersion in solution ready for further processing.^{13,14} Thus, we still aspire towards a room-temperature, solution-chemistry based method, a cousin to the Stöber method for silica, producing crystalline silicon particles.

Ligand-controlled growth, a popular technique used in other metallic and metal oxide particle syntheses, is less explored in the growth toward large Si particles. Ligand-controlled growth typically involves aqueous solvents and oxygen-containing precursors, which cannot be transferred to silicon nanochemistry due to the spontaneity of silicon to oxidize or hydrolyse in the presence of oxygen or hydroxyl groups. Seemingly transferrable, however, is the preparation of nanoparticles from organometallic precursors in organic solvents. Organometallic precursors provide dual functionality: (1) they can be decomposed under mild conditions, in comparison to traditional precursors with high Si bond strengths, and (2) upon decomposition they can provide ligands that stabilize the particle surface.

Amidinate ligands are known to form stable complexes with most transition-metals and, due to their ease of decomposition, have been explored as metallic nanomaterial precursors.^{15,16} Amidinate-based coordination complexes have yielded amidinate surface-stabilized metallic nanoparticles.¹⁷



Scheme 1. Reaction mechanism of $SiCl_2[BuC(NiPr)_2]_2$ toward Si particles. Purple indicates Si, green Cl, blue N, and grey C. Scale bars represent 200 nm.

While Si amidinate complexes have been synthesized with a variety of ligand-alterations,¹⁸ only recently have we used this type of complex successfully in particle synthesis,¹⁹ through the redox reaction between a silicon Zintl phase and an amidinate-stabilized silicon (IV) precursor. In our previous study, a stoichiometric 1 : 1 ratio between the precursors generated particle sizes from 15 to 45 nm, where particle size was altered by changing the dispersive media. Here, we chose the solvent producing the largest particles (toluene) and tuned the stoichiometric ratio $Na_4Si_4 : SiCl_2[BuC(NiPr)_2]_2$ between 1-4, to control particle size from 45 to 230 nm. Individual particle refractive index measurements were made on the largest particles produced ($d \sim 230$ nm) and the refractive index was found to be near that of bulk crystalline Si.

RESULTS AND DISCUSSION:

The redox reaction is an interfacial reaction, occurring at room temperature, between a solution phase silicon coordination complex, bis(*N,N'*-diisopropylbutylamidinato)dichlorosilane, and a solid phase Zintl salt, sodium silicide, which is synthesized to a purity of ca. 98 mol%.²⁰ The structure of $SiCl_2[BuC(NiPr)_2]_2$ is shown in Figure S1. The initial reaction between anionic $[Si_4]^{4-}$ subunits and Si^{4+} species is most likely rapid, due to the large difference in reduction potential between the two precursors. The molar ratio of the solid and dissolved silicon precursors affects the final particle diameter, as shown in Scheme 1.

First, we tested the reaction using an excess of the reducing agent, sodium silicide (1.5 $Na_4Si_4 : 1 SiCl_2[BuC(NiPr)_2]_2$). An excess of sodium silicide forms small, highly aggregated silicon particles (Figure S2) of 20-40 nm. Non-aggregated silicon nanoparticles in this size range have already been produced using commercially available silanes,²¹⁻²⁴ and thus were not characterized any further. More interesting was what happened to particle size when we used an excess molar ratio of $SiCl_2[BuC(NiPr)_2]_2$ with respect to sodium silicide. When 1

$Na_4Si_4 : 1.5 SiCl_2[BuC(NiPr)_2]_2$ were reacted, particle size nearly doubled. Several additional molar ratios (*n*) were tested and particle sizes continually increased, yielding average diameters between 45-230 nm, when using between $n=1-4$ equivalents of $SiCl_2[BuC(NiPr)_2]_2$ (Figure 1a,b). The error bars are related to the polydispersity within a batch. Particle size distributions are shown in Figure 1c (non-spherical objects were not counted in the shown size distributions). Above $n=4$, the particles became even more irregular in shape (Figure S3). For the current synthesis conditions, the sizes attainable are well-defined by the parameters shown in Figure 1a. By simply adjusting the molar ratio of the two silicon precursors, particle sizes that display Mie resonance across the visible spectrum can be obtained.




Figure 1. (a) Median particle size vs. $n SiCl_2[BuC(NiPr)_2]_2$ molar equivalents plotted and fitted with a logistic trend line. Vertical bars show the standard deviation of each batch. (b) TEM images for varying precursor ratios with $n=1.5$ to 4. All scale bars represent 100 nm. (c) Corresponding particle size distributions from counting 200 particles. (d) Typical powder diffractogram obtained from Si particles with $n=2$. (e) Calculated coherent domain sizes.




Figure 2. (a) Schematic showing particle surface chemistry where Si atoms are indicated in purple, oxygen in red, nitrogen in blue and carbon in grey. (b) ToF-SIMS mass spectra (negative mode) subset showing major peaks obtained from particles. (c) ATR-FTIR of solid particle film. High resolution XP spectra of (d) Si 2p region (Black line corresponds to fit data. $2p_{3/2}$ and $2p_{1/2}$ peak fittings are shown). High resolution XP spectra of (e) N 1s region (Black line corresponds to the fit data). Data corresponds in all cases to particles formed using $n=2$ eq. $\text{SiCl}_2[\text{BuC}(\text{N}^i\text{Pr})_2]_2$.

A typical X-ray powder diffractogram of the obtained particles confirms the presence of crystalline Si (Figure 1d), while the broad contribution around $2\theta = 25^\circ$ could also indicate the presence of amorphous silicon or partially oxidized particles. Coherent domain sizes were calculated for each batch of particle sizes (Figure 1e, Figure S4) and remain relatively similar at about 25 nm, irrespective of the particle diameter derived from TEM. This may suggest that the initial size of nucleated particles, or germs, is relatively constant, and particle growth may occur through aggregation of primary particles.

We found that the reaction proceeds without needing to first isolate the molecular complex. This prompted us to investigate whether the effect of additional Si(IV), ligand or both contribute to the growth of Si particles. The quantities of amidinate ligand and silane, in the form of SiCl_4 , were independently varied relative to a fixed quantity of sodium silicide (Figure S5). Firstly, let us specify that these reactions differ from previous reactions performed using SiCl_4 ,^{21,22,24} because the silane reacts with the lithium amidinate ligand *in situ*, prior to the reaction with sodium silicide, allowing the reaction to occur at room temperature (whereas the other studies took place at 85°C). Notably, both the amidinate and the Si(IV) concentration affect the final particle size and shape. Increasing the concentration of Si (IV) increases particle size when the amount of ligand is held constant. When both concentrations are low, particles are small and highly agglomerated. Larger and more separated particles are obtained when multiple equivalents of both ligand and silane are used relative to sodium silicide. Finally, we found that the order of addition is crucial, since when the ligand is not pre-associated with the silane (that is added after mixing Zintl salt and silane), the resulting particles are more polydisperse. This indicates that forming the complex prior to contact with the sodium silicide yields silicon batches of better quality.

Increased particle size with excess ligand is seemingly contrary to typical ligand-controlled nanoparticle growth, where higher

ligand concentrations in solution typically yield smaller nanoparticles.^{17,25} However, higher ligand concentrations do not give smaller particle sizes when the growth mechanism proceeds via aggregation and coalescence. Here, the particles are formed in a non-polar solvent, toluene. There are no strong repulsive forces due to a highly polarizable solvent, electrostatic surface charges, or steric forces from large surface-bound polymers. Thus, Van der Waals attractive forces can lead to a certain degree of aggregation.²⁶ This is consistent with TEM images showing aggregated objects. We also probed particle growth as a function of time and stopped the reaction after 1 h and 4 h (Figure S6). Smaller particles were observed by TEM, and although the sample is too aggregated to construct a size distribution, the average particle size appears to increase with time, reaching a maximum at 16 h. In order to better understand the system, the surface chemistry requires analysis.

Negative ToF-SIMS ion spectra indicate the presence of silicon clusters coordinated to amidinate ligands with intense peaks at m/z 255.2 and 283.1 (Figure 2b). Amine ions are also attached to these clusters. The fragments associated with each of these peaks, separated by the mass of one Si atom, are shown above each peak. The isotopic distribution also corresponds well with these fragments, as observed in subsequent peaks. Ion mapping is provided in Figure S7 to show the spatial distribution of the ions concentrated in regions containing the particles. For comparison, ion mapping for Au^- is shown, ensuring that the amidinate ligand comes directly from the particles and not from some residue on the gold substrate. The residual nitrogen present on the surface of the particles is likely due to reaction with the solvent used to wash the silicon particles. It has been previously shown that dimethyl formamide reacts with a silicon surface.²⁶ It is thus likely that formamide is the source of both the oxygen and the amine groups found on the particle surface.

XPS and ATR-FTIR spectroscopy support the ToF-SIMS interpretation (Figure 2c-e). A strong vibrational mode for SiO_x is centered at 1040 cm^{-1} and a weaker mode around 880 cm^{-1} .²⁷ A

vibrational mode emerges at approximately 1680 cm^{-1} which can be assigned to the amidinate ligand C=N stretching. Alkyl C-H vibrational modes are seen just below 3000 cm^{-1} and a weak, broad mode at 3300 cm^{-1} indicates the presence of primary amine. These two peaks are present for all particle sizes with no significant difference in peak height ratio from one sample to the next (Figure S8). XPS is also consistent with the presence of amidinate ligand and primary amine on the surface (Figure 2d,e). Enlargement of the Si 2p region shows two distinctive peaks corresponding to Si (0) core atoms with a peak at 98.3 eV and surface Si (IV) atoms attached to either N or O, with a peak at 103.0 eV . The N 1s region can be fit to two components corresponding to Si-N-Si (398.3 eV) and primary amine (400.1 eV).²⁸ Thus, ATR-FTIR spectroscopy and XPS indicate that the surface contains oxygen, amine and amidinate functionalities.

The particles were characterized by Raman spectroscopy to probe the silicon environment more fully (Figure 3). The two main peaks related to the light scattering of the transverse optical (TO) and transverse acoustical (TA) photons are observed for all of the samples. The TO-related peak is broad and located at 480 cm^{-1} for an amorphous Si film, and at 520 cm^{-1} for bulk crystalline Si.²⁸ For the largest particles ($\sim 230\text{ nm}$) the TO band is at 515 cm^{-1} and the TA band is at 300 cm^{-1} , both of which are close to that of bulk crystalline Si. When the size of the Si particles decreases, both bands shift to the red (i.e. to lower Raman shifts) and become more dissymmetric. Band shifting and broadening has been associated with the decrease of nanoparticle sizes due to quantum confinement effects,³⁰⁻³² however the particles made here are probably too large to display sufficient quantum confinement. Another potential explanation is the amorphization of the silicon particles, however the line shape




Figure 3. (a) Raman spectra of particles produced using 1 : n Na_4Si_4 : $\text{SiCl}_2[\text{BuC}(\text{NiPr})_2]_2$ in toluene at room temperature. (black) 1 eq., (blue) 1.5 eq., (purple) 2 eq., (pink) 3 eq., and (red) 4 eq. $[\text{BuC}(\text{NiPr})_2]_2\text{SiCl}_2$. (b) Enlargement of the region of the Si-Si TO vibrational mode, (c) Maximum Raman peak shift for each batch of particles.

does not really correspond to a progressive amorphization.³³ The red shift and the band asymmetry of TO Raman peaks could potentially originate from a Fano interference of the TO phonon with an electronic continuum, as reported for smaller Si nanoparticles.³⁴ However, the red shift, which is accompanied by a decrease in the intensity of the TO band, could also be related to a partial oxidation.^{35,36} Greater oxidation for smaller particles can be explained by their greater surface area to volume ratio.

The refractive index was measured of an individual particle with a median diameter of 230 nm (Figure 4). The optical microscope measuring the refractive index has a resolution limit near that of our largest batch of particles ($n=4$ eq. $\text{SiCl}_2[\text{BuC}(\text{NiPr})_2]_2$), thus only the refractive index of our largest particle sample could be determined. With a 532 nm laser, the refractive index for a $113 \pm 10\text{ nm}$ radius particle was found to be 4.08 ± 0.03 when the inference pattern from a single particle was fit with a Lorentz-Mie model via a previously established protocol.^{37,38} The distribution of measured indices of 170 images is shown in Figure S9. For comparison, in bulk crystalline Si, at this wavelength, the refractive index is 4.14. The measured refractive index of these large Si particles corresponds well to the highly crystalline nature observed with Raman spectroscopy for the largest particle batch.




Figure 4. (a) Experimental interference pattern captured by a single particle produced from particles formed using $n=4$ eq. $\text{SiCl}_2[\text{BuC}(\text{NiPr})_2]_2$. (b) Corresponding best-fit Lorenz-Mie interference pattern, providing the radius $a = 113 \pm 10\text{ nm}$ and refractive index $n = 4.08 \pm 0.03$ of the particle. (c) Angular averages of the intensities I (normalized by the mean intensity I_0) from the experimental and theoretical interference patterns, as functions of the radial distance to the z-axis.

CONCLUSION:

The control of particle sizes, in the size ranges of hundreds of nm, is unprecedented for solution syntheses of silicon particles. In the interfacial reaction reported here, particles with a tunable diameter between 45 nm and 230 nm can be produced by using an excess of silicon complex, $\text{SiCl}_2[\text{BuC}(\text{NiPr})_2]_2$, with respect to the Zintl phase, Na_4Si_4 . The systematic variation of $\text{SiCl}_2[\text{BuC}(\text{NiPr})_2]_2$ in solution resulted in a positive correlation between precursor ratio and particle size. The precursor was deconstructed into its Si (IV) and ligand components, which also produced Si particles with an increase in particle size observed for both greater Si (IV) and ligand quantities. Thus, this colloidal synthesis route opens future exploration of other ligands for the size and shape control of Si particles. Increases in ligand

concentration in solution did not impact particle size in the expected manner: more ligand produced larger particles. The surface binding of amidinate ligands on the surface of the particles is confirmed by ToF-SIMS, ATR-FTIR, and XPS. Optical refractive index near that of bulk silicon has been observed, showing promise for these nano-objects in optically responsive materials, although the polydispersity should be improved upon in future development. Particles of tunable size and form are equally needed in the anodes of lithium ion batteries.

EXPERIMENTAL METHODS:

Materials. Toluene (anhydrous, 99.8%), N,N'-Diisopropylcarbodiimide (99%), silicon tetrachloride (99%), n-butyllithium (2.5 M in hexane), and NaH (90%) were purchased from Sigma-Aldrich and used without further purification. Silicon particles were purchased from Nanomakers (40 nm). Tetrahydrofuran (THF, 99.9%) was obtained from Sigma-Aldrich and purified in an MBraun MBSPS 5 solvent purification system. Formamide (99%) was purchased from Fischer Scientific and the oxygen was removed by three freeze-pump-thaw cycles. The purified solvent was stored over 3 Å molecular sieves in an argon filled glovebox. Carbon-coated copper grids were purchased from Electron Microscopy Sciences (Hatfield, PA). Miniature hollow glass capillaries were purchased from CMSscientific (path length 0.2 mm, width 2 mm and 0.14 mm). All the experiments were carried out under inert atmosphere, with Schlenk line techniques, or in an argon-filled glovebox.

Synthesis of bis-(N,N'-diisopropylbutylamidinate)dichlorosilane ($\text{SiCl}_2[\text{BuC}(\text{N}^i\text{Pr})_2]_2$). The silicon precursor was prepared according to a previously reported protocol.¹⁹ First, butyllithium (13 mL, 0.032 mol) was added to a solution of N,N'-diisopropylcarbodiimide (5.0 mL, 0.032 mol) in THF (80 mL) in a cooling bath slurry consisting of a 60/40 v/v% ethanol/water mixture with liquid N_2 (-40°C). The solution was allowed to come to room temperature, and stirred overnight. This reaction yields an intermediate, lithium amidinate. In a second step, SiCl_4 (1.86 mL, 0.016 mol) was added in a cooling bath slurry consisting of a 70/30 v/v% ethanol/water mixture (-80°C) with liquid N_2 . The solution was allowed to come to room temperature, and stirred overnight. The THF was evaporated and substituted with toluene (60 mL). LiCl precipitated and was filtered out of the media via cannula filtration. Most of the toluene (50 mL) was removed via evaporation to concentrate the product. The product was stored at -30°C until crystals formed. Then, cold toluene (30 mL) was added and the product was further chilled at -30°C overnight. The next day, larger, colorless crystals had formed. These were collected and washed with cold toluene. The precursor was stored at -30°C .

Synthesis of sodium silicide, Na_4Si_4 . High purity Na_4Si_4 was prepared according to a previously published protocol.²⁰ In a typical batch, NaH (19.6 mmol, 470 mg) and silicon nanoparticles (17.9 mmol, 500 mg) were mixed together at 20 Hz for 2 min using a ball mill (Retsch MM400 ball miller, airtight vials of 50 mL, one steel ball of 62.3 g, and a diameter of 23 mm). The powder was recovered in an argon filled glovebox and put into a h-BN crucible, which was placed in an air-tight quartz tube. The quartz tube was placed inside a vertical oven and connected to an Ar flow of 0.06 L min^{-1} . A heating ramp of $10^\circ\text{C min}^{-1}$ was used to 400°C , followed by a dwell time of 24 h.

Finally, the sample was cooled naturally. The reaction vessel was then transferred back to an argon-filled glovebox and the synthesized powder was recovered and stored in the glovebox.

Reactions of $\text{SiCl}_2[\text{BuC}(\text{N}^i\text{Pr})_2]_2$ with Na_4Si_4 . In an argon-filled glove box, Na_4Si_4 was weighed and added to a round-bottom Schlenk flask equipped with a magnetic stir bar. Toluene (8 mL) was added, followed by the appropriate molar eq. of $\text{SiCl}_2[\text{BuC}(\text{N}^i\text{Pr})_2]_2$ (Table S1), maintaining a silicon concentration of 20 mM. The reagents were stirred with magnetic agitation at room temperature for 16 h under a flow of argon gas. After the synthesis, the products were collected under inert atmosphere. The crude product, appearing as a black solid, was washed twice with anhydrous formamide, and twice with anhydrous THF via 10 min centrifugation at 10 400g.

Reactions of SiCl_4 with or without lithium amidinate and Na_4Si_4 . In an argon-filled glove box, 4 mg Na_4Si_4 was weighed and added to a round-bottom Schlenk flask equipped with a magnetic stir bar. Toluene (4 mL) was added, followed by the appropriate molar eq. of SiCl_4 and/or lithium amidinate corresponding to Figure S6. The reagents were stirred with magnetic agitation at room temperature for 16 h under a flow of argon gas. After the synthesis, the products were collected under inert atmosphere and washed with the same protocol mentioned above.

Transmission electron microscopy (TEM). Particles were dispersed in THF and then sonicated for 3 min. One drop was cast onto a copper grid covered with a carbon film (previously activated by UV, carbon film, face up) for analysis by TEM. Bright field TEM images were acquired using a JEOL 1400+ (JEOL, Tokyo, Japan) microscope operating at an acceleration voltage of 120 kV and equipped with a Smart Orius 1000 camera obtained from GATAN.

Scanning electron microscopy (SEM). Samples were drop cast onto aluminum sample holders and SEM images were acquired using a field emission scanning microscope (JSM 6700F, Jeol 6700F) microscope operating at a current of 10 mA.

Powder X-Ray diffraction (XRD). X-ray diffractograms from 8 to $80^\circ 2\theta$ were recorded on dried, ground samples spread evenly onto a zero-background sample holder using a PANalytical X'Pert Proapparatus (Cu radiation source $\lambda=0.15418\text{ nm}$) equipped with an X'Celerator detector.

Time-of-Flight Secondary Ion Mass Spectrometry (ToF-SIMS). Samples were drop cast onto gold-coated substrates and experiments were performed using a TOF.SIMS 5 spectrometer (IONTOF GmbH) equipped with a liquid metal ion gun oriented at 45° to the sample. The diameter of the 30 kV Bi^{3+} ion beam was approximately $5\ \mu\text{m}$. The beam was operated at a 0.3 pA ion current in spectrometry mode and raster scanned over the surface to generate $500 \times 500\ \mu\text{m}$ secondary ion images.

Infrared Spectroscopy (ATR-FTIR). Measurements were recorded on a solid film on a Shimadzu IRAffinity-1S Fourier Transform InfraRed (FTIR) spectrometer with a MIRacle 10 Single Attenuated Total Reflection (ATR) Accessory.

X-Ray Photoelectron Spectroscopy (XPS). Powdered samples were pressed onto indium strips and X-ray Photoelectron

Spectroscopy (XPS) was carried out with a Thermo Scientific K-Alpha with an Al K α X-ray source and a spot size of 400 μm . Quantification and peak fitting were achieved by using the AVANTAGE software (Thermo Fisher Scientific).

Raman Spectroscopy. Samples were prepared by drop casting particles dispersed in THF on a microscope slide in the glove box. Raman spectra were recorded on an Xplora spectrometer (Horiba), equipped with a confocal microscope. An objective lens with a 10x magnification was used to observe the sample. An Olympus LM Plan FLN 100 \times objective lens with 0.80 numerical aperture and 3.4 mm working distance was employed to focus the laser beam on the sample and collect the scattered light. A longpass edge filter was used to remove the fundamental line from the collected scattered light. The spectra were run using a 632.81 nm HeNe gas laser, using a filter to reduce the laser power to 20% of the total power. A 600 lines per mm grating was used to separate the scattered light into its components that were collected onto a Sincerity TE-cooled FI-UV-VIS detector. Three measurements in three different zones were collected for each sample, to assess the reproducibility of the measurement and the uniformity of the sample.

Refractive Index Measurement. A dilute suspension of particles dispersed in anhydrous THF was drop casted on a microscope slide within a vacuum grease ring. A cover slip was placed over the droplet of particles, which prevented the volatile solvent from evaporating. The refractive index of an isolated particle is measured by in-line Mie holography.³⁸ A plane wave (wavelength: 532 nm) illuminated the particle. The light scattered by the particle interfered with the incident beam onto the focal plane of an oil-immersed Olympus objective lens (x 100, NA 1.45). The resulting 2-dimensional pattern (Figure 4a) was then fit to the Lorenz-Mie theory, as detailed in reference 37. The obtained theoretical pattern (Figure 4b) captures the experimental pattern, as evidenced by the intensity profiles of the patterns, thus allowing for precise measurement of particle size and refractive index.

SUPPORTING INFORMATION:

Molecular structure of bis(N,N'-diisopropylbutylamidinate) dichlorosilane, TEM images of particles produced when sodium silicide is reacted with SiCl₂[BuC(NiPr)₂]₂ in toluene at 1.5:1 and 1:5 ratios, Powder X-ray diffractograms of all samples, TEM images from additional experiments varying the quantity of Si (IV) species and ligand separately to a fixed quantity of Na₄Si₄, TEM images from growth experiments stopped early, ToF-SIMS images, ATR-FTIR spectra of all samples, Additional experimental details, Distribution of measured indices computed from 170 interference pattern images (PDF)

ASSOCIATED CONTENT

Supporting Information is available free of charge via the Internet at <http://pubs.acs.org>.

AUTHOR INFORMATION

Corresponding Author

*patrick.rosa@icmcb.cnrs.fr

*mathieu.gonidec@icmcb.cnrs.fr

*glenna.drisko@icmcb.cnrs.fr

Author Contributions

All authors have given approval to the final version of the manuscript. GLD conceptualized the project. MAP, GLD, MG, and PR developed the methodology. MAP, SK, NF, AG, and YA participated in investigations. PR, MG, and GLD supervised the project. MAP, SB, and GLD wrote the original draft. All authors contributed to the reviewing and editing of the submitted version. GLD and DP acquired funding for the research. GLD was responsible for project administration. All authors have given approval to the final version of the manuscript.

DATA AVAILABILITY STATEMENT

Data for this article, including median particle size quantification, TEM bright field images, powder diffractograms, single attenuated total reflection Fourier transform infrared spectrometry, X-ray photoelectron spectra and Raman spectra are available at Zenodo at <http://dx.doi.org/10.5281/zenodo.12943336>.

ACKNOWLEDGMENT

MAP and GLD were supported by the European Research Council (ERC) under the European Union's Horizon 2020 research and innovation programme ("Scatter", Grant agreement No.948319). NF and YA acknowledge financial support from the European Union through the ERC under EMetBrown (ERC-CoG-101039103) grant. NF and YA also acknowledge financial support from the Agence Nationale de la Recherche under EMetBrown (ANR-21-ERCC-0010-01). GLD and YA received financial support from the *Agence Nationale de la Recherche* under the project "QLeviO" (Grant agreement No. ANR-21-CE30-0006-03). MAP takes part in the LIGHT S&T Graduate Program (PIA3 Investment for the Future Program, ANR-17-EURE-0027). A. G. and D. P. received funding from the ERC Consolidation Grant GENESIS under the European Union's Horizon 2020 research and innovation program (grant agreement No864850). Views and opinions expressed are however those of the authors only and do not necessarily reflect those of the European Union or the ERC. Neither the European Union nor the granting authority can be held responsible for them. TEM observations were performed on a microscope of the Plateforme Aquitaine de Caractérisation des Matériaux (PLACAMAT, UMS 3626, CNRS–Univ.de Bordeaux, Pessac, France). Eric Lebraud assisted in collecting powder XRD data through the XRD service of the ICMCB. Christine Labrugere collected XPS data and Jean-Paul Salvétat collected ToF-SIMS data at the PLACAMAT platform, Pessac, FR.

REFERENCES

1. Fang, J.; Wang, M.; Yao, K.; Zhang, T.; Krasnok, A.; Jiang, T.; Choi J.; Kahn E.; Korgel, B.A.; Terrones, M.; Li, X.; Alu A.; Zheng Y. Directional Modulation of Exciton Emission Using Single Dielectric Nanospheres. *Adv. Mater.* **2021**, 33 (20), 2007236.
2. Okazaki, T.; Sugimoto, H.; Hinamoto, T., Fujii M. Color Toning of Mie Resonant Silicon Nanoparticle Color Inks. *Adv. Optical Mater.* **2021**, 13 (11), 13613-13619.
3. Sugimoto, H.; Fujii, M. Broadband Dielectric–Metal Hybrid Nanoantenna: Silicon Nanoparticle on a Mirror. *ACS Photonics* **2018**, 5 (5), 1986-1993.

4. Negoro, H.; Sugimoto, H.; Hinamoto, T.; Fujii, M. Template-Assisted Self-Assembly of Colloidal Silicon Nanoparticles for All-Dielectric Nanoantenna. *Adv. Opt. Mat.* **2022**, *10* (8), 2102750.
5. Matushechkina, M.; Evlyukhin, A. B.; Zenin, V. A.; Heurs, M.; Chichkov, B. N. High-efficiency silicon metasurface mirror on a sapphire substrate. *Opt. Mater.* **2023**, *138*, 113618.
6. De Marco, M. L.; Semlali, S.; Korgel, B. A.; Barois, P.; Drisko, G. L.; Aymonier, C. Silicon-Based Dielectric Metamaterials: Focus on the Current Synthetic Challenges. *Angew. Chem., Int. Ed.* **2018**, *57* (17), 4478–4498.
7. Semlali, S.; Cormary, B.; De Marco, M. L.; Majimel, J.; Saquet, A.; Coppel, Y.; Gonidec, M.; Rosa, P.; Drisko, G. L. Effect of Solvent on Silicon Nanoparticle Formation and Size: A Mechanistic Study. *Nanoscale* **2019**, *11* (11), 4696–4700.
8. Baldwin, R. K.; Pettigrew, K. A.; Ratai, E.; Augustine, M. P.; Kauzlarich, S. M. Solution reduction synthesis of surface stabilized silicon nanoparticles. *Chem Commun.* **2002**, *17*, 1822–1823.
9. Pell, L. E.; Schriker, A. D.; Mikulec, F. V.; Korgel, B. A. Synthesis of amorphous silicon colloids by trisilane thermolysis in high temperature supercritical solvents. *Langmuir* **2004**, *20* (16), 6546–6548.
10. C. M.; Henderson, E. J.; Veinot, J. G. C. Hydrogen Silsesquioxane: A Molecular Precursor for Nanocrystalline Si–SiO₂ Composites and Freestanding Hydride-Surface-Terminated Silicon Nanoparticles. *Chem. Mater.* **2006**, *18* (26), 6139–6146.
11. Sun, W.; Qian, C.; Cui, X. S.; Wang, L.; Wei, M.; Casillas, G.; Helmy, A. S.; Ozin, G. A. Silicon monoxide – a convenient precursor for large scale synthesis of near infrared emitting monodisperse silicon nanocrystals. *Nanoscale* **2016**, *8* (6), 3678–3684.
12. Sugimoto, H.; Okazaki, T.; Fujii, M. Mie Resonator Color Inks of Monodispersed and Perfectly Spherical Crystalline Silicon Nanoparticles. *Adv. Opt. Mater.* **2020**, *8* (12), 2000033.
13. Wray, P. R.; Eslamisaray, M. A.; Nelson, G. M.; Ilic, O.; Kortshagen, U. R.; Atwater, H. A. Broadband, Angle- and Polarization-Invariant Antireflective and Absorbing Films by a Scalable Synthesis of Monodisperse Silicon Nanoparticles. *ACS Appl. Mater. Interfaces* **2022**, *14* (20), 23624–23636.
14. Eslamisaray, M. A.; Wray, P. R.; Lee, Y.; Nelson, G. M.; Ilic, O.; Atwater, H. A.; Kortshagen, U. R. A Single-Step Bottom-up Approach for Synthesis of Highly Uniform Mie-Resonant Crystalline Semiconductor Particles at Visible Wavelengths. *Nano Lett.* **2023**, *23* (5), 1930–1937.
15. Matioszek, D.; Ojo, W.-S.; Cornejo, A.; Katir, N.; El Ezzi, M.; Le Troedec, M.; Martinez, H.; Gornitzka, H.; Castel, A.; Nayral, C.; Delpech, F. From rational design of organometallic precursors to optimized synthesis of core/shell Ge/GeO₂ nanoparticles. *Dalton Trans.* **2015**, *44* (16), 7242–7250.
16. Lopez-Vinasco, A. M.; Martinez-Prieto, L. M.; Asensio, J. M.; Lecante, P.; Chardret, B.; Campora, J.; van Leeuwen, P. W. N. M. Novel nickel nanoparticles stabilized by imidazolium-amidinate ligands for selective hydrogenation of alkynes. *Catal. Sci. Technol.* **2020**, *10* (2), 342–350.
17. Ehinger, C.; Zhou, X.; Candrian, M.; Docherty, S. R.; Pollitt, S.; Coperet, C. Group 10 Metal Allyl Amidinates: A Family of Readily Accessible and Stable Molecular Precursors to Generate Supported Nanoparticles. *JACS Au* **2023**, *3* (8), 2314–2322.
18. Karsch, H. H.; Schuller, P. A.; Reisky, M. Bis(amidinate) Complexes of Silicon and Germanium. *Eur. J. Inorg. Chem.* **1998**, *4*, 433–436.
19. Parker, M. A.; De Marco, M. L.; Castro-Grijalba, A.; Ghoridi, A.; Portehault, D.; Pechev, S.; Hillard, E. A.; Lacomme, S.; Bessière, A.; Cunin, F.; Rosa, P.; Gonidec, M.; Drisko, G. L. Size-tunable silicon nanoparticles synthesized in solution via a redox reaction. *Nanoscale* **2024**, *16* (16), 7958–7964.
20. Song, Y.; Gómez-Recio, I.; Kumar, R.; Coelho Diogo, C.; Casale, S.; Géniois, I.; Portehault, D. A straightforward approach to high purity sodium silicide Na₄Si₄. *Dalton Trans.* **2021**, *50* (45), 16703–16710.
21. Bley, R. A.; Kauzlarich, S. M. A Low-Temperature Solution Phase Route for the Synthesis of Silicon Nanoclusters. *J. Am. Chem. Soc.* **1996**, *118* (49), 12461–12462.
22. Yang, C.; Bley, R. A.; Kauzlarich, S. M.; Lee, H. W.; Delgado, G. R. Synthesis of Alkyl-Terminated Silicon Nanoclusters by a Solution Route. *J. Am. Chem. Soc.* **1999**, *121* (22), 5191–5195.
23. Tokarsa, K.; Shi, Q.; Otulakowski, L.; Wrobel, P.; Ta, H. Q.; Kurtyka, P.; Kordyka, A.; Siwy, M.; Vasylieva, M.; Forsys, A.; Trzebicka, B.; Bachmatiuk, A.; Rummeli, M. H. Facile production of ultra-fine silicon nanoparticles. *R. Soc. Open Sci.* **2020**, *7*, 200736.
24. Mayeri, D.; Phillips, B. L.; Augustine, M. P.; Kauzlarich, S. M. NMR Study of the Synthesis of Alkyl-Terminated Silicon Nanoparticles from the Reaction of SiCl₄ with the Zintl Salt, NaSi. *Chem. Mater.* **2001**, *13* (3), 765–770.
25. Martinez-Prieto, L. M.; Cano, I.; Marquez, A.; Baquero, E. A.; Tricard, S.; Cusinato, L.; del Rosal, I.; Poteau, R.; Coppel, Y.; Philippot, K.; Chaudret, B.; Campora, J.; van Leeuwen, P. W. N. M. Zwitterionic amidinates as effective ligands for platinum nanoparticle hydrogenation catalysts. *Chem. Sci.* **2017**, *8* (4), 2931–2941.
26. Shrestha, S.; Wang, B.; Dutta, P. Nanoparticle processing: Understanding and controlling aggregation. *Adv. Colloid Interface Sci.* **2020**, *279*, 102162.
27. Launer, P. J. Infrared analysis of organosilicon compounds, Silicon Compounds: Silanes & Silicones, B. ArkesGelest Inc, Morrisville, PA, **2013**, pp. 175–178.
28. Dasog, M.; De los Reyes, G. B.; Titova, L. V.; Hegmann, F. A.; Veinot, J. G. C. Size vs Surface: Tuning the Photoluminescence of Freestanding Silicon Nanocrystals Across the Visible Spectrum via Surface Groups. *ACS Nano* **2014**, *8* (9), 9636–9648.
29. Lopez, T.; Mangolini, L.; Low activation energy for the crystallization of amorphous silicon nanoparticles. *Nanoscale* **2014**, *6* (3), 1286–1294.
30. Petkov, V.; Hessel, C. M.; Ovtchinnikov, J.; Guillaussier, A.; Korgel, B. A.; Liu, X.; Giordano, C. Structure–Properties Correlation in Si Nanoparticles by Total Scattering and Computer Simulations. *Chem. Mater.* **2013**, *25* (11), 2365–2371.
31. Faraci, G.; Gibilisco, S.; Russo, P.; Pennisi, A. R.; La Rosa, S. Modified Raman confinement model for Si nanocrystals. *Phys. Rev. B* **2006**, *73* (3), 033307.
32. Seidel, F.; Toader, I. G.; Koth, S.; Fritzsche, R.; Schafer, P.; Bulz, D.; Buchter, B.; Gordan, O. D.; Freitag, H.; Jakob, A.; Buschbeck, R.; Hietschold, M.; Lang, H.; Mehring, M.; Baumann, R.; Zahn, D. R. T. Flash lamp annealing of spray coated films containing oxidized or hydrogen terminated silicon nanoparticles. *Thin Solid Films* **2014**, *562* (7), 282–290.

33.Hong, W.E.; Ro, J.S. Kinetics of solid phase crystallization of amorphous silicon analyzed by Raman spectroscopy. *J. Appl. Phys.* **2013**, *114*, 073511.

34.Sagar, D.M.; Atkin, J.M. ; Pablomaki, P.K.B.; Neale, N.R.; Blackburn, J.L.; Johnson, J.C.; Nozik, A.J.; Raschke, M.B.; Beard, M.C.; Quantum Confined Electron-Phonon Interaction in Silicon Nanocrystals. *Nano Lett.*, 2015, *15* (3), 1511-1516.

35.Zhong F.; JIA, Z., Raman scattering study on pristine and oxidized n-type porous silicon. *Physica B*, 2013, *411*, 77-80.

36.Liu, L.Z. ; Wu, X.L. ; Zhang, Z.Y. ; Li, T.H.; Chu, P.K. Raman investigation of oxidation mechanism of silicon nanowires. *Appl. Phys. Lett.* **2009**, *95*, 093109.

37.Lavaud, M.; Salez, T.; Louyer, Y.; Amarouchene, Y. Stochastic inference of surface-induced effects using Brownian motion. *Phys. Rev. Research* **2021**, *3* (3), L032011.

38.Lee, S. H.; Roichman, Y.; Yi, G.-R.; Kim, S.-H.; Yang, S.-M.; van Blaaderen, A.; van Oostrum, P.; Grier, D. G. Characterizing and tracking single colloidal particles with video holographic microscopy. *Opt Express* **2007**, *15* (26), 18275-18282.