



# Development of copper free click chemistry active surfaces for bacteria trapping on porous silicon: gas phase silanisation and molecular dynamics simulations studies

Laetitia-Eiko Xerri, Thomas Gehin, Emmanuel Drouard, Rodolphe Antoine,  
Emmanuelle Laurenceau, Yann Chevolut, Christelle Yeromonahos

## ► To cite this version:

Laetitia-Eiko Xerri, Thomas Gehin, Emmanuel Drouard, Rodolphe Antoine, Emmanuelle Laurenceau, et al.. Development of copper free click chemistry active surfaces for bacteria trapping on porous silicon: gas phase silanisation and molecular dynamics simulations studies. Journée plénière 2024 du GDR-B2i, Jul 2024, Mulhouse (FR), France. hal-04725484

HAL Id: hal-04725484

<https://hal.science/hal-04725484v1>

Submitted on 18 Oct 2024

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

# Bacteria trapping on porous silicon: development of copper-free click-chemistry active surfaces

Laetitia-Eiko Xerri<sup>1</sup>, Thomas Gehin<sup>2</sup>, Yann Chevrolot<sup>2</sup>, Rodolphe Antoine<sup>3</sup>, Emmanuel Drouard<sup>1</sup>, Emmanuelle Laurenceau<sup>1</sup>, Christelle Yeromonahos<sup>1</sup>

<sup>1</sup> Ecole Centrale de Lyon, INSA Lyon, CNRS, Université Claude Bernard Lyon 1, CPE Lyon, INL, UMR5270, 69134 Ecully, France ; <sup>2</sup> CNRS, INSA Lyon, Ecole Centrale de Lyon, Université Claude Bernard Lyon 1, CPE Lyon, INL, UMR5270, 69134 Ecully, France, <sup>3</sup> Institut Lumière Matière UMR 5306, Université Claude Bernard Lyon 1, CNRS, Univ Lyon, F69100 Villeurbanne, France

Sepsis is a blood bacterial Infection that can lead to death in few hours in the most severe cases. Sepsis diagnosis requires blood culture for several days because of the low blood concentration of bacteria (1 CFU/mL) before mass spectrometry (MS) analysis.

Our objective is to develop chemically functionalised porous silicon (pSi) surfaces to trap selectively bacteria from blood and identify them by infrared desorption-ionisation on silicon (DIOS)-MS in few minutes.



Bacteria will be specifically trapped on the pSi surface thanks to immobilisation of a nanobody (Nb) via copper-free click reaction with dibenzocyclooctyne (DBCO-PEG-silane molecules) modified surfaces.

## Porosification

### Electrochemical etching

Silicon wafer parameters	
Resistivity	0.001-0.005 Ω.cm
Diameter	2"
Thickness	300 μm
Type	P, Boron doped
Orientation	100

Process parameters	
Current Density	200-2000 mA
Etching time	5-30 min
HF concentration	12,5%-37,5%




pSi : 20 nm diameter, 12 μm depth, 70% porosity

### pSi characteristics

Pores depth	3 - 30 μm
Pore size	10 - 100 nm
Porosity	35 - 80 %

## Molecular Dynamics Simulation


### Molecular Dynamics (MD) Simulation (Gromacs 2023.2)



SiO<sub>2</sub> surface modified by a mix DBCO-PEG34:PEG34 (1:1)

30 ns simulation, average of triplicate

Optimisation of the accessibility of the DBCO groups by tuning surface modification





## Surface functionalisation

### Gas Phase



Propyldimethylmethoxysilane (CH<sub>3</sub>-short)

20 Torr of silane at room temp., then 4h (16h) curing at 180°C (120°C)




### Liquid Phase

Dibenzocyclooctine-PEG(2000Da)-silane (DBCO-PEG)



### Adsorption of a nanobody(Nb) (3 orientations, 7 surfaces)



	Bare SiO <sub>2</sub>	CH <sub>3</sub> -short	PEG <sub>34</sub>	DBCO <sub>34</sub>	DBCO <sub>34</sub> :* PEG <sub>34</sub>	DBCO <sub>66</sub>	DBCO <sub>66</sub> :* PEG <sub>34</sub>
Most probable orientation	No Access.	Access.	No Access.	No Access.	Inter.	Inter.	Inter.
Relative E(kJ/mol)	1060	1389	760	394	287	0	604

\* 1:1 molecular ratio  
None of the surface gives any deformation of the Nb (RMSF<3A)  
CH<sub>3</sub>-short : gives an orientation compatible with bacteria trapping but is the less stable  
DBCO<sub>66</sub> : recognition site on the side but the highest stability

## Conclusion and Perspectives

Experimentally, we managed to make some reproducible protocols for each silane in two different ways. Furthermore, we successfully made some pSi with large pores (100 nm) even if we have to optimise the protocol to increase porosity. For the simulation, the deformation and the orientation of Nb were studied following physisorption. According to the simulation, CH<sub>3</sub>-short gives the orientation where the recognition site is accessible while the DBCO<sub>66</sub> gives the most stabilised system. We will investigate antifouling properties of the different surfaces by determining the structure of the interfacial water layer (water molecule diffusion coefficient, coordination number...), and graft a Nb with a covalent bond to look at the deformation of the recognition site. Then, these simulation works will be used to explain experimental results. The different pSi modified surfaces, presented above, will be elaborated (with at least pore diameter of 100 nm but 1 μm would be preferred if possible). Nb will be grafted by click-chemistry on the DBCO groups. Then, bacteria trapping efficiency will be evaluated by fluorescence spectroscopy, and compared to the results obtained with adsorbed Nb.

Acknowledgement: ANR MOONSTONE (Projet-ANR-22-CE42-0031), the cluster Newton of the PMCS2I Ecole Centrale de Lyon, the Nanolyon platform