
ChemNanoMat

Supporting Information

Efficient Electrocatalysts for Alkaline Oxygen Evolution Reaction from Wolframite Derived Heteroatom Materials

Linghui Li^[a], Sandrine Tusseau-Nenez^[b], Clément Marchat^[b], and Cédric Tard^{*[a]}

[a] L. Li, C. Tard

Laboratoire de Chimie Moléculaire (LCM), CNRS
École Polytechnique, Institut Polytechnique de Paris, 91120 Palaiseau, France
E-mail: cedric.tard@polytechnique.edu

[b] S. Tusseau-Nenez, C. Marchat

Laboratoire de Physique de la Matière Condensée (PMC), CNRS
École Polytechnique, Institut Polytechnique de Paris, 91120 Palaiseau, France

Table S1. Chemical composition by EDX of the $\text{Ni}_x\text{Mn}_{1-x}\text{WO}_4$ series.

Element	Atomic percentage					
	Formula	$\text{Ni}_{0.9}\text{Mn}_{0.1}\text{WO}_4$	$\text{Ni}_{0.75}\text{Mn}_{0.25}\text{WO}_4$	$\text{Ni}_{0.6}\text{Mn}_{0.4}\text{WO}_4$	$\text{Ni}_{0.5}\text{Mn}_{0.5}\text{WO}_4$	$\text{Ni}_{0.4}\text{Mn}_{0.6}\text{WO}_4$
Ni		91,45	78,99	62,31	50,61	42,18
Mn		8,55	21,01	37,69	49,39	57,82
$\Delta\%$		1,45	3,99	2,31	0,61	2,18
						4,89

EDX measurements of Ni and Mn composition for samples of different formula content x (0.9 to 0.25). The results are averaged values from spectra done on 1 to 3 area of each sample. The quantification was done using the Phi-Rho-Z model without standard. The samples surfaces were not flat surface as expected by the model but a layer of nanosized particles. For such surface and without standard, significant experimental error on the quantification have been observed in the literature.^[1] We considered a conservative absolute experimental error of 5 %. The observed differences between the measured and theoretical compositions ($\Delta\%$) of the samples ranged from 0.61 % to 4.89 % which is within the 5 % experimental error.

Table S2. Chemical composition by EDX of the $\text{Ni}_x\text{Mn}_{1-x}\text{WO}_4$ series.

Element	Atomic percentage					
	Formula	$\text{Ni}_{0.9}\text{Mn}_{0.1}\text{WO}_4$	$\text{Ni}_{0.75}\text{Mn}_{0.25}\text{WO}_4$	$\text{Ni}_{0.6}\text{Mn}_{0.4}\text{WO}_4$	$\text{Ni}_{0.5}\text{Mn}_{0.5}\text{WO}_4$	$\text{Ni}_{0.4}\text{Mn}_{0.6}\text{WO}_4$
Ni		91,45	78,99	62,31	50,61	42,18
Mn		8,55	21,01	37,69	49,39	57,82
$\Delta\%$		1,45	3,99	2,31	0,61	2,18
						4,89

Table S3. The overpotential value of $\text{M}_{1-x}\text{M}_{2(1-x)}\text{WO}_4$ at different current densities.

Samples	Overpotential (v vs. RHE) at 1 mA·cm ⁻²	Overpotential (v vs. RHE) at 5 mA·cm ⁻²	Overpotential (v vs. RHE) at 10 mA·cm ⁻²
$\text{Fe}_{0.5}\text{Ni}_{0.5}\text{WO}_4$	1.71	2.35	2.42
$\text{Co}_{0.5}\text{Mn}_{0.5}\text{WO}_4$	1.94	2.31	2.79
$\text{Fe}_{0.5}\text{Co}_{0.5}\text{WO}_4$	1.75	2.03	2.48
$\text{Ni}_{0.5}\text{Mn}_{0.5}\text{WO}_4$	1.63	1.75	1.83

Table S4. The overpotential value of $\text{Ni}_x\text{Mn}_{1-x}\text{WO}_4$ at different current densities.

Samples	Overpotential (v vs. RHE) at 1 mA·cm ⁻²	Overpotential (v vs. RHE) at 5 mA·cm ⁻²	Overpotential (v vs. RHE) at 10 mA·cm ⁻²
NiWO_4	1.85	2.58	2.68
$\text{Ni}_{0.9}\text{Mn}_{0.1}\text{WO}_4$	2.19	2.61	2.71
$\text{Ni}_{0.75}\text{Mn}_{0.25}\text{WO}_4$	2.26	2.74	2.87
$\text{Ni}_{0.6}\text{Mn}_{0.4}\text{WO}_4$	1.75	2.23	2.29
$\text{Ni}_{0.5}\text{Mn}_{0.5}\text{WO}_4$	1.61	1.76	1.83
$\text{Ni}_{0.4}\text{Mn}_{0.6}\text{WO}_4$	1.61	2.14	2.25
$\text{Ni}_{0.25}\text{Mn}_{0.75}\text{WO}_4$	1.97	2.60	2.76
MnWO_4	2.02	2.60	2.71

Table S5. Comparison of the onset potential, overpotential and Tafel plot of samples

Samples	Overpotential (v vs. RHE) at 10 mA·cm ⁻²	Tafel plot (mv·dec ⁻¹)
NiWO_4	2.68	399
$\text{Ni}_{0.9}\text{Mn}_{0.1}\text{WO}_4$	2.71	380
$\text{Ni}_{0.75}\text{Mn}_{0.25}\text{WO}_4$	2.87	322
$\text{Ni}_{0.6}\text{Mn}_{0.4}\text{WO}_4$	2.29	264
$\text{Ni}_{0.5}\text{Mn}_{0.5}\text{WO}_4$	1.83	247
$\text{Ni}_{0.4}\text{Mn}_{0.6}\text{WO}_4$	2.25	252
$\text{Ni}_{0.25}\text{Mn}_{0.75}\text{WO}_4$	2.76	379
MnWO_4	2.71	373




Figure S1. Rietveld plot for $\text{Ni}_{0.5}\text{Mn}_{0.5}\text{WO}_4$ sample.




Figure S2. XRD patterns for selected $\text{Ni}_x\text{Mn}_{1-x}\text{WO}_4$ samples




Figure S3. Chemical composition by EDX of the $\text{Ni}_x\text{Mn}_{1-x}\text{WO}_4$ series. Comparison of theoretical (black line) and measured (red square) nickel proportion for $\text{Ni}_x\text{Mn}_{1-x}\text{WO}_4$ series. The experimental error bar is represented by the red line.

References

- [1] Shirley, B., Jarochowska, E. Chemical characterisation is rough: the impact of topography and measurement parameters on energy-dispersive X-ray spectroscopy in biominerals. *Facies* **68**, 7 (2022). <https://doi.org/10.1007/s10347-022-00645-4>