



HAL
open science

Challenges in Nasal Cartilage Tissue Engineering to Restore the Shape and Function of the Nose

Delphine Vertu-Ciolino, Fanny Brunard, Edwin-Joffrey Courtial, Marielle Padeloup, Christophe André Marquette, Emeline Perrier-Groult, Frédéric Mallein-Gerin, Jean-Daniel Malcor

► To cite this version:

Delphine Vertu-Ciolino, Fanny Brunard, Edwin-Joffrey Courtial, Marielle Padeloup, Christophe André Marquette, et al.. Challenges in Nasal Cartilage Tissue Engineering to Restore the Shape and Function of the Nose. *Tissue Engineering Part B: Reviews*, 2024, 10.1089/ten.TEB.2023.0326 . hal-04731053

HAL Id: hal-04731053

<https://hal.science/hal-04731053v1>

Submitted on 11 Oct 2024

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

CHALLENGES IN NASAL CARTILAGE TISSUE ENGINEERING TO RESTORE THE SHAPE AND FUNCTION OF THE NOSE

Delphine Vertu-Ciolino^{1,2}, Fanny Brunard², Edwin-Joffrey Courtial³, Marielle Padeloup², Christophe André Marquette³, Emeline Perrier-Groult^{2†}, Frédéric Mallein-Gerin², Jean-Daniel Malcor^{2}*

1. Hospices Civils de Lyon, Hôpital Edouard Herriot, 5, place d'Arsonval, 69003 Lyon
2. Laboratory of Tissue Biology and Therapeutic Engineering, CNRS UMR 5305, University Claude Bernard-Lyon 1 and University of Lyon, 7 Passage du Vercors, 69367 Lyon Cedex 07, France
3. 3d.FAB, Univ Lyon, Université Lyon1, CNRS, INSA, CPE-Lyon, ICBMS, UMR 5246, 43, Bd du 11 novembre 1918, 69622 Villeurbanne Cedex, France

[†]Current address: IRMB, University of Montpellier, INSERM, 34000 Montpellier, France

*Corresponding author: Jean-Daniel Malcor. Email: jean-daniel.malcor@ibcp.fr

Contact information

Delphine Vertu-Ciolino : delphine.vertu-ciolino@chu-lyon.fr ; +33 (0)4 72 72 26 19 ; Hospices Civils de Lyon, Hôpital Edouard Herriot, 5, place d'Arsonval, 69003 Lyon

Fanny Brunard : fanny.brunard@ibcp.fr +33 (0)4 72 72 26 17 ; Laboratory of Tissue Biology and Therapeutic Engineering, CNRS UMR 5305, University Claude Bernard-Lyon 1 and University of Lyon, 7 Passage du Vercors, 69367 Lyon Cedex 07, France

Edwin-Joffrey Courtial : edwin.courtial@univ-lyon1.fr ; +33 (0)4 72 43 13 69 ; 3d.FAB, Univ Lyon, Université Lyon1, CNRS, INSA, CPE-Lyon, ICBMS, UMR 5246, 43, Bd du 11 novembre 1918, 69622 Villeurbanne Cedex, France

Marielle Padeloup : marielle.padeloup@ibcp.fr ; +33 (0)4 72 72 26 17 ; Laboratory of Tissue Biology and Therapeutic Engineering, CNRS UMR 5305, University Claude Bernard-Lyon 1 and University of Lyon, 7 Passage du Vercors, 69367 Lyon Cedex 07, France

Christophe André Marquette : christophe.marquette@univ-lyon1.fr ; +33 (0)4 72 43 13 69 ; 3d.FAB, Univ Lyon, Université Lyon1, CNRS, INSA, CPE-Lyon, ICBMS, UMR 5246, 43, Bd du 11 novembre 1918, 69622 Villeurbanne Cedex, France

Emeline Perrier-Groult : emeline.groult@inserm.fr ; +(33)-4-72-72-26-17 ; Institute for Regenerative Medicine & Biotherapy, Centre Hospitalier Régional Universitaire de Montpellier Hopital St Eloi 80 avenue Augustin Fliche 34295 Montpellier, 298 Rue du Truel, 34090 Montpellier

Frédéric Mallein-Gerin : f.mallein-gerin@ibcp.fr ; +33 (0)4 37 65 29 19 ; Laboratory of Tissue Biology and Therapeutic Engineering, CNRS UMR 5305, University Claude Bernard-Lyon 1 and University of Lyon, 7 Passage du Vercors, 69367 Lyon Cedex 07, France

Jean-Daniel Malcor : jean-daniel.malcor@ibcp.fr ; +33-(0)4-72-72-26-19 ; Laboratory of Tissue Biology and Therapeutic Engineering, CNRS UMR 5305, University Claude Bernard-Lyon 1 and University of Lyon, 7 Passage du Vercors, 69367 Lyon Cedex 07, France

Keywords

Tissue engineering ; Nasal septum cartilage repair ; biomaterials ; graft implantation.

Abstract

The repair of nasal septal cartilage is a key challenge in cosmetic and functional surgery of the nose, as it determines its shape and its respiratory function. Supporting the dorsum of the nose is essential for both the prevention of nasal obstruction and the restoration of the nose structure. Most surgical procedures to repair or modify the nasal septum focus on restoring the external aspect of the nose by placing a graft under the skin, without considering respiratory concerns. Tissue engineering offers a more satisfactory approach, in which both the structural and biological roles of the nose are restored. To achieve this goal, nasal cartilage engineering research has led to the development of scaffolds capable of accommodating cartilaginous ECM-producing cells, possessing mechanical properties close to those of the nasal septum, and retaining their structure after implantation *in vivo*. The combination of a non-resorbable core structure with suitable mechanical properties and a biocompatible hydrogel loaded with autologous chondrocytes or mesenchymal stem cells is a promising strategy. However, the stability and immunotolerance of these implants are crucial parameters to be monitored over the long term after *in vivo* implantation, in order to definitively assess the success of nasal cartilage tissue engineering. Here, we review the tissue engineering methods to repair nasal cartilage, focusing on the type and mechanical characteristics of the biomaterials; cell and implantation strategy; and the outcome with regard to cartilage repair.

Impact statement

Nasal septal cartilage is key to the cosmetic and function of the nose. To repair important damage to the nasal septum, current surgical techniques are complex and limited by graft source availability. Conversely, tissue engineering is a promising strategy to reproduce the dimensions and mechanical properties of the nose without causing donor site morbidity. This approach, however, remains overlooked for the reconstruction of the nasal septum compared to other cartilaginous tissues. This review describes the specific challenges associated with nasal cartilage repair and the pioneering studies leading to advances in the growing field of nose tissue engineering.

1. Introduction

The nasal septum is the cornerstone of the nasal framework, with morphological and respiratory functions. It is composed of cartilage, an avascular tissue with poor regenerative abilities. Consequently, the repair of traumatic, post-operative or constitutional lesions of the nasal septum represents a major medical challenge. For instance, the deviation of the nasal septum is thought to affect close to 90% of the general population (1). The nose is also exposed to multiple traumas, infections, and skin or mucosal tumors (2) that affect nasal morphology and respiratory function. Additionally, rhinoplasty, which involves altering the shape or size of the nose, is one of the most commonly performed surgical procedures (3), despite significant side effects (notably due to possible airway obstruction, which requires additional intervention (4)) and a high rate of patient dissatisfaction.

Following an accident or serious illness, patients hope to regain the best possible quality of life, which encompasses a state of physical, mental and social well-being (3). Indeed, as the nose is an important aesthetic marker, its deformities have a negative impact on the patient's psychological health (4), in addition to causing nasal airway obstruction. Reconstruction of the nose framework is thus essential. This commonly relies on grafting autologous tissue, in most cases rib cartilage, to replace the nasal septum, but this procedure is strongly limited by donor graft availability and may cause donor site morbidity (5). If the nasal envelope is also

damaged, skin and mucosal flaps are also needed, ideally from the forehead. Free skin flaps can alternatively be taken from the forearm in situations where facial skin is not available (6, 7). These are sometimes prepared with insertion of a framework under the skin prior to displacement, and are called composite flaps (8).

Nowadays, surgery is increasingly assisted by tissue engineering to avoid shortcomings such as harvesting a large amount of material from the patient (9-12). Like articular cartilage, the nasal cartilages are hyaline. Thus, although nasal cartilage engineering is a relatively recent area of research, it is likely to progress rapidly, as it will benefit from efforts devoted to articular cartilage engineering. In this context, the traditional paradigm of tissue engineering of combining biomaterials with cells and stimulating factors applies to nasal cartilage engineering as well. Thus, nasal cartilage engineering involves fabricating biocompatible cellular scaffolds with suitable biological and mechanical properties to restore the aspect and function of the nose, without eliciting immune or inflammatory response that may result in implant rejection. These biomaterials, assembled from biomolecules (such as collagen or alginate) or synthetic polymers (principally polycaprolactone), host chondrocytes or mesenchymal stem cells (MSCs) which are induced to undergo chondrogenesis under the influence of selected growth factors. Although non-resorbable materials (made for instance from MedPor or GoreTex) are routinely used to fabricate acellular nasal grafts, the progressive degradation and replacement of biomaterials by neo-synthesized extracellular matrix (ECM) significantly improve their integration within native tissues (13, 14). Mechanical properties may evolve over time, as the new ECM progressively replaces the biomaterial. At the same time, the neo-synthesized tissue must maintain its structural integrity and shape, to continuously provide support for the respiratory function of the nose (15-17).

A growing number of studies are investigating the stiffness, elasticity, and degradability of the biomaterial and of the engineered tissue, to compare them to native septal cartilage (17-24). Assessing the long-term evolution of such devices, however, remains a challenge. Preclinical trials are also hampered by the absence of an animal model with an external nose protruding from a flat face, which is a human specificity (25). This review aims to present the advances, short-comings and promising approaches in biomaterial design for nasal septum tissue engineering.

2. Anatomy of the nose

2.1 Structure and function of nasal cartilage

2.1.1. Structure of the nose. To support its structure and regulate airflow, the nose is composed of the following tissues, each possessing interactive functions: 1. The skin, the outer layer, provides a protection against external elements. 2. Fatty and fibromuscular layers separate the skin from the cartilage and mucosa below, and contribute to nose flexibility, shape and stability. 3. A mucosa rich in blood vessels nourishes nasal cartilage by imbibition. Its outermost subsection is exposed to airflow and acts as a protective barrier, while its innermost part, known as the perichondrium, is adjacent to cartilage. 4. The nasal bone forms the upper part of the nose, contributes to its overall structure and stability, and provides anchorage points for the nasal septum. 5. Finally, nasal cartilages (Figure1), which include: the upper lateral cartilage located below the nasal bone, forming soft lateral sidewalls; the lower lateral cartilage (also called alar cartilage) that determines the shape of the tip of the nose and the opening of the nostrils; and the nasal septum, located in a central position. The septum rests on the maxilla in front, joins the bony nose at the top and links

with the bony septum at the back. It divides the nose into two nasal cavities and it is structurally the most important cartilage component of the nose, supporting the upper and lower cartilages, as well as the overlying nasal skin.

2.1.2. Composition. Septal cartilage is a hyaline cartilage containing chondrocytes embedded in an ECM rich in GAGs (glycosaminoglycans) and collagen, with type II collagen being the most abundant. In its superficial zone, chondrocytes have an elongated morphology and are aligned parallel to the surface. There, collagen is also organized in thick sheets of fibers that orientate perpendicularly to the surface (26). In contrast, chondrocytes in the central zone are more rounded and collagen lacks a definite arrangement (this is also the case in alar cartilage). The GAG/collagen ratio also varies according to location within the septum, with a higher abundance of GAGs in the central zone and of collagen in the superficial zone (26). In addition, unlike other hyaline cartilages, the superficial zone of nasal septal cartilage contains nasoseptal progenitor cells (NSPs). This cell type shares surface markers and proliferation potential with MSCs, suggesting an intermediate state of differentiation between MSCs and chondrocytes (27, 28).

2.1.3. Function. The shape of the nose conditions nasal breathing in humans. Nasal permeability is essential to filter, warm and humidify the air, and regulate breathing by secreting mediators to the lungs and brain (29). The respiratory flow is conditioned by the intrathoracic depression and the shape of the nose. This shape is linked to the static calibre of the nasal cavities (affected by possible deviation of the nasal septum, or the thickness of the nasal mucosa (30)), as well as the capacity of the nose to resist dynamic inspiratory collapse (31). If the cartilaginous structure of the nose is not resistant enough, the airflow in the nasal cavity creates a transmural pressure differential which may lead to the collapse of the nasal nostrils by Venturi effect (32) and valve-related obstruction (33). As a consequence, the cartilage tissues of the nose have a crucial morphological and mechanical role. The nasal septum, in particular, maintains sufficient tension to prevent collapse during inspiratory flow.

2.2 Pathologies of nasal cartilage

Due to the avascular nature of the cartilage, injuries to the nasal septum do not have the ability to heal, and are at best filled with fibrous tissue. During development, septal cartilage is one of the drivers for the shaping of the face. Its growth is hampered by the nasal bone possessing a different embryonic origin and developing in the opposite way (34). Excess growth of nasal septum may exceed the capacity of the overlying skin, resulting in a deformation inside the nose with narrower zones that are responsible for a decrease in respiratory flow. Besides deformation due to extreme growth, the weakening or destruction of nasal septum is most often caused by trauma, prone to occur due to the protruding nature of the nasal pyramid.

Although trauma is often tolerated to some degree due to the elastic properties of cartilage, it can cause dislocation of the septum from the nasal bone and, in more severe cases, fracture. Following a fracture, nasal cartilage resistance is permanently altered and constraints exercised by the overlying skin will lead to additional deformation (35). Nasal cartilage loss may also result from cartilage infection (chondritis), or from excessive cartilage resection following rhinoplasty, an extremely frequent procedure that can lead to the iatrogenic loss of nose support (36). This deficiency can lead to a reduction of the size of the nasal cavities and subsequent static obstruction or collapse of the nasal cavities during inspiration, called the nasal valve phenomenon.

Following trauma, a hematoma appearing between the cartilage and the perichondrium can lead to prolonged ischemia and eventually to necrosis of the cartilage while the mucosa is still present (37). The nasal mucosa is also subjected to autoimmune (such as Wegener's or Churg-Strauss disease) and inflammatory (such as vasculitis) diseases. These lead to capillary damage and mucosal destruction, resulting in necrosis of the underlying cartilage, collapse of the nasal pyramid and nasal airway obstruction. Destruction of the nasal mucosa also occurs in cases of amputation of the nose following, for instance, excision of a tumor, or advanced burns. In such cases, the repair of the nasal septum is particularly challenging, as the mucosa (and potentially the overlying skin) must be replaced with vascularized tissue able to supply nutrients to the nasal cartilage (6). This procedure is demanding and technically very complex, with issues related to the availability of vascularized tissues. As an alternative, patients can use a removable prosthesis that is fixed to the skin on a daily basis with glue, magnets or anchor bolts, either as a permanent solution or while waiting for surgery (38).

3. Current surgical techniques

3.1 Cartilage grafts

Posteroinferior deformities of the nasal septum are the most common constitutional problems. The usual approach to nasal septoplasty is to remove the deformed areas without reconstruction, while preserving the anterior and superior part of the septal cartilage forming a square resting on the maxillary bone and joining the bony nose (Figure 2A). This L-shaped square is usually sufficient to preserve the shape of the nasal pyramid and its respiratory function (Figure 2B). However, if the anterior and superior zones of the septal cartilage are affected by deformities or are destroyed, an L-shaped cartilaginous structure (called L-strut) is reconstructed. The L-strut is completed with a dorsal graft at the top to enable interlocking with the bony nose, and spreader grafts on each side connecting the neo-septum to the upper lateral cartilage on each edge of the nose (Figure 3) (39). Whenever possible, grafts are sutured to the remaining native cartilage and surgical attachment to the bony nose is not required. This autologous grafting approach is highly preferred, as the grafts elicit little immunogenic responses and are very well accepted in an anatomical position. Autografts made from the posterior fragments of the septum are ideal, due to the adequate stiffness, thickness and straight morphology of septal cartilage. If there is not enough septum left to constitute an L-strut, autografts may be made from ear or rib cartilage instead. Autologous cartilage L-strut grafts are commonly performed on patients undergoing subtotal or total framework reconstruction of nasal defects, including for autoimmune, malignant, traumatic, and iatrogenic aetiologies (40-42). Clinical trials resulted in good aesthetic results as well as a clear improvement in nasal breathing. In addition, numerous clinical trials have been carried out using autologous cartilage in aesthetic augmentative rhinoplasty procedures (43-46). However, the deformation and resorption of the autologous grafts remained a major drawback, with costal cartilage frameworks undergoing deformation in almost 60% of cases (42).

However, the quality of the ear or rib cartilage is not identical to that of the septal cartilage and the available quantity is limited. Ear cartilage is not abundant enough and too thin to reconstruct the entire cartilaginous septum; its removal implies a skin scar, which is often not apparent but is likely to evolve into a hypertrophic or even keloid aspect; and there is a risk of pain and collateral deformation of the auricle (47). Moreover, the composition of ear cartilage is different from that of septal cartilage, with a higher elastin content associated with lower

tissue stiffness (48). Conversely, costal cartilage is relatively abundant compared to the dimensions of the nasal septum. Because of its availability and stiffness, it can alone replace the entire septum and provide the spreader grafts. Nevertheless, the thoracic scar is visible, and the harvesting site is very painful postoperatively. Complications such as pneumothorax, diaphragmatic hernia, or secondary deformation of the chest wall are also possible (49). This cartilage is also stiffer than the nasal septum, and may undergo unexpected deformation following surgery (50). The harvesting of cartilage grafts therefore entails morbidity at the donor site. Allografts represent an alternative to circumvent this issue, but are limited by donor availability and represent a higher risk of immune response. While the immunogenicity of cartilaginous allografts can be reduced by irradiation to remove resident cells (51-56), their use in nasal cartilage septoplasty remains understudied. Dorsal augmentations of the septum have also been performed with equine, porcine and caprine cartilage xenografts (57-59). Although these grafts provide good aesthetic results for augmentative rhinoplasty, they possess a high risk of immune reaction and rejection, as well as disease transmission.

3.2. Synthetic grafts

Synthetic materials such as Gore-Tex (made from expanded PTFE), MedPor (made from porous polyethylene) or silicone-based implants are commonly employed in septoplasty due to their availability in different sizes and shapes, their simple surgical use and their low cost. However, the ectopic implantation of such non-resorbable materials under the skin of the nose leads to high complication rates. These materials are considered biocompatible and non-toxic, but often lead to superinfection and rejection (in 21% of cases with MedPor (60)). Moreover, their excessive stiffness may result in extrusion and perforation of the skin (16). The behaviour of the skin above the implant is evaluated clinically, but no mechanical analyses has been performed, as these implants had no structural purpose. To date, the potential of these implants for functional purposes remains unknown.

As an example of a straightforward implantation of synthetic grafts in the nose, silicone prostheses have been used for nasal dorsum augmentation in surgeries aiming to “westernize” the nasal pyramid, a strong demand in Asia where noses are generally characterized by a low projection of the dorsum (61). These prostheses are positioned under the skin of the nose, above the nasal osteo-cartilaginous skeleton, in a non-anatomical position (Figure 2C). These non-degradable implants were not subjected to mechanical studies, as their design was not aimed at any functional role. Unfortunately, infection and spontaneous extrusion are favoured by the thinness of the integument covering these prostheses on the cutaneous or mucous side, and the frequency of trauma and micro-trauma to the nasal pyramid (due to nose blowing, scratching, dressing, practicing sports) (62). Additionally, a superinfected synthetic material cannot be cleared of germs and must be removed. Instead, biomaterials providing a suitable environment for cell activity and for the secretion of the ECM, to eventually constitute a cartilage tissue, represent a more promising class of medical devices (Figure 4A).

3.3. Challenges in nasal cartilage engineering

Tissue engineering aims to develop biomaterials that mimics the function of a healthy biological tissue. Hyaline cartilages are characterized by a very low cell density and a dense ECM (27, 63), giving the tissue its unique histological and mechanical characteristics. The particularity of the septal cartilage resides in its greater rigidity and lower elasticity than that of alar or auricle cartilages (48), providing shape stability and preventing fracture in the event

of minor trauma. However, the elastic behaviour of the septal cartilage is non-linear, which results in the possible fracture span style="font-family:'Times New Roman'">if the stress is too high (64). Moreover, since this tissue is not vascularized, the cartilage has no regenerative capability and the septum does not regain its overall mechanical characteristics following fracture. Thus, a major challenge in septal cartilage engineering is to develop an artificial tissue that mimics the unique elastic characteristics of human septal cartilage, so as to give shape and support to the lateral cartilages, while being well supported by the skin (65). Such engineered tissues must also resist contraction due wound healing and repeated long-term respiratory nasal valve deformation. As a consequence, evaluating the compressive or tensile modulus of biomaterials is a crucial step to predict their successful use in nasal cartilage engineering. In a biomimicry approach, this notably involves the production of a cartilaginous ECM with a high content in type II collagen and GAG by live cells seeded in biomaterials.

An additional obstacle is the protrusion and very thin overlying skin that are specific to the human nose, and not found in any animal model for preclinical studies. Thus, while implanting the prosthesis subcutaneously in animals (e.g. flat on the back of nude mice) enables testing of a certain resistance to skin tension, it does not reproduce the actual positioning of the nasal septum anatomically perpendicular to the skin. As a result, animal experimentation allows researchers to study the stability of the engineered nasal cartilage, but without replicating its true morphological or respiratory function.

4. Combining cells and biomaterial scaffolds for nasal cartilage engineering

4.1 Cells

Chondrocytes, the cellular components of cartilage, are the most intuitive cellular candidates for septum engineering. Human chondrocytes can be obtained by extraction from surgical septal residues, expanded *in vitro* and re-differentiated into chondrocytes using culture media containing Bone Morphogenic Protein 2 (BMP-2) (66). If the residual septum is not available in sufficient quantity, other cartilage tissues could serve as source of chondrocytes. However, the proliferative and chondrogenic capacity of chondrocytes varies according to their origin: auricular, nasal and costal chondrocytes could be easily amplified, but auricular and nasal chondrocytes generate better quality cartilage pellets than costal chondrocytes, as evidenced by higher production of type II collagen and proteoglycans (67). Moreover, nasal chondrocytes have a higher proliferative and chondrogenic capacity than articular chondrocytes (68), which has prompted clinical trials using autologous nasal chondrocytes for the treatment of focal traumatic lesions of articular cartilage (69). These data suggest that it will be more difficult to reconstruct good-quality nasal cartilage using non-nasal chondrocytes. Clinical trials using chondrocytes extracted from nasal septum for nasal reconstruction are underway, with very satisfactory initial results for functional alar lobule restoration (70).

Alternatively, mesenchymal stem cells can be preferred for their proliferative nature and versatility, and their potential to undergo chondrogenesis (71) in the presence of Transforming Growth Factor-beta 3 (TGF- β 3) (72). MSCs from adipose tissue (73-75), Wharton's jelly (76) or bone marrow (77-79) have already been successfully differentiated into ECM-producing chondrocytes. As the stabilization of the chondrocyte phenotype as well as the production of ECM by chondrocytes is favoured by a three-dimensional environment (80), cell matrices in the form of hydrogels are usually preferred to obtain a cartilage-like tissue.

Finally, NSPs are extremely promising cell candidates for cartilage tissue engineering. They have the potential to differentiate into a chondrogenic and osteogenic (but

not adipogenic) lineage (27) and they possess a proliferation potential similar or greater than MSCs (18, 81). However, the use of NSPs is highly limited by tissue availability, in particular for cases where the nasal septum has been heavily damaged or requires total replacement.

4.2 Materials for nose cartilage engineering

In the literature, the most frequently reported building block for producing biomaterials for nasal cartilage engineering is polycaprolactone (PCL) (17, 19, 28, 75, 82-88) (Table 1-3), followed by natural biomolecules such as alginate (23, 79, 89-91), collagen (24, 92-94), fibrin (21, 84), elastin (95), hyaluronic acid (24, 95) or gelatin (21, 24, 77, 84, 95, 96). As an example, alginate can be employed on its own as beads to encapsulate growth factors (89) or chondrocytes (23, 90, 91), leading to enhanced type II collagen and glycosaminoglycan (GAG) production. Importantly, PCL (17, 19, 28, 75, 82-86), as well as poly(glycolic acid), poly-L-lactic (22), type I collagen (93, 94) or hyaluronic acid (24), are compatible with 3D-printing, an advantage for reproducing the specific shape of patients' nasal cartilage, as part of personalized medicine approaches. As a synthetic alternative to PCL, polymers such as PLGA (78), poly(glycolic acid) (22) or poly(vinyl alcohol) (90) have shown promising results, with the GAG accumulation in constructs implanted subcutaneously in nude mice. Furthermore, in a comparative study involving six different scaffold types, polydioxanone, poly-3-hydroxybutyrate-co-3-hydroxyvalerate and PCL materials best supported cartilage ECM and GAG deposition (74).

4.3 Improving biomaterials for nasal cartilage engineering

Ideally, the hydrogels used for tissue repair should progressively degrade as they are replaced by the ECM secreted by seeded cells. The time required for this substitution to occur, however, is difficult to master, and few degradable hydrogels possess sufficient rigidity to withstand the mechanical stresses sustained by the native nasal septum. To solve this problem, a solid scaffold whose biomechanical properties mimic those of the native septum can be combined with a hydrogel (Figure 4 B-D) (17, 21, 75, 76, 88). The role of this solid scaffold is threefold:

- 1) - Ensure the structural integrity of the chondrocyte-containing hydrogel in areas exposed to mechanical loads. This notably involves preventing the hydrogel from collapsing under the stress imposed by the overlying nasal skin. Strong attachment of the hydrogel to the scaffold can be enhanced by maximizing contact between the gel and the scaffold, for example by creating pores and increasing the hydrophilicity of its surface.
- 2) - Determine the shape and volume of the tissue to be reconstructed. 3D printing technology is particularly well-suited, thanks to an automated manufacturing process that can generate scaffolds with precise geometries and internal architectures (such as pore size) which plays a critical role in tissue formation *in vitro* and *in vivo* (97, 98). This technology also allows scaffolds to be customized to suit patient- and clinical-specific needs.
- 3) - Provide mechanical properties to the hydrogel-scaffold construct that mimic those of the native septum. These properties can be adjusted by selecting the type, concentration and cross-linking method of the scaffold components.

As an example of combining robust scaffolds with softer but more biocompatible hydrogels, PCL combined with alginate formed 3D-printed biomaterials that stimulate ECM production by chondrocytes and are stable for 4 weeks after ectopic implantation in mice (85). PCL has also been combined with agarose (87), fibrin (84) and gelatin (19) to enhance cellular interactions, thus promoting cartilage tissue formation. In addition, the incorporation

of a decellularized matrix has proven to be a powerful tool for improving the adhesion, proliferation and viability of cells seeded onto scaffolds of PCL (88), chitosan and agarose (76) or fibrin cross-linked with genepin (21). However, even with a decellularized matrix, colonization of seeded cells throughout the scaffold structure remains a major challenge (73). To circumvent this problem, 3D bioprinting has been performed with bioinks encapsulated with live cells. Type I collagen or nanofibrillated cellulose/alginate were tested as a scaffolding material in combination with nasal chondrocytes or MSCs, but *in vivo* studies have been limited to subcutaneous implantation in nude mice (79, 99, 100).

5. Biocompatibility of reconstructed nasal cartilage

5.1 Mechanical properties

The mechanical properties of the nasal cartilage are highly dependent on its ECM composition, notably the collagen to GAG ratio (101). Ideally, engineered nasal cartilage constructs will aim to mimic the biomechanical properties of the native septum as close as possible (Table 1). Decellularized nasal cartilage may serve as a cellular scaffold, provided that the stability and rigidity of the ECM are preserved (20) or restored by chondrocyte culture over 6 weeks (18). In synthetic biomaterials, 3D-printing procedures has been employed to modulate Young's modulus, for instance in PCL-based biomaterials (87). A 3D-printing approach was also used to fabricate customized poly-L-lactic acid porous implants to reconstruct nasal septum perforations, designed with a topography that could accommodate nanoparticles for drug delivery applications (22). Further, the compressive or tensile modulus of engineered nasal septa were evaluated both *in vitro* in the presence of chondrocytes from the human nose (17, 28, 88, 89, 91, 94) or sheep condyle (19), or human MSCs (73); and *in vivo* with human (22, 23, 90, 92, 93, 95), rabbit articular (84) or goat ear (24) chondrocytes. Overall, following ECM deposition by cells seeded in PCL-based biomaterials, the measured biomechanical properties were akin to that of native nasal cartilage (17, 86). However, the mechanical evaluation of collagen/hyaluronic constructs over 8 weeks after *in vivo* implantation in mice showed insufficient resorption time and stiffness (24), although the deposition of cartilage ECM was promoted. With other biomolecules, cross-linking has been successfully used to modulate the stiffness and stability of fibrin (21) and gelatin (76, 77) hydrogels, but these remain considerably lower than those of native cartilage. Therefore, efforts to produce biomaterials that better mimic the mechanical properties of the nasal septum are still needed in the field, to ensure that the engineered cartilage is compatible with the respiratory function of the nose on the long term.

5.2 Degradability

Non-resorbable implants like Medpor (porous polyethylene), Gore-Tex or silicon that are often used in purely aesthetic procedures (for instance, to increase the profile line of the dorsum) are positioned ectopically under the overlying skin of the nose. These materials are considered biocompatible and non-toxic, however, their rate of rejection and superinfection in the nose is significant (60). Aesthetic results and complications were retrospectively evaluated after augmentation rhinoplasty (16), and showed that rejection rate and adverse evolution of the capsule around the implant are high, particularly with Medpor (60, 62). Further, mechanical analyses of these implants with no functional or biological aim remain overlooked to this day.

In parallel, efforts have been made to produce rhinoplasty implants with improved tolerability, using degradable materials. For instance, PCL has successfully been used as a scaffold to accommodate and provide a mid-term structural basis for hydrogels. In a first study, it was expected that PCL scaffolds filled with alginate gels or decellularized cartilage ECM loaded with human adipose-derived stem cells would change shape *in vivo* over time as the PCL degraded (75). However, in most reported cases, PCL scaffolds retained their structural integrity (85), including after 12 weeks of implantation (75) (although the formation of neo-cartilage was not significant in this case). Although it is very difficult to perform *in vivo* studies that cover this time frame, studying the evolution of PCL biomaterials on the long run is an essential step before initiating human translation procedures. To circumvent the problems of premature degradation of biomaterials, PCL scaffolds were mixed with graphene, a non-resorbable material, to provide a long-term biocompatible porous and elastic material with antibacterial properties (17).

The production of a cartilage ECM by cells seeded onto medical devices is key to their acceptance by the host following implantation, and thus to their biocompatibility (Table 2). However, the production and remodelling of neo-synthesized ECM is likely to modify their mechanical properties over time. For example, the mechanical strength of type I collagen hydrogels was increased two-fold after a 5-week subcutaneous implantation in mice, possibly due to the production of ECM by seeded chondrocytes (93). Similarly, alginate (23) or poly(glycolic acid) and poly-L-lactic (22) scaffolds containing chondrocytes and implanted subcutaneously in mice exhibited biomechanical properties that evolved toward those of native cartilage. The stiffness of alginate beads could also be improved by stimulating chondrocytes with growth factors (89). Furthermore, the combination of 3D printed alginate with cellulose, as well as chondrocytes co-cultured with bone marrow MSCs, showed improved maximum compression test (probably due to the neo-synthesis of the ECM, as the lifetime of natural polymers is expected to be short) over 60 days *in vivo* (79). Finally, in the decellularized matrix as well, the stiffness of the artificial cartilage increased over 6 weeks to approach the stiffness of native nasal cartilage (18).

5.3 *In vivo* response

To further investigate the potential of these biomaterials to repair damaged nasal cartilage, orthotopic implantations were performed (Table 3), first along the nasal septum in New Zealand White rabbits (77, 83, 84, 95). After 12 weeks, the PCL implants retained their shape and did not result in adverse distribution or inflammatory response (83, 84). However, new cartilage ECM was not detected in significant amounts, with the presence of vascularization instead (84). In comparison, biomolecule-based biomaterials, made from elastin/gelatin/hyaluronic acid composites (95) or photocrosslinked gelatin encapsulated with TGF- β 1 (77), showed improved septum repair. Orthotopic implantation has also been performed on the nasal tip of rats. In this case, the PLGA/alginate/acellular gelatin composite scaffold was loaded with TGF- β 3 to promote cellular homing of stem/progenitor cells from neighboring tissues, triggering cartilage tissue formation in the implanted scaffold (102). In addition, orthotopic implantation has been studied in minipigs, where PCL constructs were grafted to the nasal periosteum, showing good tolerance and cartilage repair over 6 months (82). We believe that orthotopic positioning of an entire artificial septum would help tissue engineers assess the ability of an implant to maintain nasal airway respiratory flow, but no animal model recapitulates the projected positioning of the human nose. As an alternative, mechanical investigations could

be conducted on cadavers. So far, in humans, implantation of synthetic nasal cartilage has been performed for restoration of the alar lobule after excision of skin cancer (92). In this first human trial, autologous chondrocytes were cultured on collagen membranes *in vitro* and then implanted as a support under the skin, with satisfactory morphological and functional results, without adverse effects. Overall, these results indicate that medical devices developed for nasal cartilage engineering elicit an appropriate host response, thus meeting key criteria for biocompatibility.

5.4 Biocompatibility requirements for clinical application

Regulatory bodies, such as the Food and Drug Administration (FDA) in the USA and the European Medicines Agency (EMA), require specific tests to be carried out in accordance with a series of standards developed by the International Organization for Standardization (ISO) to guarantee biocompatibility. Specifically, ISO 10993 tests are generally required to assess the safety of the implant material and its interaction with the human body. Tests typically relevant to nasal cartilage implants include:

- 1) - Cytotoxicity tests (ISO 10993-5) to assess the potential of the implant material or its extract to cause damage to cells. This is a pivotal prerequisite to the development of implants, and is routinely verified in tissue engineering studies for nasal cartilage repair both *in vitro* (17-20, 28, 73, 74, 76, 87-89, 91, 94) and *in vivo* (22-24, 75, 77-79, 84, 85, 90, 92, 93, 95).
- 2) - Implantation test (ISO 10993-6) to assess the tissue response to the implant material when implanted in the body. In a tissue engineering approach, this involves the progressive replacement of the biomaterial with neo-synthesized ECM. This aspect is notably central to the nasal cartilage repair studies reported in Table 2.
- 3) - Sensitization test or reactivity test (ISO 10993-10) to assess the potential of the implant material or its extracts to cause allergic reactions, irritation or inflammation. The lack of inflammation has been checked *in vivo* for implants made from PLGA (78), poly(glycolic acid) and poly-L-lactic (22), Poly(vinyl alcohol) and alginate (90), hyaluronic acid and collagen (24), elastin and gelatin (95), fibrin (84) and PCL (82, 83).
- 4) - Subacute and subchronic toxicity tests (ISO 10993-11) to assess the potential toxic effects of the implant material or its extract over a long period of exposure. The evolution of tissue engineering constructs in humans has so far been monitored up to 12 months and showed no adverse effects (92).

6. Future research and perspectives

Research on nasal cartilage engineering has suggested the possibility of generating a neo-synthesized ECM produced by cells seeded in biomaterials that replicate the characteristics of the native nasal septum. Such engineered cartilages constitute promising tools for the future development of medical devices that will assist surgeons in recapitulating the structural and respiratory function of the nose. Long-term mechanical measurements will help validate further the potential of candidate biomaterials for septum engineering. Future research in nose regenerative medicine may also include the analysis of macrophagic response following implantation, to assess the inflammatory effects of biomaterial degradation by-products. Additionally, the use of non- or minimally-invasive sensors would be of great interest for monitoring the quality of nasal cartilage reconstruction *in vivo*. Biosensors which are being used in microfluidic tissue engineering platforms could be employed to monitor cartilage-specific macromolecule secretion, inflammatory or immune markers, and chondrocyte behaviour *in situ*. Finally, the integration of the biomaterial into the native nasal mucosa will

be crucial to provide the engineered cartilage with nutrients and establish the clinical applicability of the biomaterials envisioned for nasal septum reconstruction.

Acknowledgment

We thank Monique Billaud from the Innovation Conception et Accompagnement pour la Pédagogie (ICAP) of the University of Lyon 1 for providing the illustrations presented in this review.

Funding

E.P.-G. and C.M. was supported by the “Fondation des Gueules Cassées” (2021) ; D.V.-C. was supported by the “Hospices Civils de Lyon” (2022) ; and F.M.-G. and J.-D.M. were supported by the Prematuration Program of the CNRS (2022).

Authorship confirmation statement

All author confirm that the manuscript has been read, reviewed and approved by all named authors, and that there are no other persons who satisfied the criteria for authorship but are not listed. The authors further confirm that the order of authors listed in the manuscript has been approved by all.

Contribution statement

Delphine Vertu-Ciolino: conceptualization, funding acquisition, writing (original draft), writing (review and editing)

Frédéric Mallein-Gerin: conceptualization, funding acquisition, project administration, writing (original draft), writing (review and editing)

Emeline Perrier-Groult: funding acquisition, project administration

Edwin-Joffrey Courtial: conceptualization

Christophe André Marquette: funding acquisition

Jean-Daniel Malcor: conceptualization, project administration, writing (original draft), writing (review and editing)

Conflicts of interest disclosure

All authors confirm that there are no known conflicts of interest associated with this publication and there has been no significant financial support for this work that could have influenced its outcome.

References

1. Mladina R, Cujic E, Subaric M, Vukovic K. Nasal septal deformities in ear, nose, and throat patients: an international study. *American journal of otolaryngology*. 2008;29(2):75-82.
2. Conte CC, Razack MS, Sako K. Skin cancer of the nose: options for reconstruction. *Journal of surgical oncology*. 1988;39(1):1-7.
3. Constitution of the World Health Organization. 1946;36(11):1315-23.
4. Rankin M, Borah GL. Perceived functional impact of abnormal facial appearance. *Plast Reconstr Surg*. 2003;111(7):2140-6; discussion 7-8.
5. Ho TT, Sykes K, Kriet JD, Humphrey C. Cartilage Graft Donor Site Morbidity following Rhinoplasty and Nasal Reconstruction. *Craniomaxillofacial trauma & reconstruction*. 2018;11(4):278-84.

6. Antunes MB, Chalian AA. Microvascular reconstruction of nasal defects. *Facial plastic surgery clinics of North America*. 2011;19(1):157-62.
7. Ahcan U, Didanovic V, Porcnik A. A Unique Method for Total Nasal Defect Reconstruction - Prefabricated Innervated Osteocutaneous Radial Forearm Free Flap. *Case reports in plastic surgery & hand surgery*. 2019;6(1):11-9.
8. Fujiwara M, Suzuki A, Mizukami T, Terai T, Fukamizu H. Prefabricated scalping forehead flap with skeletal support. *The Journal of craniofacial surgery*. 2009;20(4):1182-5.
9. Lavernia L, Brown WE, Wong BJF, Hu JC, Athanasiou KA. Toward tissue-engineering of nasal cartilages. *Acta Biomater*. 2019;88:42-56 [PubMed](#) .
10. Bagher Z, Asgari N, Bozorgmehr P, Kamrava SK, Alizadeh R, Seifalian A. Will Tissue-Engineering Strategies Bring New Hope for the Reconstruction of Nasal Septal Cartilage? *Curr Stem Cell Res Ther*. 2020;15(2):144-54.
11. Watson D, Reuther MS. Tissue-engineered cartilage for facial plastic surgery. *Current opinion in otolaryngology & head and neck surgery*. 2014;22(4):300-6.
12. Oseni AO, Butler PE, Seifalian AM. Nasal reconstruction using tissue engineered constructs: an update. *Annals of plastic surgery*. 2013;71(2):238-44.
13. Puelacher WC, Mooney D, Langer R, Upton J, Vacanti JP, Vacanti CA. Design of nasoseptal cartilage replacements synthesized from biodegradable polymers and chondrocytes. *Biomaterials*. 1994;15(10):774 [PubMed](#) -8.
14. Sun H, Mei L, Song C, Cui X, Wang P. The in vivo degradation, absorption and excretion of PCL-based implant. *Biomaterials*. 2006;27(9):1735 [PubMed](#) -40.
15. Massey CJ, Suh JD, Tessema B, Gray ST, Singh A. Biomaterials in Rhinology. *Otolaryngology–Head and Neck Surgery*. 2016;154(4):606-17.
16. Kim HS, Park SS, Kim MH, Kim MS, Kim SK, Lee KC. Problems associated with alloplastic materials in rhinoplasty. *Yonsei medical journal*. 2014;55(6):1617-23.
17. Rajzer I, Kurowska A, Jabłoński A, Kwiatkowski R, Piekarczyk W, Hajduga MB, et al. Scaffolds modified with graphene as future implants for nasal cartilage. *Journal of Materials Science*. 2020;55(9):4030-42.
18. Schwarz S, Elsaesser AF, Koerber L, Goldberg-Bockhorn E, Seitz AM, Bermueller C, et al. Processed xenogenic cartilage as innovative biomatrix for cartilage tissue engineering: effects on chondrocyte differentiation and function. *J Tissue Eng Regen Med*. 2015;9(12):E239-E51.
19. Ruiz-Cantu L, Gleadall A, Faris C, Segal J, Shakesheff K, Yang J. Multi-material 3D bioprinting of porous constructs for cartilage regeneration. *Materials Science and Engineering: C*. 2020;109:110578.
20. Graham ME, Gratzner PF, Bezuhly M, Hong P. Development and characterization of decellularized human nasoseptal cartilage matrix for use in tissue engineering. *The Laryngoscope*. 2016;126(10):2226 [PubMed](#) -31.
21. Gupta N, Cruz MA, Nasser P, Rosenberg JD, Iatridis JC. Fibrin-Genipin Hydrogel for Cartilage Tissue Engineering in Nasal Reconstruction. *The Annals of otology, rhinology, and laryngology*. 2019;128(7):640-6.
22. Xu Y, Fan F, Kang N, Wang S, You J, Wang H, et al. Tissue engineering of human nasal alar cartilage precisely by using three-dimensional printing. *Plast Reconstr Surg*. 2015;135(2):451-8.
23. Chang AA, Reuther MS, Briggs KK, Schumacher BL, Williams GM, Corr M, et al. In vivo implantation of tissue-engineered human nasal septal neocartilage constructs: a pilot study. *Otolaryngology–head and neck surgery : official journal of American Academy of Otolaryngology-Head and Neck Surgery*. 2012;146(1):46-52.

24. Xia H, Zhao D, Zhu H, Hua Y, Xiao K, Xu Y, et al. Lyophilized Scaffolds Fabricated from 3D-Printed Photocurable Natural Hydrogel for Cartilage Regeneration. *ACS applied materials & interfaces*. 2018;10(37):31704-15.
25. Nishimura T, Mori F, Hanida S, Kumahata K, Ishikawa S, Samarat K, et al. Impaired Air Conditioning within the Nasal Cavity in Flat-Faced Homo. *PLOS Computational Biology*. 2016;12(3):e1004807.
26. Brown WE, Lavernia L, Bielajew BJ, Hu JC, Athanasiou KA. Human nasal cartilage: Functional properties and structure-function relationships for the development of tissue engineering design criteria. *Acta Biomaterialia*. 2023;168:113-24 [PubMed](#) .
27. do Amaral RJ, Pedrosa Cda S, Kochem MC, Silva KR, Aniceto M, Claudio-da-Silva C, et al. Isolation of human nasoseptal chondrogenic cells: a promise for cartilage engineering. *Stem Cell Res*. 2012;8(2):292 [PubMed](#) -9.
28. Kim DH, Lim MH, Jeun JH, Park SH, Lee W, Park SH, et al. Evaluation of Polycaprolactone-Associated Human Nasal Chondrocytes as a Therapeutic Agent for Cartilage Repair. *Tissue engineering and regenerative medicine*. 2019;16(6):605-14.
29. Jankowski R, Nguyen DT, Poussel M, Chenuel B, Gallet P, Rumeau C. Sinusology. *European annals of otorhinolaryngology, head and neck diseases*. 2016;133(4):263-8.
30. Wittkopf M, Wittkopf J, Ries WR. The diagnosis and treatment of nasal valve collapse. *Current opinion in otolaryngology & head and neck surgery*. 2008;16(1):10-3.
31. Daniel RK, Palhazi P. The Nasal Ligaments and Tip Support in Rhinoplasty: An Anatomical Study. *Aesthetic surgery journal*. 2018;38(4):357-68.
32. Gagnieur P, Fieux M, Louis B, Béquignon E, Bartier S, Vertu-Ciolino D. Objective diagnosis of internal nasal valve collapse by four-phase rhinomanometry. *Laryngoscope investigative otolaryngology*. 2022;7(2):388-94.
33. Ishii LE, Rhee JS. Are diagnostic tests useful for nasal valve compromise? *The Laryngoscope*. 2013;123(1):7-8.
34. Jankowski R. Revisiting human nose anatomy: phylogenetic and ontogenic perspectives. *The Laryngoscope*. 2011;121(11):2461-7.
35. Klinginsmith M, Katrib Z. Nasal Septal Fracture. *StatPearls*. Treasure Island (FL): StatPearls Publishing
Copyright © 2022, StatPearls Publishing LLC.; 2022.
36. Yeo NK, Jang YJ. Rhinoplasty to correct nasal deformities in postseptoplasty patients. *American journal of rhinology & allergy*. 2009;23(5):540-5.
37. Savage RR, Valvich C. Hematoma of the nasal septum. *Pediatrics in review*. 2006;27(12):478-9.
38. D'Heygere V, Mattheis S, Stähr K, Bastian T, Höing B, Lang S, et al. Epithetic nasal reconstruction after total rhinectomy: Oncologic outcomes, immediate and long-term adverse effects, and quality of life. *Journal of plastic, reconstructive & aesthetic surgery : JPRAS*. 2021;74(3):625-31.
39. Terra Brito CL, Disant F. [The nasal framework in rhinoplasty and its dimensions: the importance of a third element]. *Revue de laryngologie - otologie - rhinologie*. 2010;131(2):119-23.
40. Apaydin F, Garcia RFF, Tas V. L-Strut Graft: A Very Versatile Graft in the Management of Crooked and Traumatic Noses. *Facial plastic surgery & aesthetic medicine*. 2021;23(2):110-7.
41. Ciolek PJ, Hanick AL, Roskies M, Fritz MA. Osseocartilaginous Rib Graft L-Strut for Nasal Framework Reconstruction. *Aesthetic surgery journal*. 2020;40(4):Np133-np40.

42. Haack S, Gubisch W. Reconstruction of the septum with an autogenous double-layered conchal L-strut. *Aesthetic plastic surgery*. 2014;38(5):912-22.
43. Kumar R, Darr A, Gill C, Bhamra N, Mistry N, Barraclough J. The Use of Auricular Cartilage Grafts in Septorhinoplasty: A Dual-Centre Study of Donor Site Patient-Reported Outcome Measures. *Cureus*. 2022;14(7):e26547.
44. Lee M, Callahan S, Cochran CS. Auricular cartilage: harvest technique and versatility in rhinoplasty. *American journal of otolaryngology*. 2011;32(6):547-52.
45. As'adi K, Salehi SH, Shoar S. Rib Diced Cartilage-Fascia Grafting in Dorsal Nasal Reconstruction: A Randomized Clinical Trial of Wrapping With Rectus Muscle Fascia vs Deep Temporal Fascia. *Aesthetic surgery journal*. 2014;34(6):Np21-31.
46. Cervelli V, Bottini DJ, Gentile P, Fantozzi L, Arpino A, Cannatà C, et al. Reconstruction of the nasal dorsum with autologous rib cartilage. *Annals of plastic surgery*. 2006;56(3):256-62.
47. Park TH, Park JH, Kim JK, Seo SW, Rah DK, Chang CH. Analysis of 15 cases of auricular keloids following conchal cartilage grafts in an asian population. *Aesthetic plastic surgery*. 2013;37(1):102-5.
48. Bos EJ, Pluemeekers M, Helder M, Kuzmin N, van der Laan K, Groot ML, et al. Structural and Mechanical Comparison of Human Ear, Alar, and Septal Cartilage. *Plastic and reconstructive surgery Global open*. 2018;6(1):e1610.
49. Marin VP, Landecker A, Gunter JP. Harvesting rib cartilage grafts for secondary rhinoplasty. *Plast Reconstr Surg*. 2008;121(4):1442-8.
50. Siegert R, Magritz R. Reducing the morbidity involved in harvesting autogenous rib cartilage. *Facial plastic surgery : FPS*. 2009;25(3):169-74.
51. Menger DJ, Nolst Trenité GJ. Irradiated homologous rib grafts in nasal reconstruction. *Archives of facial plastic surgery*. 2010;12(2):114-8.
52. Wee JH, Mun SJ, Na WS, Kim H, Park JH, Kim DK, et al. Autologous vs Irradiated Homologous Costal Cartilage as Graft Material in Rhinoplasty. *JAMA facial plastic surgery*. 2017;19(3):183-8.
53. Wan R, Weissman JP, Williams T, Ullrich PJ, Joshi C, Huffman K, et al. Prospective Clinical Trial Evaluating the Outcomes Associated with the Use of Fresh Frozen Allograft Cartilage in Rhinoplasty. *Plastic and reconstructive surgery Global open*. 2023;11(10):e5315.
54. Kridel RW, Ashoori F, Liu ES, Hart CG. Long-term use and follow-up of irradiated homologous costal cartilage grafts in the nose. *Archives of facial plastic surgery*. 2009;11(6):378-94.
55. Saadi R, Loloi J, Schaefer E, Lighthall JG. Outcomes of Cadaveric Allograft versus Autologous Cartilage Graft in Functional Septorhinoplasty. *Otolaryngology--head and neck surgery : official journal of American Academy of Otolaryngology-Head and Neck Surgery*. 2019;161(5):779-86.
56. Kadakia N, Nguyen C, Motakef S, Hill M, Gupta S. Is Irradiated Homologous Costal Cartilage Reliable? A Meta-Analysis of Complication Rates in Rhinoplasty. *Plastic surgery (Oakville, Ont)*. 2022;30(3):212-21.
57. Chang Y, Yun H, Choi JW, Suh JM, Jeong WS, Park H, et al. Efficacy and safety of equine cartilage for rhinoplasty: a multicenter double-blind non-inferiority randomized confirmatory clinical trial. *Archives of craniofacial surgery*. 2022;23(4):152-62.
58. Bhattacharya R, Das P, Joardar SN, Biswas BK, Batabyal S, Das PK, et al. Novel decellularized animal conchal cartilage graft for application in human patient. *J Tissue Eng Regen Med*. 2019;13(1):46-57.

59. Lin S, He Y, Tao M, Wang A, Ao Q. Fabrication and evaluation of an optimized xenogenic decellularized costal cartilage graft: preclinical studies of a novel biocompatible prosthesis for rhinoplasty. *Regenerative biomaterials*. 2021;8(6):rbab052.
60. Stelter K, Strieth S, Berghaus A. Porous polyethylene implants in revision rhinoplasty: chances and risks. *Rhinology*. 2007;45(4):325-31.
61. Kim IS. Augmentation Rhinoplasty Using Silicone Implants. *Facial plastic surgery clinics of North America*. 2018;26(3):285-93.
62. Patel K, Brandstetter K. Solid Implants in Facial Plastic Surgery: Potential Complications and How to Prevent Them. *Facial plastic surgery : FPS*. 2016;32(5):520-31.
63. Bleys RL, Popko M, De Groot JW, Huizing EH. Histological structure of the nasal cartilages and their perichondrial envelope. II. The perichondrial envelope of the septal and lobular cartilage. *Rhinology*. 2007;45(2):153-7.
64. Chang B, Reighard C, Flanagan C, Hollister S, Zopf D. Evaluation of human nasal cartilage nonlinear and rate dependent mechanical properties. *Journal of biomechanics*. 2020;100:109549.
65. Fertuzinhos A, Teixeira MA, Ferreira MG, Fernandes R, Correia R, Malheiro AR, et al. Thermo-Mechanical Behaviour of Human Nasal Cartilage. *Polymers*. 2020;12(1):177.
66. Hautier A, Salentey V, Aubert-Foucher E, Bougault C, Beauchef G, Ronzière MC, et al. Bone morphogenetic protein-2 stimulates chondrogenic expression in human nasal chondrocytes expanded in vitro. *Growth factors (Chur, Switzerland)*. 2008;26(4):201-11.
67. Tay AG, Farhadi J, Suetterlin R, Pierer G, Heberer M, Martin I. Cell yield, proliferation, and postexpansion differentiation capacity of human ear, nasal, and rib chondrocytes. *Tissue engineering*. 2004;10(5-6):762-70.
68. Kafienah W, Jakob M, Démarteau O, Frazer A, Barker MD, Martin I, et al. Three-dimensional tissue engineering of hyaline cartilage: comparison of adult nasal and articular chondrocytes. *Tissue engineering*. 2002;8(5):817-26.
69. Mumme M, Barbero A, Miot S, Wixmerten A, Feliciano S, Wolf F, et al. Nasal chondrocyte-based engineered autologous cartilage tissue for repair of articular cartilage defects: an observational first-in-human trial. *Lancet (London, England)*. 2016;388(10055):1985-94.
70. Fulco I, Miot S, Haug MD, Barbero A, Wixmerten A, Feliciano S, et al. Engineered autologous cartilage tissue for nasal reconstruction after tumour resection: an observational first-in-human trial. *The Lancet*. 2014;384(9940):337-46.
71. Fabre H, Ducret M, Degoul O, Rodriguez J, Perrier-Groult E, Aubert-Foucher E, et al. Characterization of Different Sources of Human MSCs Expanded in Serum-Free Conditions with Quantification of Chondrogenic Induction in 3D. *Stem cells international*. 2019;2019:2186728.
72. Na K, Kim S, Woo DG, Sun BK, Yang HN, Chung HM, et al. Synergistic effect of TGFbeta-3 on chondrogenic differentiation of rabbit chondrocytes in thermo-reversible hydrogel constructs blended with hyaluronic acid by in vivo test. *Journal of biotechnology*. 2007;128(2):412-22.
73. Kuhlmann C, Schenck TL, Tluczynski K, Aszodi A, Metzger P, Giunta R, et al. Experimental approach to nasal septal cartilage regeneration with adipose tissue-derived stem cells and decellularized porcine septal cartilage. *Xenotransplantation*. 2021;28(2):e12660.
74. San-Marina S, Sharma A, Voss SG, Janus JR, Hamilton GS, 3rd. Assessment of Scaffolding Properties for Chondrogenic Differentiation of Adipose-Derived Mesenchymal Stem Cells in Nasal Reconstruction. *JAMA facial plastic surgery*. 2017;19(2):108-14.
75. Yi H-G, Choi Y-J, Jung JW, Jang J, Song T-H, Chae S, et al. Three-dimensional printing of a patient-specific engineered nasal cartilage for augmentative rhinoplasty. *Journal of Tissue Engineering*. 2019;10:2041731418824797.

76. Saeedi Garakani S, Khanmohammadi M, Atoufi Z, Kamrava SK, Setayeshmehr M, Alizadeh R, et al. Fabrication of chitosan/agarose scaffolds containing extracellular matrix for tissue engineering applications. *Int J Biol Macromol*. 2020;143:533-45 [PubMed](#) .
77. Zhang D, Su Y, Sun P, Liu X, Zhang L, Ling X, et al. A TGF-loading hydrogel scaffold capable of promoting chondrogenic differentiation for repairing rabbit nasal septum cartilage defect. *Frontiers in bioengineering and biotechnology*. 2022;10:1057904.
78. Zhang J, Liu L, Gao Z, Li L, Feng X, Wu W, et al. Novel approach to engineer implantable nasal alar cartilage employing marrow precursor cell sheet and biodegradable scaffold. *Journal of oral and maxillofacial surgery : official journal of the American Association of Oral and Maxillofacial Surgeons*. 2009;67(2):257-64.
79. Möller T, Amoroso M, Hägg D, Brantsing C, Rotter N, Apelgren P, et al. In Vivo Chondrogenesis in 3D Bioprinted Human Cell-laden Hydrogel Constructs. *Plastic and reconstructive surgery Global open*. 2017;5(2):e1227.
80. Dufour A, Buffier M, Vertu-Ciolino D, Disant F, Mallein-Gerin F, Perrier-Groult E. Combination of bioactive factors and IEIK13 self-assembling peptide hydrogel promotes cartilage matrix production by human nasal chondrocytes. *J Biomed Mater Res A*. 2019;107(4):893-903.
81. Kim DH, Lim JY, Kim SW, Lee W, Park SH, Kwon MY, et al. Characteristics of Nasal Septal Cartilage-Derived Progenitor Cells during Prolonged Cultivation. *Otolaryngology--head and neck surgery : official journal of American Academy of Otolaryngology-Head and Neck Surgery*. 2018;159(4):774-82.
82. Wiggenhauser PS, Balmayor ER, Rotter N, Schantz JT. In vivo evaluation of a regenerative approach to nasal dorsum augmentation with a polycaprolactone-based implant. *European journal of medical research*. 2019;24(1):6.
83. Park SH, Yun BG, Won JY, Yun WS, Shim JH, Lim MH, et al. New application of three-dimensional printing biomaterial in nasal reconstruction. *The Laryngoscope*. 2017;127(5):1036-43.
84. Kim YS, Shin YS, Park DY, Choi JW, Park JK, Kim DH, et al. The Application of Three-Dimensional Printing in Animal Model of Augmentation Rhinoplasty. *Annals of biomedical engineering*. 2015;43(9):2153-62.
85. Kundu J, Shim J-H, Jang J, Kim S-W, Cho D-W. An additive manufacturing-based PCL-alginate-chondrocyte bioprinted scaffold for cartilage tissue engineering. *Journal of Tissue Engineering and Regenerative Medicine*. 2015;9(11):1286-97.
86. Hashimdeen SH, Thorogate R, Miodownik M, Edirisinghe MJ. Fabrication of bespoke nasal septal scaffolds. *Materials & Design*. 2016;90:403-9 [PubMed](#) .
87. Khan G, Kim DG, Nam SM, Choi YD, Park ES. Experimental study on polycaprolactone scaffold cell-based nasal implant using 3D printing. *Journal of plastic, reconstructive & aesthetic surgery : JPRAS*. 2022;75(10):3869 [PubMed](#) -76.
88. Wiggenhauser PS, Schwarz S, Koerber L, Hoffmann TK, Rotter N. Addition of decellularized extracellular matrix of porcine nasal cartilage improves cartilage regenerative capacities of PCL-based scaffolds in vitro. *J Mater Sci Mater Med*. 2019;30(11):121.
89. Alexander TH, Sage AB, Chen AC, Schumacher BL, Shelton E, Masuda K, et al. Insulin-like growth factor-I and growth differentiation factor-5 promote the formation of tissue-engineered human nasal septal cartilage. *Tissue engineering Part C, Methods*. 2010;16(5):1213 [PubMed](#) -21.

90. Bichara DA, Zhao X, Hwang NS, Bodugoz-Senturk H, Yaremchuk MJ, Randolph MA, et al. Porous poly(vinyl alcohol)-alginate gel hybrid construct for neocartilage formation using human nasoseptal cells. *The Journal of surgical research*. 2010;163(2):331-6.
91. Chia SH, Schumacher BL, Klein TJ, Thonar EJ, Masuda K, Sah RL, et al. Tissue-engineered human nasal septal cartilage using the alginate-recovered-chondrocyte method. *The Laryngoscope*. 2004;114(1):38-45.
92. Fulco I, Miot S, Haug MD, Barbero A, Wixmerten A, Feliciano S, et al. Engineered autologous cartilage tissue for nasal reconstruction after tumour resection: an observational first-in-human trial. *Lancet (London, England)*. 2014;384(9940):337-46.
93. Lan X, Liang Y, Erkut EJN, Kunze M, Mulet-Sierra A, Gong T, et al. Bioprinting of human nasoseptal chondrocytes-laden collagen hydrogel for cartilage tissue engineering. *Faseb j*. 2021;35(3):e21191.
94. Lan X, Liang Y, Vyhlidal M, Erkut EJ, Kunze M, Mulet-Sierra A, et al. In vitro maturation and in vivo stability of bioprinted human nasal cartilage. *J Tissue Eng*. 2022;13:20417314221086368.
95. Shokri A, Ramezani K, Jamalpour MR, Mohammadi C, Vahdatinia F, Irani AD, et al. In vivo efficacy of 3D-printed elastin-gelatin-hyaluronic acid scaffolds for regeneration of nasal septal cartilage defects. *Journal of biomedical materials research Part B, Applied biomaterials*. 2022;110(3):614-24.
96. Chiesa-Estomba CM, Aiastui A, González-Fernández I, Hernández-Moya R, Rodiño C, Delgado A, et al. Three-Dimensional Bioprinting Scaffolding for Nasal Cartilage Defects: A Systematic Review. *Tissue engineering and regenerative medicine*. 2021;18(3):343-53.
97. Nava MM, Draghi L, Giordano C, Pietrabissa R. The effect of scaffold pore size in cartilage tissue engineering. *Journal of applied biomaterials & functional materials*. 2016;14(3):e223-9.
98. Karageorgiou V, Kaplan D. Porosity of 3D biomaterial scaffolds and osteogenesis. *Biomaterials*. 2005;26(27):5474-91.
99. McMillan A, McMillan N, Gupta N, Kanotra SP, Salem AK. 3D Bioprinting in Otolaryngology: A Review. *Advanced Healthcare Materials*. 2023;12(19):2203268.
100. Apelgren P, Amoroso M, Lindahl A, Brantsing C, Rotter N, Gatenholm P, et al. Chondrocytes and stem cells in 3D-bioprinted structures create human cartilage in vivo. *PLOS ONE*. 2017;12(12):e0189428.
101. Watson D, Reuther MS, Wong VW, Sah RL, Masuda K, Briggs KK. Effect of hyaluronidase on tissue-engineered human septal cartilage. *The Laryngoscope*. 2016;126(9):1984-9.
102. Mendelson A, Ahn JM, Paluch K, Embree MC, Mao JJ. Engineered nasal cartilage by cell homing: a model for augmentative and reconstructive rhinoplasty. *Plast Reconstr Surg*. 2014;133(6):1344-53.

Figure Legends

Figure 1. Anatomy of human nasal cartilage. Views with skin removed to show upper (yellow) and lower (purple) lateral cartilages and septal cartilage (green). A) Frontal view. B) Inferior view. C) Side view.

Figure 2. A) Lateral view of the septal nasal cartilage (green). B) L-strut positioning to replace the native septal cartilage (green mesh). C) Positioning the nasal dorsum augmentation prosthesis (blue) on native septal cartilage (green).

Figure 3. Reconstruction of the nasal septum using the extracorporeal L-strut septoplasty technique. A) Cartilaginous pieces that will compose the L-strut. B) Lateral view of the assembled L-strut neo-septum. The spreader grafts connect the upper lateral cartilages and the dorsal graft connects the nose bone upwards. C) Upper view of the assembled L-strut.

Figure 4. A) Nasal septum engineering approaches consisting in combining cells with biomaterials. The resulting engineered septal cartilage can be implanted orthotopically to replace missing nasal septum. B-D) Example of a scaffold-hydrogel construct prototype. The scaffold determines the mechanical properties and the shape of the biomaterial, while the hydrogel provides the cellular micro-environment. B) A silicone scaffold was 3D-printed with a porous architecture; C) A chondrocyte-laden fibrin gel was cast into the 3D-printed scaffold; D) The construct was cultured *in vitro* for three weeks in the presence of a cocktail of chondrogenic factors. E) The construct was then implanted in the back of a nude mouse to verify its stability. The photograph shows the reconstituted cartilage tissue after explant.




Figure 1




Figure 2




Figure 3








Figure 4

Table 1. Mechanical properties of scaffolds developed for nasal cartilage engineering

Scaffold material	Mechanical tests	Mechanical properties	Ref.
Decellularized porcine nasal septum cartilage ECM	Linear modulus determined after a uniaxial confined compression test.	Native cartilage rigidity (6.5 MPa) decreased after decellularization (1.92 MPa), and progressively increased in cell culture (4.9 MPa after 42 days) due to ECM production by chondrocytes.	Schwarz et al. 2015 (18)
Alginate beads	Confined compressive modulus.	IGF-1 and GDF-5 growth factors supplemented in chondrocyte culture influenced ECM production, and in turn the biomechanical properties of the engineered tissue.	Alexander et al. 2010 (89)
PCL and graphene	Young's modulus, tensile strength and strain at break.	Mechanical properties were measured for PCL biomaterials containing 0% to 10% of graphene. The presence of up to 5% of graphene improved tensile strength and strain at break.	Rajzer et al. 2020 (17)
PCL and gelatin methacrylate	Compressive Young's modulus and dynamic modulus.	Complex modulus increased as the concentration of gelatin methacrylate rose from 10% (400 Pa) to 20% (650 Pa). Further, Young's modulus increased over 50 days in culture, due to tissue maturation and increase in collagen content.	Ruiz-Cantu et al. 2020 (19)
Chitosan, agarose and decellularized nasal septum ECM	Viscosity, loss modulus, storage modulus.	The addition of decellularized ECM to agarose and chitosan gels increased their modulus and made them more elastic. Further, the addition of ECM slowed degradation, and made the structure of the hydrogels more compact.	Garakani et al. 2019 (76)
Decellularized nasal septum cartilage ECM	Tensile strength and Young's modulus.	No significant differences in mechanical properties between fresh and decellularized samples were observed.	Graham et al. 2016 (20)
Fibrin-genipin with decellularized bovine annulus fibrosus ECM	Compressive, tensile and dynamic modulus.	Genipin increased the mechanical properties of fibrin gels (200, 281 and 82 kPa for compressive, tensile and complex modulus respectively), but adding ECM decreases them (180, 190 and 59 kPa respectively). Furthermore, these hydrogels did not achieve the mechanical properties of a native nasal septum (900, 4000 and 200 kPa respectively).	Gupta et al. 2019 (21)
PCL	Young modulus measured by AFM and viscosity.	Viscosity and Young's modulus increased as the PCL polymer concentration rose from 15wt% to 12wt%.	Hashimdeen et al. 2016 (86)
Poly(glycolic acid) and poly-L-lactic	Compressive Young's modulus.	Young's modulus of engineered cartilage after <i>in vivo</i> implantation (8.60 MPa) was significantly higher than <i>in vitro</i> (3.00 MPa) and comparable to native cartilage (7.46 MPa).	Xu et al. 2015 (22)
Alginate	Tensile modulus.	Biomechanical properties were influenced by chondrocyte matrix production and increased over 60 days of culture (1.15 MPa). After 2 months, the tensile strength of the constructs was similar to native septal cartilage (3.01 MPa).	Chang et al. 2011 (23)
Poly(vinyl alcohol) and alginate	Compressive modulus.	Compressive modulus increased after 6 weeks following <i>in vivo</i> implantation. Prior cell culture in a spinner flask bioreactor over 10 days further improved compressive modulus.	Bichara et al. 2010 (90)
Type I collagen	Three-point bending modulus.	The mechanical strength of 3D-printed engineered cartilage constructs increased two-fold 5 weeks following implantation.	Lan et al. 2022 (93)
Nano-fibrillated cellulose and alginate	Maximum compressive stress.	Stiffness of the 3D-printed constructs increased after 60 days following implantation <i>in vivo</i> .	Möller et al. 2017 (79)
Hyaluronic acid and collagen	Compressive Young's modulus and maximum compressive stress	Collagen-hyaluronic acid constructs were lyophilized to improve their stability and mechanical strength. However, scaffold rigidity remains suboptimal for nasal cartilage repair.	Xia et al. 2018 (24)

Gelatin methacrylate	Compressive Young's modulus.	The crosslinking of gelatin through methacrylate groups enabled adjustment of hydrogel stiffness. Overall, stiffness increased with increasing GelMA concentrations.	Zhang et al. 2022 (77)
----------------------	------------------------------	--	------------------------

Table 2. Neocartilage ECM production in cellularized biomaterials for nasal cartilage engineering

Scaffold material	Cell type	<i>In vitro</i> cartilage ECM production	Ref.
PCL	Human nasal chondrocytes	After 24h, chondrocytes were viable and expressed aggrecan, collagen and Sox9 at the protein level.	Kim et al. 2019 (28)
PCL and porcine decellularized matrix	Human nasal chondrocytes	The combination of decellularized matrix to PCL scaffolds enables better cartilage regeneration while maintaining the stability of PCL.	Wiggenhauser et al. 2019 (88)
Alginate	Human nasal chondrocytes	Chondrocytes cultured in alginate produced significantly more GAG and collagen type II.	Chia et al. 2004 (91)
Decellularized porcine nasal septal cartilage	Human adipose stem cells	Adipose stem cells cultured in decellularized matrix over 6 weeks showed increased ECM deposition in the presence of chondrogenic media. These cells, however, invaded only the superficial parts of the decellularized matrix.	Kuhlmann et al. 2020 (73)
Polydioxanone, poly-3-hydroxybutyrate-co-3-hydroxyvalerate, PCL, poly(L-lactide-co-caprolactone), poly(lactic-co-glycolic acid) or polystyrene	Rabbit adipose mesenchymal stem cells	Scaffold coating with poly-lysine and laminin improved cell adhesion. Polydioxanone, poly-3-hydroxybutyrate-co-3-hydroxyvalerate and PCL materials enhanced cartilage ECM and GAG deposition.	San-Marina et al. 2017 (74)
PCL and agarose	Chondrocytes, Fibroblasts or diced cartilage	PCL hydrogels encapsulated with agarose and fibroblasts enabled cartilage tissue formation.	Khan et al. 2022 (87)
Decellularized porcine nasal septum cartilage ECM	Human nasal chondrocytes	Chondrocytes cultured in decellularized matrix over 6 weeks synthesized collagen type II and GAGs.	Schwarz et al. 2015 (18)
Alginate beads	Human nasal chondrocytes	Growth factors IGF-1 and GDF-5 enhanced GAG and type II collagen production, as well as confined compressive modulus.	Alexander et al. 2010 (89)
PCL and graphene	Human nasal chondrocytes	PCL-graphene constructs were biocompatible and supported cartilage ECM production.	Rajzer et al. 2020 (17)
Type I collagen	Human nasal chondrocytes	Encapsulated chondrocytes produced similar quantities of GAGs as native cartilage and expressed <i>ACAN</i> , <i>COL2</i> , <i>Sox9</i> and <i>Col10</i> , suggesting the re-differentiation of chondrocytes following expansion.	Lan et al. 2021 (94)
PCL and gelatin	Chondrocytes from sheep condyle	Gelatin-PCL constructs supported cell proliferation and cartilage ECM production. However, the rigidity of the constructs remained lower than that of the native septum.	Ruiz-Cantu et al. 2020 (19)
Chitosan, agarose and decellularized nasal septum ECM	Wharton's jelly mesenchymal stem cells	Hydrogels degraded by around 50% after 200 hours and 70-90% after 450 hours. The combination of decellularized matrix to chitosan-agarose scaffolds improved cell viability, adhesion and proliferation.	Garakani et al. 2019 (76)
Decellularized nasal septum cartilage ECM	HEK293 cells	Decellularized ECM did not show any cytotoxicity and enabled HEK293 proliferation.	Graham et al. 2016 (20)

Table 3. Host response of biomaterials developed for nasal cartilage engineering implanted *in vivo*.

Scaffold material	Cell type	Positioning of the implant	<i>In vivo</i> response	Ref.
PCL-alginate	Human nasal chondrocytes	Ectopic. Implantation under the skin of nude-mice	PCL-alginate constructs were stable 4 weeks following implantation <i>in vivo</i> and encapsulated chondrocytes synthesized collagen type II and GAGs.	Kundu et al. 2015 (85)
PCL and alginate or decellularized cartilage	Human adipose-derived stem cells	Ectopic. Implantation under the skin of nude-mice	No scaffold deformation was observed after 6 and 12 weeks. The implants were covered with blood vessels and completely filled with neo-tissue after 12 weeks. In addition, no blood vessel network was observed in the internal region of the implants. Hypoxia was rarely generated in the implants, which implies that their architecture allowed sufficient oxygen and nutrients transfer. Encapsulated chondrocytes showed increased <i>Col2</i> , <i>Sox9</i> and <i>ACAN</i> expression, as well type II collagen and aggrecan production, with decellularized cartilage ECM.	Yi et al. 2019 (75)
PLGA	Rabbit marrow precursor cells	Ectopic. Implantation under the skin of nude-mice	Marrow precursor cell sheets lining PLGA scaffolds formed an alar cartilage graft, with increased GAG accumulation 4 weeks after implantation <i>in vivo</i> . Macroscopically, no inflammation, infection, or extrusion was observed postoperatively.	Zhang et al. 2009 (78)
Poly(glycolic acid) and poly-L-lactic	Human nasal chondrocytes	Ectopic. Implantation under the skin of nude-mice	3D-printing was used to reproduce precisely the shape of alar cartilage. These patient-specific constructs maintained their length and width after implantation <i>in vivo</i> . No inflammation, infection, or extrusion was observed in any of the animals.	Xu et al. 2015 (22)
Alginate	Human nasal chondrocytes	Ectopic. Implantation under the skin of nude-mice	In scaffolds implanted <i>in vivo</i> , the expression of type II collagen increased with time, while type I collagen and GAGs decreased. Infection and extrusion were not observed during the course of the study. Upon recovery, each cartilage construct was surrounded by a thin fibrous capsule, separating the neocartilage from the murine tissue.	Chang et al. 2011 (23)
Poly(vinyl alcohol) and alginate	Human nasal chondrocytes	Ectopic. Implantation under the skin of nude-mice	Cell-laden flexible PVA-alginate hydrogels implanted for 6 weeks resulted in a GAG-rich engineered tissue. There were no signs of extrusion, inflammation, or foreign-body reaction. A fibrous capsule surrounded the constructs and was easily removed.	Bichara et al. 2010 (90)
Type I collagen	Human nasal chondrocytes	Ectopic. Implantation under the skin of nude-mice	Markers for cartilage increased over 9 weeks <i>in vitro</i> in the presence of TGF- β 3. However, while type II collagen expression remained unchanged, Safranin O staining decreased after <i>in vivo</i> implantation. There was no evidence of blood vessel invasion, bone growth, or mineralization in the cell-laden constructs. Macrophages were observed in these constructs.	Lan et al. 2022 (93)
Nano-fibrillated cellulose and alginate	Human nasal chondrocytes and bone marrow MSCs	Ectopic. Implantation subcutaneously in Balb-C mice	Scaffolds maintained their structural integrity 60 days following <i>in vivo</i> implantation. Co-cultures of chondrocytes and bone marrow stem cells showed improved proliferation and type II collagen deposition.	Möller et al. 2017 (79)
Hyaluronic acid and collagen	Goat ear cartilage-derived chondrocytes	Ectopic. Implantation in nude mice and autologous implantation in goat	The resulting scaffolds enabled cartilage ECM production during 8 weeks <i>in vivo</i> . No evident inflammatory reaction was observed.	Xia et al. 2018 (24)
Collagen membranes	Human nasal chondrocytes	Orthotopic. Implantation in humans after tumour excision	After 12 months, implants resulted in functional and aesthetically satisfying nasal repair, and no adverse effects were recorded. The implanted fibrocartilaginous grafts were remodelled into fibromuscular fatty structures similar to the tissue at the site of implantation.	Fulco et al. (92)
Elastin-gelatin-hyaluronic acid	Autologous/ homologous auricular chondrocytes	Orthotopic. Implantation in New Zealand white rabbits	Scaffolds seeded with autologous chondrocytes showed improved regeneration of the nasal septum. More cases of inflammation were detected when homologous instead of autologous cells were used. Homologous cells, but not autologous cells, also resulted in cases of tissue granulation and calcification.	Shokri et al. 2021 (95)
PCL and fibrin	Rabbit articular chondrocytes	Orthotopic. Implantation on the nasal periosteum in rabbits	PCL scaffolds seeded with chondrocyte-embedded fibrin gels maintained their shape 12 weeks following implantation. Formation of neo-cartilage, however, was not significant. Instead, the formation of new vessels in the central portion of the scaffolds and an inflammation with minimal positive staining for macrophages were observed.	Kim et al. 2015 (84)
PCL	Acellular	Orthotopic. Implantation in New Zealand white rabbits along the native septum	The implant was stable over 3 months, and did not result in unwanted biodistribution, postoperative complications (graft extrusion, skin infection, wound dehiscence) or important inflammatory response were observed. Macrophages were observed at 4 and 8 weeks, but their presence decreased over time. Vascular structures were detected at 4, 8, and 12 weeks.	Park et al. 2017 (83)
PCL	Acellular	Orthotopic. Implantation over the nasal periosteum in minipigs	This preclinical study in minipigs demonstrates that PCL-based implants are tolerated 6 months following implantation and are suitable for <i>in vivo</i> cartilage regeneration. There were no signs of a foreign-body reaction, infection or unexpected allocation of inflammatory cells. Capillary, arterial, and venous structures were observed within the scaffolds indicating the presence of vascularization.	Wiggenhauser et al. 2019 (82)
Porous PLGA with alginate and gelatin microspheres	Acellular	Orthotopic. Implantation in Sprague Dawley rats onto the nasal tip	TGF- β 3 encapsulated in gelatin microspheres induced homing of stem/progenitor cell from native cartilage and cartilage tissue formation.	Mendelson et al. 2014 (102)
Gelatin methacrylate	Rabbit bone marrow stem cells	Orthotopic. Implantation in New Zealand white rabbits	The encapsulation of TGF- β 1 in hydrogels prompted chondrogenic differentiation <i>in vitro</i> , and repair of nasal septum <i>in vivo</i> . Nasal cartilage showed very little immune cell infiltration and no signs of fibrotic tissue.	Zhang et al. 2022 (77)