



**HAL**  
open science

## Efficient and stable photocatalyst for photoelectrochemical splitting of water

Andreas Zerr, Eduard Feldbach, Tavo Romann, Rasmus Seerma, Marco Kirm

► **To cite this version:**

Andreas Zerr, Eduard Feldbach, Tavo Romann, Rasmus Seerma, Marco Kirm. Efficient and stable photocatalyst for photoelectrochemical splitting of water. 8th Baltic Electrochemistry Conference: Finding New Inspiration 2 (BEChem2024), Apr 2024, Tartu, Estonia. hal-04750940

**HAL Id: hal-04750940**

**<https://hal.science/hal-04750940v1>**

Submitted on 24 Oct 2024

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

# Efficient and stable photocatalyst for photoelectrochemical splitting of water

Andreas Zerr<sup>1</sup>, Eduard Feldbach<sup>2,\*</sup>, Tavo Romann<sup>3</sup>, Rasmus Seerma<sup>2</sup>, Marco Kirm<sup>2</sup>

<sup>1</sup>LSPM-CNRS, Université Sorbonne Paris Nord, France


<sup>2</sup>Institute of Physics, University of Tartu, Estonia

<sup>3</sup>Institute of Chemistry, University of Tartu, Estonia

\*[eduard.feldbach@ut.ee](mailto:eduard.feldbach@ut.ee)

The commercialization of photoelectrochemical (PEC) water splitting technology requires an efficient, stable, long service life, low price, and production scalable photocatalyst. Inspired by earlier publications of competing teams and knowledge of the material by the French partner, the project team is synthesizing and investigating the spinel-structured  $\gamma$ - $\text{Sn}_3\text{N}_4$ , expected to be suitable for the efficient PEC splitting of water. Two synthesis methods were tested. Firstly, the synthesis of microscopic amounts of the oxygen-free  $\gamma$ - $\text{Sn}_3\text{N}_4$  via the reaction of elemental tin with molecular nitrogen,  $3 \cdot \text{Sn} + 2 \cdot \text{N}_2 \rightarrow \gamma\text{-Sn}_3\text{N}_4$ , in a laser heated diamond anvil cell (LH-DAC) was successfully accomplished<sup>1</sup>. The compound formed at pressures between 15.7 GPa and 20 GPa and temperatures  $\sim 2000^\circ\text{C}$ . However, the presence of unreacted tin was recognized even though nitrogen was introduced in excess.

Secondly, RF-magnetron sputtering was applied to deposit films of  $\gamma$ - $\text{Sn}_3\text{N}_4$  on various substrates such as monocrystalline Si-wafers, single crystals of spinel-structured  $\text{MgAl}_2\text{O}_4$ , glass- and plastic plates. As followed from the preliminary XRD measurements based on a microfocus source delivering  $\text{MoK}\alpha$  radiation ( $\mu\text{S}$  high Brilliance-Incoatec Microfocus Source Mo ELM33, Incoatec) and an imaging plate detector (MAR345, marXperts), crystalline products were obtained on the first two substrate types while amorphous products were found on the latter two substrate types. The spatially ( $\sim 200 \mu\text{m}$ ) resolved XRD examination, performed in LSPM, showed that the phase composition of the crystalline films depends on their thickness. Those of  $\sim 160 \text{ nm}$  in thickness contained  $\gamma$ - $\text{Sn}_3\text{N}_4$  and a presently unknown  $\text{Sn}_x\text{N}_y$  phase (patterns A and B in Figure 1). Also, the films deposited on monocrystalline  $\text{MgAl}_2\text{O}_4$  exhibited a better crystallinity when compared with those on the monocrystalline Si-wafers. Thick films of  $\sim 1.3 \mu\text{m}$  contained the unknown  $\text{Sn}_x\text{N}_y$  only (patterns C and D in Figure 1), independent of the substrate.



**Figure 1:** XRD patterns of thin (A, B) and thick (C, D) crystalline films. Vertical ticks indicate positions of the  $\gamma$ - $\text{Sn}_3\text{N}_4$  peaks. Stars indicate peaks of an unknown  $\text{Sn}_x\text{N}_y$  phase while a square the (111) peak of  $\text{MgAl}_2\text{O}_4$ , the substrate material. The insert shows the 2D-XRD pattern of the thin film deposited on a monocrystalline Si-wafer.

## Acknowledgements

This work was partially supported by the “PHC PARROT” programme (project number: 48994YJ), funded by the French Ministry for Europe and Foreign Affairs, the French Ministry for Higher Education and Research and the Estonian Research Council. The financial support from the Estonian Center of Excellence (TK210) by the Estonian Ministry of Education and Research is gratefully acknowledged.

## References

<sup>1</sup>Zerr A., Miehle G. *Phil. Trans. R. Soc. A* **381**, 20220330 (2023) doi: 10.1098/rsta.2022.0330