



Sonohydrothermal synthesis of zeolite A and its phase transformation to sodalite

William'S Nzodom Djozing, Sergey I. Nikitenko, Sabine Valange, Tony Chave

► To cite this version:

William'S Nzodom Djozing, Sergey I. Nikitenko, Sabine Valange, Tony Chave. Sonohydrothermal synthesis of zeolite A and its phase transformation to sodalite. ESS18 - European Society of Sonochemistry Sonochemistry, May 2024, Louvain, Belgium. hal-04768695

HAL Id: hal-04768695

<https://hal.science/hal-04768695v1>

Submitted on 6 Nov 2024

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.



Sonohydrothermal synthesis of zeolite A and its phase transformation to sodalite

William's Nzodom¹, Tony Chave¹,
Sabine Valange², Sergey I. Nikitenko¹

¹*Marcoule Institute in Separation Chemistry (ICSM), CEA, CNRS, ENSCM,
Marcoule Site, Bagnols-sur-Cèze, France*

²*University of Poitiers, IC2MP, CNRS, ENSI Poitiers, Poitiers, France*



UNIVERSITÉ DE
MONTPELLIER




IC2MP

Institut de Chimie des Milieux et Matériaux de Poitiers


Context



Zeolites are crystalline aluminosilicates (and related compositions)
with framework structures containing well-defined **micropores**






Conventional zeolite synthesis



- Mixing of the raw materials to give a precursor (gel) mixture
- **Hydrothermal treatment** at elevated temperature for different times (**hours to days**)

Zeolite synthesis

The crystallization of zeolite proceeds via two steps



Hydrothermal synthesis (HT)



Time & Energy consuming process

(because of the required restructuring)

New alternative synthesis route




Simultaneous coupling of HT conditions with power ultrasound


⇒ **Sonohydrothermal (SHT) synthesis**

Structure of zeolite A


The structure of zeolite A consists of a cubic array of cages forming a 3D network



Zeolite A
structure





Sodalite
structure



Cubic zeolite A crystal

conversion
→



Dissolution / Precipitation

Metastable phase

Stable phase

Hydrothermal (silent conditions) versus Sonohydrothermal (SHT) synthesis of zeolite A



SHT



Gel preparation

SiO_2 : 1,6g }
 NaOH : 2,1g } 21 mL H_2O

NaAlO_2 : 4,7g 27mL H_2O

- ♦ Mechanical stirring (**MS**)
30 min

or


- ♦ 20 kHz **US**, 70% amplitude,
30 min




HT (silent conditions)

Parr reactor

100 °C to 150 °C, 25 min to 48 h



SHT vs. HT: influence on the crystallization of zeolite A




Conversion of the amorphous gel to zeolite A in the SHT reactor is 9.6 times faster than in hydrothermal conditions

Effect on crystal size - Hydrothermal synthesis




Crystal size calculated using ImageJ software



Method used for the hydrogel preparation

US: ultrasonic precipitation



MS: mechanical stirring


More homogeneous, centered particle size distribution for the solid based on ultrasonic precipitation prior to the heating treatment (**US-HT-4h-100**)

Effect on crystal size - SHT synthesis




Crystal size calculated using ImageJ software


Method used for the hydrogel preparation



US: ultrasonic precipitation
MS: mechanical stirring




US-SHT-100 °C-1h



MS-SHT-100 °C-1h


Smaller crystals size for the specimen based on ultrasonic precipitation prior to the SHT treatment

Zeolite A crystallite size evolution



Sonofragmentation

Gel mixture (precursor)




SHT conditions at 20 kHz


⇒ shockwave effects

- Gel fragmentation
- More nucleation seeds
- Enhanced mass transfer
- Smaller zeolite crystals


Cavitation bubble sample solvent




Cavitation bubble formation



Enlargement of cavitation bubbles




Collapse of cavitation bubbles




High energy release (up to 5000 K and 1000 atm)

Release of content into the solvent






High shear force (breakdown of sample particle and increased mass transfer)

SHT vs. HT: influence on **sodalite** phase transformation



The conversion rate of zeolite A to sodalite increases by a factor of more than 96 compared with hydrothermal synthesis


SEM images



Conclusion

Fully crystalline zeolite A synthesized under SHT conditions in just 25 min
(9.6 times faster than under HT) \Rightarrow improved crystallization rate

Smaller zeolite crystals with more homogeneous particle size distribution



Drastic kinetic increase in the transformation of zeolite A into the more stable sodalite zeolite (96-fold)

The combined *in situ* action of 20 kHz ultrasound and hydrothermal conditions is a sound alternative for zeolite synthesis

Acknowledgement

Funding

Ecochem
PEPR




Supervisors

- Sergey I. Nikitenko
- Tony Chave
- Sabine Valange

SEM images

Joseph Lautru




Matthieu
Simon
Rachel
Rita, Julien

Conclusion

Fully crystalline zeolite A synthesized under SHT conditions in just 25 min
(9.6 times faster than under HT) \Rightarrow improved crystallization rate


Smaller zeolite crystals with more homogeneous particle size distribution





Drastic kinetic increase in the transformation of zeolite A into the more stable sodalite zeolite (96-fold)

The combined *in situ* action of 20 kHz ultrasound and hydrothermal conditions is a sound alternative for zeolite synthesis

Classical crystallization of zeolites



Effect on particle size




The abundance of sodalite makes it difficult to determine size distribution

Absorbed acoustic power influence

SHT 100 °C_1H

Variation réacteur filling rate



Decrease in the conversion rate of amorphous gel to LTA and of LTA to sodalite when absorbed acoustic power decrease