



# Phonon Properties of Multi-layered Graphene from Molecular Dynamics Simulations

Markos Poulos<sup>1</sup>, Konstantinos Papagelis<sup>2,3</sup>, Emmanuel N. Koukaras<sup>3,4</sup>, George Kalosakas<sup>5</sup>, Giorgia Fugallo<sup>6</sup> and Konstantinos Termentzidis<sup>7</sup>


<sup>1</sup>INSA Lyon, CNRS, CETHIL UMR5008, Villeurbanne, France, <sup>2</sup>AUTH, School of Physics, Thessaloniki, Greece, <sup>3</sup>FORTH/ICE-HT, Patras, Greece, <sup>4</sup>AUTH, School of Chemistry, Thessaloniki, Greece, <sup>5</sup>University of Patras, Department of Materials Science, Patras, Greece, <sup>6</sup>CNRS, Université de Nantes, LTEN, Nantes, France, <sup>7</sup>CNRS, INSA Lyon, CETHIL UMR5008, Villeurbanne, France

# Objective of this work

- **Phonon properties** of single- and multi-layered graphene: dispersion curves, pDOS and dependence of  $\omega(T)$  and  $\tau(T)$  of  $\Gamma$ -point phonons
- Influence of the **number of layers N**
- Influence of the **interlayer interaction modelling/strength** on the phonon properties

# Interlayer interaction in multilayered graphene

## Classical interatomic potentials for Molecular Dynamics




- Intra-layer: sp<sup>2</sup> covalent C-C bonds (Tersoff)
- Inter-layer: Van der Waals interaction (non-polar materials)



### $\pi$ -orbital overlap (Pauli)


- Short-range
- Repulsive
- Anisotropic
- Non-local + many-body
- **Responsible for rugosity!**

Lennard-Jones (LJ) potential (2body+radial)  
“too smooth” for short-range part  
→ complex, many-body potential:  
**Kolmogorov-Crespi (KC)**




### Dispersion (London)

- Long-range
- Attractive
- Two-body  $\sim \left( -\frac{1}{r^6} \right)$



local normal




transverse distance

# $\Gamma$ -point phonons in Multilayered graphene


From 1L to Graphite

## Single-layer

### Optical Modes




G (In-Plane)




ZO (out-of-plane)

### Acoustical Modes



## N-layers


### N-Davydov multiplets



G in-phase

G out-of-phase

### (N-1) Interlayer modes



(N-1) Shear Modes (C)


(N-1) Layer Breathing Modes (LBM)

# $\Gamma$ -point phonons in Multilayered graphene

# Choosing the mode representatives


## Inter-layer

## **Shear Mode**



Tan et al. *Nat. Mat.* 11, 3245 (2012)


## Breathing Mode



*Lui et al., Nano Lett. 14, 4615 (2014)*

## Intra-layer

# Optical Modes



## G in-phase

## ZO in-phase

# **Always Raman active<sup>1</sup>**

(for comparison with experiment)

# The kVACS method

k-VACS: k-space Velocity Autocorrelation Sequence  $Z_x^p(\mathbf{k}, \omega)$

$$Z_x^p(\mathbf{k}, \omega) = \int d\tau e^{i\omega\tau} \langle v_x^p(\mathbf{k}, \tau) v_x^{p*}(\mathbf{k}, 0) \rangle$$

- $\langle \dots \rangle$  denotes time-average
- $v_x^p(\mathbf{k}, t) = \sum_j v_x^p(l, t) e^{-i\mathbf{k}\mathbf{R}^p(l)}$
- $\mathbf{R}^p(l)$ : equilibrium position of atom p in unit cell l
- l: unit cell, i: time, p: atom species, x: cartesian coordinate, \* : complex conjugate

$$\left. Z_{total}(\mathbf{k}, \omega) = \sum_x \sum_p m_p Z_x^p(\mathbf{k}, \omega) \right\}$$

➤ Wiener-Khintchin Theorem (ergodic processes):  $Z_x^p(\mathbf{k}, \omega) \propto \Phi_x^p(\mathbf{k}, \omega)$  (Power Spectral Density )

$$\Phi_x^p(\mathbf{k}, \omega) = \frac{1}{\tau} \left| \sum_l \sum_i v_x^p(j, t) e^{-i[\mathbf{k}\mathbf{R}^p(l) - \omega t_i]} \right|^2$$

$\tau$ : total simulation time

# The kVACS method

- $Z(\mathbf{k}, \omega)$  is a superposition of Lorentzian functions, centered at the phonon eigenfrequencies and **FWHM** equal to double the phonon decay rates<sup>1</sup>


$$Z(\mathbf{k}, \omega) = \sum_j C(\mathbf{k}, j) \frac{\Gamma^2(\mathbf{k}, j)}{[\omega - \omega_R(\mathbf{k}, j)]^2 + \Gamma^2(\mathbf{k}, j)}$$

- The decay rates obtained are only due to ph-ph interactions ( $\Gamma_{ph-ph}$ )
- Applicable to all kinds of systems (non-periodic, amorphous, defects, dislocations, strain, etc.)
- **Inherently includes all orders of anharmonicity + thermal lattice expansion!**

<sup>1</sup>Poulos et al (2024) *Manuscript submitted to Physical Review B*

# The kVACS method



## Example kVACS spectrum



Polarization of  $\Phi(\mathbf{k}, \omega)$  gives the polarization of the phonon peaks!

# Dispersion Curves and density of states

## Bulk Graphite @ T = 300K



- Excellent agreement for acoustic branches
- **Z-phonons have larger  $\tau$**
- 40% overestimation of ZO
- 12% overestimation of LO/TO
- $\omega_{\text{LO}} < \omega_{\text{TO}}$
- Unable to capture Kohn anomaly at K and M (no  $e$ - $p$ - $h$ )
- Reflected in PDOS

# Dependence on # of Layers

## Inter-layer optical phonons

$$k_{Shear} = 0.96 \times 10^{19} \text{ Nm}^{-2}$$

$$k_{Shear}^{exp} = 1.26 \times 10^{19} \text{ Nm}^{-2}$$



Linear Chain Model:  
3(N-1) Optical Modes

$$\omega_{\nu}^{(i,N)} = \sqrt{\frac{2k_{\nu}}{\mu} \left\{ 1 - \cos \left( \frac{(i-1)\pi}{N} \right) \right\}}$$



(N-1) Longitudinal (LBM)

(N-1) 2bly degenerate Transverse (Shear)




$$k_{LBM} = 7.97 \times 10^{19} \text{ Nm}^{-2}$$

$$k_{LBM}^{exp} = 8.84 \times 10^{19} \text{ Nm}^{-2}$$



# Dependence of energies on temperature


Inter-layer



# Dependence of energies on temperature

↑ N ( $\sim 1\text{-}5 \text{ cm}^{-1}$ )

Practically independent of N



# Dependence of energies on temperature


Temperature slope  $x(T)$

# of Layers	Shear	Inter-layer	Intra-layer	G
		LBM ( $\times 10^{-3} \text{ cm}^{-1} \text{K}^{-1}$ )	ZO	
1	—	—	-36	-51
2	-6.2	-9.7	-35	-47
3	-5.9	-6.3	-34	-48
5	-5.7	-3.6	-35	-49
BG	-4.4	-5.6	-35	-50
Exper.	—	—	—	-21


- One order of magnitude lower
- # of layers affects slope of interlayer, but not for intra-layer

# Dependence of lifetimes on temperature

Inter-layer




Intra-layer



# Dependence of lifetimes on temperature

Single-layer graphene,  $E_{2g}$  phonon (G-mode)





$$\gamma_G = \gamma_G^{ph-ph} + \gamma_G^{el-ph}$$

- $\gamma^{el-ph}$  dominant in graphene
- **Conventional Raman captures both mechanisms!**
- Only Time-Resolved Raman captures purely  $\gamma^{ph-ph}$  (challenging experiments)
- **No experimental data on multi-layered!**

# Dependence of energies on temperature


Different interlayer potential (Lennard Jones)



# Dependence of lifetimes on temperature


Different interlayer potential (Lennard Jones)

## Inter-layer




↓ LJ

## Intra-layer



# Dependence of lifetimes on temperature

Different interlayer potential (Lennard Jones)




$$\tau^G_{\text{graphite}} > \tau^G_{\text{1L}}$$

# Effect of Interlayer Coupling Strength

Effect of interlayer coupling strength (Lennard-Jones)

$$V(x) = \chi \cdot 4\epsilon \left( \frac{\sigma}{x^6} - \frac{\sigma}{x^{12}} \right)$$



- $T^{ph-ph}$  increases with increasing the coupling strength
- For  $\chi \rightarrow 0$  it converges to the 1L value
  - $T^{BG} = 3.5 \text{ ps}$
  - $T^{1L} = 1.9 \text{ ps}$
- For  $\chi \geq 2$  it reaches a plateau (strong coupling limit)


# Conclusions

- T-dependence of interlayer C and LBM, as well as intralayer ZO and  $G$  phonons for multi-layered graphene by classical MD
- Phonon lifetimes: Quantum-mechanical quantities calculated with classical physics!  
(Important parameters for transport phenomena)
- Inter- and intra-layer phonons have different behaviour: inter → strong N-dependence, while intra → N-independent
- Kolmogorov-Crespi potential superior in describing interlayer properties
- The dependence of  $\tau_G$  on #N is independent of the choice of the interlayer interaction:  $T_{\text{graphene}} < T_{\text{graphite}}$ !
- Strengthening the interlayer interaction increases  $\tau$ !
- Experimental confirmation is challenging → we invite the experimental community to be involved!


**Thank you!**

# Molecular Dynamics Modelling

- System Size:  $10 \times 10 \text{ nm}$  ( $40 \times 40$  unit cells)
- Brillouin Zone Path:  $\Gamma \rightarrow K \rightarrow M \rightarrow \Gamma$
- Interatomic Potentials: **Tersoff-2010** for intra-layer, **Kolmogorov-Crespi (KC)** for inter-layer interactions
- Temperature: from 80 K to 1000 K
- Timestep: **0.5 fs**, Total Simulation Time: **328 ps**
- “Thermal averaging” of  $\Phi(\mathbf{k}, \omega)$  over 10 realizations at each T




- $\Gamma \rightarrow K$ : Zig-zag
- $K \rightarrow M$ : Armchair
- $\Gamma \rightarrow M$ : C-C Bond




# Anharmonicity: ph-ph interactions

$$U(\bar{\mathbf{R}}) = U_0(\mathbf{R}_{\text{equil}}) + \frac{1}{2!} \sum_{i,j} \frac{\partial^2 U}{\partial \mathbf{u}_i \partial \mathbf{u}_j} \mathbf{u}_i \mathbf{u}_j + \frac{1}{3!} \sum_{i,j,k} \frac{\partial^3 U}{\partial \mathbf{u}_i \partial \mathbf{u}_j \partial \mathbf{u}_k} \mathbf{u}_i \mathbf{u}_j \mathbf{u}_k + \dots$$


Harmonic Approximation



Phonon Interactions: 3<sup>rd</sup>, 4<sup>th</sup> and higher order anharmonic terms



Anharmonic Decay



Perturbation theory: Phonon quasi-particle “dressed” in a virtual phonon cloud

$$\omega(\mathbf{q}, j) \rightarrow \omega(\mathbf{q}, j) + \Delta(\mathbf{q}, j) + i\Gamma(\mathbf{q}, j)$$


Frequency Shift



Decay Rate



# Interlayer Phonon Eigenvectors



# Phonon Linewidth Fitting (1L vs 2L)

