



HAL
open science

Cu Ferros spinel Thin Films for Sub-ppm NO₂ Sensing

Sabah Zahaf, Lionel Presmanes, Antoine Barnabé, Thierry Camps, Philippe Menini

► **To cite this version:**

Sabah Zahaf, Lionel Presmanes, Antoine Barnabé, Thierry Camps, Philippe Menini. Cu Ferros spinel Thin Films for Sub-ppm NO₂ Sensing. Proceedings, 2024, 97 (1), pp.168. <10.3390/proceedings2024097168>. <hal-04796278>

HAL Id: hal-04796278

<https://hal.science/hal-04796278v1>

Submitted on 21 Nov 2024

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire HAL, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.



Distributed under a Creative Commons CC BY 4.0 - Attribution - International License

Abstract

Cu Ferros spinel Thin Films for Sub-ppm NO₂ Sensing[†]

Sabah Zahaf^{1,2}, Lionel Presmanes^{1,*} , Antoine Barnabé¹, Thierry Camps² and Philippe Menini² 

- ¹ CIRIMAT, Université Toulouse 3 Paul Sabatier, Toulouse INP, Université de Toulouse, CNRS, 118 Route de Narbonne, 31062 Toulouse, France; sabah.zahaf@laas.fr (S.Z.); antoine.barnabe@univ-tlse3.fr (A.B.)
- ² Laboratoire d'Analyse et d'Architecture des Systèmes (LAAS), Université de Toulouse, CNRS, UPS, 7 Avenue du Colonel Roche, 31031 Toulouse, France; thierry.camps@laas.fr (T.C.); philippe.menini@laas.fr (P.M.)
- * Correspondence: lionel.presmanes@univ-tlse3.fr
- [†] Presented at the XXXV EUROSENSORS Conference, Lecce, Italy, 10–13 September 2023.

Abstract: The paper reports the synthesis and characterization of a copper ferros spinel thin layer. The thin layer (25 nm) was synthesized by RF sputtering of a pure CuFe₂O₄ target. The material structure and microstructure were characterized using X-ray diffraction and transmission electron microscopy. Simplified test substrates were microfabricated with interdigitated Pt electrodes to investigate electrical properties in a controlled atmosphere. The sensitive layer was stabilized by annealing at 550 °C under air. NO₂ responses at a low concentration (<1 ppm) and 50% relative humidity were measured between 100 and 500 °C. The optimal response was obtained at 250 °C.

Keywords: ferros spinel; semiconducting oxide; thin layer; RF sputtering; gas sensors; NO₂ sensing

1. Introduction

Nitrogen dioxide (NO₂) is a toxic gas produced by industrial and domestic use, in particular by internal combustion engines used in vehicles. NO₂ is dangerous for human health, with a threshold limit value (TLV) of 0.5 ppm. Many sensing technologies are being developed; among them, metal oxide semiconductor gas sensors are the most widely used for NO₂ detection [1]. Copper ferros spinel is an interesting candidate thanks to its electrical and reactional properties. Indeed, CuFe₂O₄ is used as a catalyst in particular for the removal of NO_x emitted from diesel exhaust [2].

2. Materials and Methods

Twenty-five nm thin layers were elaborated by RF sputtering at 2 Pa under argon on various substrates and annealed at 550 °C under air. The structural properties were studied by X-ray diffraction (XRD) in grazing incidence ($\alpha = 1^\circ$), transmission electron microscopy (TEM) and Raman spectroscopy. Microstructure analysis was performed using scanning electron microscopy (SEM). The gas-sensing performance was studied using simplified test substrates with Pt interdigitated electrodes (Figure 1) to measure the resistance variation under clean and polluted air. The test substrate was introduced on a heating chuck in a small chamber in which the atmosphere was well controlled.



Figure 1. Electrical microdevice design used for sensing performance evaluation with 16 Pt electrodes of 100 μm width. The distance between each electrode is 50 μm .

3. Discussion

XRD analysis on a thin layer deposited on a substrate without electrodes (Figure 2) reveals a quadratic CuFe₂O₄ pattern (JCPDS card 034-0425) at room temperature. No additional phases were detected. Transmission Electronic Microscopy confirms the XRD results.



Citation: Zahaf, S.; Presmanes, L.; Barnabé, A.; Camps, T.; Menini, P. Cu Ferros spinel Thin Films for Sub-ppm NO₂ Sensing. *Proceedings* **2024**, *97*, 168. <https://doi.org/10.3390/proceedings2024097168>

Academic Editors: Pietro Siciliano and Luca Francioso

Published: 9 April 2024



Copyright: © 2024 by the authors. Licensee MDPI, Basel, Switzerland. This article is an open access article distributed under the terms and conditions of the Creative Commons Attribution (CC BY) license (<https://creativecommons.org/licenses/by/4.0/>).




Figure 2. XRD pattern of copper ferros spinel thin film.

Structural properties were also investigated under temperature since the sensing performances are measured at high temperatures. The literature shows structural distortions when CuFe_2O_4 is heated, due to a cooperative Jahn–Teller effect [3]. High temperature XRD analysis was performed and revealed that elaborated ferros spinel thin film turns into a cubic structure above 350 °C.

The resistance behavior under air and NO_2 at 250 ppb was investigated at different temperatures in isothermal mode. As the NO_2 is an oxidizing gas, the resistance increased, meaning that the material is an n-type semiconductor. The $R_{\text{NO}_2}/R_{\text{air}}$ ratio was calculated at each temperature and is represented in Figure 3. The best response was obtained at 250 °C and decreased above that temperature (Figure 3). Furthermore, above 450 °C the response was reversed; the copper ferros spinel film behaved like a p-type semiconductor. Gas-sensing performances seem to depend on structural properties, since the structural transition starts at 350 °C.




Figure 3. NO_2 -sensing performance.

Author Contributions: Experimentations and abstract redaction by S.Z.; work supervision by L.P. and P.M.; material characterization support by A.B. and electrical characterization support by T.C. All authors have read and agreed to the published version of the manuscript.

Funding: This research received cofunding from ELLONA. This work was also supported by the LAAS-CNRS micro and nanotechnologies platform, a member of the french Renatech network.

Institutional Review Board Statement: Not applicable.

Informed Consent Statement: Not applicable.

Data Availability Statement: Data are available in this manuscript.

Conflicts of Interest: The authors declare no conflicts of interest.

References

1. Wetchakun, K.; Samerjai, T.; Tamaekong, N.; Liewhiran, C.; Siriwong, C.; Kruefu, V.; Wisitsoraat, A.; Tuantranont, A.; Phanichphant, S. Semiconducting metal oxides as sensors for environmentally hazardous gases. *Sens. Actuators B Chem.* **2011**, *160*, 580–591. [[CrossRef](#)]
2. Shangguan, W.; Teraoka, Y.; Kagawa, S. Promotion effect of potassium on the catalytic property of CuFe_2O_4 for the simultaneous removal of NO_x and diesel soot particulate. *Appl. Catal. B Environ.* **1998**, *16*, 149–154. [[CrossRef](#)]
3. Balagurov, A.; Bobrikov, I.; Maschenko, M.; Sangaa, D.; Simkin, V. Structural phase transition in CuFe_2O_4 spinel. *Crystallogr. Rep.* **2013**, *58*, 710–717. [[CrossRef](#)]

Disclaimer/Publisher's Note: The statements, opinions and data contained in all publications are solely those of the individual author(s) and contributor(s) and not of MDPI and/or the editor(s). MDPI and/or the editor(s) disclaim responsibility for any injury to people or property resulting from any ideas, methods, instructions or products referred to in the content.