

# Molecular modelling and molecular dynamics studies of HCH and chlordecone adsorption on activated carbon surface

A. Duro, Francesca Goudou-Rosnel, K. Melchor-Rodríguez, C. Carmenate-Rodríguez, A. Ferino-Pérez, J. J. Gamboa-Carballo, B. Minofar, S. Gaspard, U. J. Jáuregui-Haza

## ▶ To cite this version:

A. Duro, Francesca Goudou-Rosnel, K. Melchor-Rodríguez, C. Carmenate-Rodríguez, A. Ferino-Pérez, et al.. Molecular modelling and molecular dynamics studies of HCH and chlordecone adsorption on activated carbon surface. The World Conference on Carbon 2023: Renewing the World Through Carbon, CARBON, Jul 2023, Cancun, Mexico. pp.243-248. hal-04817521

## HAL Id: hal-04817521 https://hal.science/hal-04817521v1

Submitted on 17 Dec 2024

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers. L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

### Molecular modelling and molecular dynamics studies of HCH and chlordecone adsorption on activated carbon surface

A. Duro<sup>a</sup>, <u>F. Goudou<sup>a</sup></u>, K. Melchor-Rodríguez<sup>b</sup>, C. Carmenate-Rodríguez<sup>b</sup>, A. Ferino-Pérez<sup>b</sup>, J. J. Gamboa-Carballo<sup>b</sup>, B. Minofar<sup>c</sup>, S. Gaspard<sup>a</sup>, U. J. Jáuregui-Haza<sup>b,d</sup>.

<sup>a</sup>Laboratoire COVACHIM-M2E, EA 3592, Université des Antilles, 97157 Pointe à Pitre Cedex, Guadeloupe. <sup>b</sup>INSTEC, University of Havana, Avenida Salvador Allende, 1110, Quinta de los Molinos, Plaza de la Revolución, A.P. 6163, La Habana, Cuba.

<sup>c</sup> Department of Chemistry, Faculty of Science, University of South Bohemia, Branišovská 1760, 37005 České Budějovice, Czech Republic

<sup>d</sup>Instituto Tecnológico de Santo Domingo, Ave. de los Próceres, Santo Domingo, República Dominicana

e-mail: francesca.goudou@univ-antilles.fr

**Keywords:** chlordecone; beta-hexachlorocyclohexane; water treatment; activated carbon; molecular modeling, molecular dynamics

### **Extended abstract:**

In the 1950s, banana fields in the French West Indies were infested by a parasite called Cosmopolitan Sordidus. To face this invasion, farmers had to use organochlorine phytosanitary products. One of them,  $\gamma$ -hexachlorocyclohexane ( $\gamma$ -HCH) (CAS: 58-89-9), usually known under the name of lindane have been massively used to treat banana fields but the parasites developed resistance. Chlordecone (CLD) (CAS: 143-50-0) has been the most common substitute. In 1975, the Life Science Products Company was manufacturing Kepone® (commercialized name of CLD) at Hopewell USA, when many of its workers have been sick[1]. Blood tests have showed a high presence of this pesticide indicating the neurotoxicity of chlordecone [2]. After this chemical disaster, CLD was banned from the United States 2 years later. The use of this pesticide was only banned in 1991 in the French West Indies. For about twenty years, the ground has been soiled with this pesticide causing pollution of various ecosystems such as agricultural land [3], water sources[4], products from agriculture [5], local fishing[6]. Consequently, the local populations have been highly exposed [3-6]. On 22 May 2001, the Stockholm Convention certified that CLD and hexachlorocyclohexane (HCH, the  $\beta$  form being the most recalcitrant isomer) are persistent organic pollutants (POPs). These two organochlorine molecules are toxic to the human organism.  $\beta$ -hexachlorocyclohexane ( $\beta$ -HCH) is an endocrine disruptor [7]. CLD is responsible of the high rate of prostate cancer in the French West Indies [8,9]. One of the most used way for removing these pollutants from water is the utilization of activated carbon (AC). AC wearing basic surface groups (SGs) have been obtained by steam activation whereas AC with acidic (SGs) have been elaborated when phosphoric acid H<sub>3</sub>PO<sub>4</sub> has been used as activating agent [12]. The porous structures of AC allows to trap on its surface molecules via a phenomenon called adsorption [13]. It has been shown an enhancing of this phenomenon specially when CLD was in presence of AC with carboxylic acid SGs [14]. From that results, theorical studies have been led by our team to study the influence of acidic and nitrogen containing surface groups of activated carbon model on the adsorption of CLD and ( $\beta$ -HCH), considering pH and hydration effect. These interactions using acidic SG at neutral pH have revealed a chemisorption whereas nitrogen basic SGs have shown a physisorption. In fact, the interactions were governed by dispersive interactions of chlorine atoms of the pollutants with the graphitic surface and by electrostatic interactions with COO<sup>-</sup> and O<sup>-</sup> acidic groups and water molecules. For nitrogenous basic SGs, the results showed a greater association of both pesticides with the primary amine in comparison with the pyridine, secondary and tertiary amine in the absence and presence of water molecules, and this behavior increase at acidic pH conditions where the amines and pyridine are protonated [15].

Here, a theoretical study of the interactions of these pesticides with oxygenated SG of AC is reported. A molecule of coronene with a functional group whether it be pyrone, chromene or ketone in the edge, was used as a simplified model of AC [15-21] (figure 1).





Figure 1. Structures of basic oxygen surface groups on coronene molecule as activated carbon model (grey: carbon, white: hydrogen, red: oxygen)


Multiple Minima Hypersurface methodology was employed to study the interactions of CLD and  $\beta$ -HCH with SGs on AC using PM7 semiempirical Hamiltonian. The principal aim of this methodology is to calculate the variation of the association energy  $\Delta E_{association}$  which describe the stability of adsorption of POPs by AC. A further re-optimization of obtained structures was done for pesticide-AC complexes by means of Density Functional Theory. To choose these SGs, the lowest value of association energy was the criteria (MMH-PM7 and DFT results). The Quantum Theory of Atoms in Molecules was used to characterize the interaction types using the Nakanishi criteria. No interactions have been shown at acidic pH for both pollutants whereas dispersive interactions have been found at neutral and basic pH explaining a physisorption process (**figure 2**).



**Figure 2.** Interactions and bond paths obtained by QTAIM for distinctive minima structures of the systems Chromene/CLD/2 $H_2$ O and Chromene/ $\beta$  –HCH/3 $H_2$ O

The two best AC surface groups for adsorption (AC-chromene and AC-pyrone) have been selected and have been performed with the molecular dynamics simulation (MDs) and the same findings have been illustrated (**figure 3**).

This study has shown the possibility of the adsorption of  $\beta$ -HCH and chlordecone by basic oxygen activated at neutral and basic pH means by quantum mechanics calculations and molecular dynamics simulation. In fact, the adsorption of  $\beta$ -HCH is better than CLD with basic activated carbon and joined the previous study about nitrogen basic SG by Melchor *and al.*[19]. MDs confirm the better adsorption of  $\beta$ -HCH on graphitic surface basic oxygen-containing than CLD. Furthermore, MDs was brought information about competition adsorption with the two organochlorine pesticides and has shown repulsive interaction. At the end, the adsorption process of CLD or  $\beta$ -HCH on an AC is enhanced with acidic SG as shown in our previous studies (chemisorption) rather than basic SG.



**Figure 3.** Distance between AC and pesticide molecules as a function of time: (**a**) radial distribution between AC-Chromene with  $\beta$ -HCH and CLD during competition adsorption; (**b**) Distance between AC-Chromene with  $\beta$ -HCH and CLD during competitive adsorption.

#### References

[1] R.E. Vanhuss Jr, Kepone a crisis situation, Quarterly Bulletin-Association of Food and Drug Officials. (1978).

[2] U.E.N.C. for E. Assessment, Distribution and excretion of kepone (KP) in humans, (2009). https://hero.epa.gov/hero/index.cfm/reference/details/reference\_id/2917173 (accessed June 7, 2022).

[3] Y.-M. Cabidoche, R. Achard, P. Cattan, C. Clermont-Dauphin, F. Massat, J. Sansoulet, Long-term pollution by chlordecone of tropical volcanic soils in the French West Indies: A simple leaching model accounts for current residue, Environmental Pollution. 157 (2009) 1697–1705. <u>https://doi.org/10.1016/j.envpol.2008.12.015</u>

[4] J.-M. M, Pollution à la chlordécone aux Antilles, Revue Francophone des Laboratoires. 2016 (2016) 89. https://doi.org/10.1016/S1773-035X(16)30097-1.

[5] D. Guadeloupe, Cartographie - analyses des sols, (2021). https://daaf.guadeloupe.agriculture.gouv.fr/Cartographie-analyses-des-sols (accessed July 7, 2021).

[6] D.R. Charlotte, B.-N. Yolande, S. Cordonnier, B. Claude, The invasive lionfish, Pterois volitans, used as a sentinel species to assess the organochlorine pollution by chlordecone in Guadeloupe (Lesser Antilles), Marine Pollution Bulletin. 107 (2016) 102–106. <u>https://doi.org/10.1016/j.marpolbul.2016.04.012</u>.

[7] K.L. Willett, E.M. Ulrich, R.A. Hites, Differential Toxicity and Environmental Fates of Hexachlorocyclohexane Isomers, Environ. Sci. Technol. 32 (1998) 2197–2207. <u>https://doi.org/10.1021/es9708530</u>

[8] L. Multigner, Chlordécone et cancer de la prostate aux Antilles françaises : du gène à l'environnement, Annales d'Endocrinologie. 74 (2013) 244. <u>https://doi.org/10.1016/j.ando.2013.07.036</u>.

[9] L. Multigner, P. Kadhel, F. Rouget, P. Blanchet, S. Cordier, Chlordecone exposure and adverse effects in French West Indies populations, Environ Sci Pollut Res. 23 (2016) 3–8. <u>https://doi.org/10.1007/s11356-015-4621-5</u>.

[10] Chlordécone : les cancers de la prostate reconnus comme maladie professionnelle, Gouvernement.fr. (n.d.). https://www.gouvernement.fr/actualite/chlordecone-les-cancers-de-la-prostate-reconnus-comme-maladie-professionnelle (accessed March 14, 2022).

[11] L. Saunders, P. Kadhel, N. Costet, F. Rouget, C. Monfort, J.-P. Thomé, L. Guldner, S. Cordier, L. Multigner, Hypertensive disorders of pregnancy and gestational diabetes mellitus among French Caribbean women chronically exposed to chlordecone, Environment International. 68 (2014) 171–176. https://doi.org/10.1016/j.envint.2014.03.024.

[12] Durimel Axelle, Etude des voies de dépollution de milieux et matériaux contaminés par la chlordécone et l'hexachlorocyclohexane [Texte imprimé] / Axelle Durimel ; sous la direction de Sarra Gaspard, (2010).R.C.

[13] Bansal, M. Goyal, Activated Carbon Adsorption, CRC Press, Boca Raton, 2005. https://doi.org/10.1201/9781420028812.

[14] A. Durimel, S. Altenor, R. Miranda-Quintana, P. Couespel Du Mesnil, U. Jauregui-Haza, R. Gadiou, S. Gaspard, pH dependence of chlordecone adsorption on activated carbons and role of adsorbent physico-chemical properties, Chemical Engineering Journal. 229 (2013) 239–249. <u>https://doi.org/10.1016/j.cej.2013.03.036</u>.

[15] K. Melchor-Rodríguez, J.J. Gamboa-Carballo, A. Ferino-Pérez, N. Passé-Coutrin, S. Gaspard, U.J. Jáuregui-Haza, Theoretical study on the interactions between chlordecone hydrate and acidic surface groups of activated carbon under basic pH conditions, Journal of Molecular Graphics and Modelling. 81 (2018) 146–154. https://doi.org/10.1016/j.jmgm.2018.02.012.

[16] C. Enriquez-Victorero, D. Hernández-Valdés, A.L. Montero-Alejo, A. Durimel, S. Gaspard, U. Jáuregui-Haza, Theoretical study of  $\gamma$ -hexachlorocyclohexane and  $\beta$ -hexachlorocyclohexane isomers interaction with surface groups of activated carbon model, Journal of Molecular Graphics and Modelling. 51 (2014) 137–148. https://doi.org/10.1016/j.jmgm.2014.05.004.

[17] J.J. Gamboa-Carballo, K. Melchor-Rodríguez, D. Hernández-Valdés, C. Enriquez-Victorero, A.L. Montero-Alejo, S. Gaspard, U.J. Jáuregui-Haza, Theoretical study of chlordecone and surface groups interaction in an activated carbon model under acidic and neutral conditions, Journal of Molecular Graphics and Modelling. 65 (2016) 83–93. https://doi.org/10.1016/j.jmgm.2016.02.008.

[18] K. Melchor-Rodríguez, S. Gaspard, U. Jáuregui-Haza, CHLORDECONE ADSORPTION ON FUNCTIONALIZED ACTIVATED CARBONS: COMPUTATIONAL CHEMISTRY AS A TOOL FOR UNDERSTANDING THE ADSORPTION PROCESS, Quím. Nova. (2020). <u>https://doi.org/10.21577/0100-4042.20170666</u>.

[19] K. Melchor-Rodríguez, C. Carmenate-Rodríguez, A. Ferino-Pérez, S. Gaspard, U.J. Jáuregui-Haza, Role of Basic Surface Groups of Activated Carbon in Chlordecone and  $\beta$ -Hexachlorocyclohexane Adsorption: A Molecular Modelling Study, Molecules. 26 (2021) 6969. <u>https://doi.org/10.3390/molecules26226969</u>.

[20] H. Ruuska, T.A. Pakkanen, Ab Initio Study of Interlayer Interaction of Graphite: Benzene–Coronene and Coronene Dimer Two-layer Models, J. Phys. Chem. B. 105 (2001) 9541–9547. https://doi.org/10.1021/jp011512i .

[21] M. Bonfanti, R. Martinazzo, G.F. Tantardini, A. Ponti, Physisorption and Diffusion of Hydrogen Atoms on Graphite from Correlated Calculations on the H–Coronene Model System, J. Phys. Chem. C. 111 (2007) 5825–5829. <u>https://doi.org/10.1021/jp070616b</u>.