



HAL
open science

Eugenol's journey to high-performance and fire-retardant biobased thermosets

Pierre Dellière, Camille Bakkali-Hassani, Sylvain Caillol

► To cite this version:

Pierre Dellière, Camille Bakkali-Hassani, Sylvain Caillol. Eugenol's journey to high-performance and fire-retardant biobased thermosets. *Current opinion in green and sustainable chemistry*, 2025, 51, pp.100988. 10.1016/j.cogsc.2024.100988 . hal-04845347

HAL Id: hal-04845347

<https://hal.science/hal-04845347v1>

Submitted on 18 Dec 2024

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Eugenol's journey to high-performance and fire-retardant biobased thermosets

Eugenol, biobased polymers, fire-retardant, thermoset

Pierre Dellière ^{a*}, Camille Bakkali-Hassani ^{a*}, Sylvain Caillol ^{a*}

(a) *ICGM, Univ Montpellier, CNRS, ENSCM, Montpellier, France*

PD, ORCID ID: 0000-0001-7531-538X; CBH, ORCID ID: 0000-0003-3633-2675; SC, ORCID ID: 0000-0003-3106-5547

pierre.delliere@umontpellier.fr

camille.bakkali-hassani@umontpellier.fr

sylvain.caillol@enscm.fr


Introduction

Thermosets correspond to 10% of global polymer production 400 Mt/y. [1] Most of them present outstanding properties which are essential for designing high-performance composites (wind turbine blades, aeronautics, etc.). Among precursors, bisphenol A, bismaleimide (BMI) or phenol-formaldehyde are well suited to produce chemically crosslinked networks used as matrices for composites. Their rigid chemical structures, *i.e.* high aromatic content and/or fused cycles, results in materials with glass transition temperature (T_g) exceeding 100 °C. These precursors are petroleum-based and often pose risks to human health, leading to intensive research in the past decades for sustainable and safer alternatives. [2] However, common bio-based thermosets from vegetable oils [3] or cashew nut shell liquid derivatives [4] often lack the high T_g required for high-performance applications. Building blocks based on furanic (5-hydroxymethylfurfural, furfural) and aromatic (eugenol, vanillin) groups bear potential as precursors for high T_g polymers. [2, 5, 6]

Among natural compounds, the peculiar chemical structure of eugenol holds a strong potential to prepare suitable thermosets for high performance composite applications. Eugenol is a non-edible natural phenol, which can lead to monomers with relatively similar structures to many petroleum-derived monomers. Eugenol does not have the plasticizing aliphatic chain(s) of cardanol and vegetable oils but only a short allylic moiety directly grafted on the *para*-position of the phenolic ring. Thus, higher thermo-mechanical properties are achievable with eugenol while keeping potential chemical modification on the alkene function. [3, 4] Several reviews dealing with eugenol-based polymers appeared in the last years. The main focus was put on the possibilities of functionalization offered by eugenol to obtain high T_g thermoset for the manufacture composites, coatings or target fire-retardancy. [7, 8, 9, 10, 11, 12] This review aims at emphasizing the growing potential of eugenol for high-performance applications (construction, automotive, aeronautics, ...). Starting with a survey of the functionalization routes of eugenol (methoxy, phenol, allyl, aromatic) we will summarize the different pathways to prepare eugenol-based precursors with constrained structures (biphenyls, Alder-ene, benzoxazines). Finally, fire-retardant polymers achievable by the introduction of specific spacers between eugenol molecules are presented (silicones, phosphates, cyclophosphazenes).

Functionalization routes eugenol

Nowadays, 6 kt/y of oil are extracted from the clove tree world-wide. [13] Eugenol represents 70 to 90 w.% of clove-oil and can be recovered in good yields. Eugenol can also be synthesized from lignin derivatives, which opens the way to massive production. It is already used to synthesize part of the 50 kt/y of vanillin.[7, 8] The cosmetic and pharmaceutical industry are major consumers of eugenol for its intrinsic wide range of biological activities and antioxidant properties (among others). [7, 14, 15] An array of other applications is possible using eugenol's functionalization routes (methoxy, hydroxyl, aromatic, allyl, Scheme 1). [7, 9, 10, 11] Their chemistries can be exploited, alone or together, to graft chemical functions and introduce spacers. Another of the advantages of eugenol is its low oxygen concentration, which limits the reduction reactions which must often be carried out on natural derivatives.



Scheme 1. Eugenol's reactive sites

Transformation of the methoxy group has been limited but it can be converted to a hydroxyl function by either oxidative *O*-Demethylation or silylation followed by hydrolysis. [7, 16] This modification allows to introduce another hydroxyl, either for direct polymerization or for further functionalization *via* the phenol route.

The phenol route is of significant interest for the production of monomers. Phenolic hydroxyls can be (hydroxy)alkoxylated yielding more reactive aliphatic alcohols which can be employed for rigid poly(urethane) foams. [7, 17] Esterification with anhydrides or acyls is a way to graft functional groups or dimerise/trimerise eugenol with rigid or flexible spacers to tune the T_g of the resulting materials. [18] Phosphorylation with phosphorous oxychloride yields a eugenol trimer. The introduction of phosphorylated moieties is a strong asset when fire-retardant properties are targeted (*vide infra*). [12, 19,20]

O-Glycidylation can be employed to introduce an epoxy ring, a convenient function for the manufacture of thermosetting resins (about 8% of the thermosets are epoxies). [11, 21] *O*-Glycidylation involves epichlorohydrin. Although it can be bio-based, this compound is both carcinogenic and toxic, thus greener paths for *O*-Glycidylation are desirable. [22, 23] Hydroxyl


group can undergo Williamson etherification or Tsuji-Trost allylation to give allyl functions. [2, 7, 24] A major interest of allyl functions is their ability to undergo thiol-ene click reactions either in a thermally (composite matrices) or photo-initiated process (coatings, 3D printing). As one allyl group is already present on eugenol, the addition of another one is convenient to access pluri-functionality. [7, 25]

Thiol-ene click reaction is one of the most advantageous routes to functionalize allylic moieties. [26] It is suitable to introduce either flexible or rigid spacers between eugenol dimers. This leads to a broad range of achievable properties. Hydrosilylation is a valuable way to obtain silicones with thermal resistance and potential anti-bacterial properties. [27, 28, 29] Epoxy functions can be obtained using oxidants such as *m*-CPBA or ozone. [30] The enzyme-catalyzed epoxidation with hydrogen peroxide was never performed on eugenol. It would be worth investigating. [31] Phenol oxidative-coupling is a mean to reach dimers with biphenyl moieties, *i.e.*, higher T_g and better fire-resistance. [7, 24, 30, 32, 33] Benzoxazine derivatives can be obtained through Mannich-like reactions (*via* intramolecular cyclisation) . [7, 34, 35] All these examples are suited for thermally and/or mechanically demanding applications through the input of rigid and/or fire-resistant spacers.


High-performance thermosets from Eugenol

Eugenol's aromatic ring provides intrinsic rigidity to the resulting polymers. For instance, diglycidyl [8, 11, 12, 36] and triglycidyl eugenol [10, 11, 12] yield thermosets with T_g between 103 °C and 155 °C. A series of patents claimed the functionalization of eugenol with triglycidyl [37], dicarbonate [38] and acrylic [39] groups as well as eugenol-based amine curing agents. [40, 41] They were submitted in the last two years, showcasing the interest in eugenol. Authors limited their approach to mono-eugenol systems. The performance of eugenol-based polymers can be further improved through advanced chemical modification (fused cycles, dimerization).


Light can be shed on four eugenol-derived structures for high-performance thermosets (Scheme 2). Biphenyl structures from oxidative coupling were reported as poly(urethanes) hard segments [7], di and tetra allyl eugenol [7, 11] as well as di and tetra glycidyl eugenol. [11, 12, 30] Such systems without spacers allowed to reach T_g as high as 216 °C (tetraglycidyl eugenol).




Biphenyls



Benzoxazines



Esters



Alderene adducts

Scheme 2. Promising hard segments for Eugenol-based polymers


Esterification can be employed to dimerise eugenol with the acyl derivatives of furandicarboxylic acid [42, 43] isophthalic acid and benzene-1,3,5-tricarboxylic acid yielding respectively dimers and trimers. [18] Similarly to biseugenol systems, thermosets from esterified eugenol exhibit T_g between 153 and 208 °C.

Poly(benzoxazines) synthesized through cationic ring-opening polymerization of benzoxazines are a recent class of thermoset with attractive thermal and mechanical properties. [2, 5] The occupied *ortho*-position of eugenol is preventing the occurrence of chain-growth limiting the development of fully eugenol-based benzoxazines. Examples of copolymerization [7] using eugenol-based monomers and furfurylamine ($T_\alpha = 162$ °C) [34] or *n*-octadecanamine/furfurylamine [35] are promising as attested by similar patented systems involving eugenol-based benzoxazines. [44, 45]

Neda *et al.* suggested an approach where di and tetraallylbiseugenol react with bismaleimide to yield a thermoset with a $T_{\alpha} > 357$ °C and a $T_{5\%} > 475$ °C (inert atm). [24] In this line, Alder-ene chemistry, *i.e.* a ene-reaction and Diels-Alder reaction followed by rearomatization, leads to highly constrained structures composed of fused cycles. Alder-ene chemistry was employed with eugenol [46], eugenyl-phosphate [47,], eugenol/hydroxymetyeugenol [48], eugenol-silsesquioxane [49] and eugenol-siloxane-resveratrol. [50] These Alder-ene systems with their fused aromatic, imide and alkyl cycles allow T_g between 250 and 380 °C. Alder-ene systems are, to the best of our knowledge, the eugenol-based systems with the highest T_g that were reported so far. In the case of eugenol-phosphate, fire retardancy is achievable on top of its high T_g . [47] The following section aims to further highlight promising eugenol precursors bearing potential for materials with resistance to thermal and thermo-oxidative degradation.

Flame retardancy from eugenol-based compounds

The global flame retardant market size was valued at USD 8.63 billion in 2022 and is anticipated to grow at a compound annual growth rate (CAGR) of 7.1% from 2023 to 2030. [51] Forty percent of the market share of flame retardants (FRs) is held by halogenated compounds. [52] Despite being highly efficient FRs, they are also considered as both hazardous and toxic chemicals. [53] Greener alternatives include silicon and organophosphorus derivatives. [52, 53] Though chemical functionalization, eugenol can become an intrinsically fire-retardant thermoset precursor. Flourishing eugenol-based structures suited for these purposes are presented in Scheme 3.



Scheme 3. Promising Eugenol-based segments bearing fire/heat resistance.


Hydrosilylation was used to introduce silicon-based spacers between eugenyl moieties. Even at low concentrations ($\leq 3\%$), hydrosilylated eugenol enhanced the properties of waterborne poly(urethanes) [27]. When eugenol was employed in higher proportions in silicones, it improved their char yield and reduced their rate of thermal degradation. [28, 29] Systems comprising eugenol-silicon spacers [54], eugenol-polysiloxane-carbonate systems [55, 56], and eugenol grafted siloxane [57] have been patented since 2022, underscoring the growing interest in these innovative polymers. The downside of silicon spacers is their flexibility, when high T_g materials are targeted.

If both high T_g and fire-retardancy are desired, phosphorylated eugenol offers a promising alternative. Eugenol was successfully spaced with organophosphorus moieties to enhance the fire retardancy of epoxy [11, 12, 19, 20] and allyl-terminated monomers. [58] While their effectiveness is somewhat limited, nitrogen-based compounds remain as the safest fire-retardants. [52] Eugenol-based triazines were reported in poly(cyanurate) resins [59], as a side-reaction in phthalonitrile resins [60] and in epoxy-terminated triseugenol. [61]

The fire-retardancy of nitrogen compounds synergizes with phosphorylated ones by combining gas-phase and solid-phase actions. [52] Cyclophosphazenes contain both nitrogen and phosphorous. They are emerging as promising fire-retardant moieties. [53] Cyclophosphazene were reported as a spacer for eugenol with up to six left-over allyl functions. These allyl groups can either be used directly in thiol-ene polymerization, [62] self-polymerization [63], or undergo epoxidation [11, 12, 64] or involve series of reactions with the silyl derivative of 4-vinylbenzocyclobutene. [65] In all these cases, the authors praised the fire-retardancy or thermostability of cyclophosphazene-spaced eugenol. Incorporating fire-retardant spacers reduces the need for potentially leaking fire-retardant additives.

Overall, key structures with high potential can be isolated from the this minireview (Scheme 4). Eugenol compounds functionalized with epoxy or allyl end group offer an ease of manufacturing *via* epoxy-amine and thiol-ene chemistry, for example. In terms of polymer architectures, light can be shed on Alder-enes. Their constrained structures allow high T_g thermosets suitable for high-performance applications. Finally, the introduction of phosphorylated moieties is an advantageous way to increase the fire-resistance of eugenol-based thermosets.

Scheme 4. Overview of the most promising monomer's functional groups and polymer architectures derived from eugenol.



Conclusion

Eugenol, a non-edible natural phenol, is one of the most promising natural phenols whose commercial availability can rapidly increase by deconstruction of lignin. Indeed, it makes it possible to increase renewable carbon content while achieving exceptional properties required in many thermoset polymers, unlike many biosourced compounds. The presence of an *ortho*-methoxy and a *para*-allylic group on a phenolic ring makes eugenol suitable for the synthesis of high-value added thermoset precursors. By itself, eugenol's aromatic group is an asset for both high T_g and fire-retardant materials. When one combines it with the ability of eugenol to form biphenyls, Alder-ene, benzoxazines, phosphates or cyclophosphazenes, precursors to materials with high T_g (> 150 °C) and thermostability can be manufactured. These precursors, especially epoxy and allyl-terminated bear the potential to replace the petroleum-based standards such as bisphenol A, bismaleimide or phenol-formaldehyde. Thus, we can consider that eugenol-based precursors could find their place in mechanically and thermally demanding fields, such as

composites for transport and aeronautics, which is still a pitfall for most derivatives of renewable resources.

REFERENCES

Papers of particular interest, published within the period of review, have been highlighted as:

* of special interest

** of outstanding interest

1 “Plastics the facts 2022”, <https://plasticseurope.org/knowledge-hub/plastics-the-facts-2022/>, Last accessed 15 July 2024

2 * J.S. Mahajan, R.M. O’Dea, J.B. Norris, L.S.T.J. Korley, T.H. Epps, Aromatics from Lignocellulosic Biomass: A Platform for High-Performance Thermosets, *ACS Sustain. Chem. Eng.* 8 (2020) 15072–15096. <https://doi.org/10.1021/acssuschemeng.0c04817>

This contribution provides an overview of the sustainable thermosets achievable from aromatic building blocks to target the replacement of phenol formaldehyde resins and bisphenol-based resin. Vanillin, guaiacols, eugenol and syringaldehyde based precursors and their polymerization routes are reported along with the properties of the resulting thermosets.

3 C. Zhang, T.F. Garrison, S.A. Madbouly, M.R. Kessler, Recent advances in vegetable oil-based polymers and their composites, *Prog. Polym. Sci.* 71 (2017) 91–143. <https://doi.org/10.1016/j.progpolymsci.2016.12.009>.

4 S. Caillol, Cardanol: A promising building block for biobased polymers and additives, *Curr. Opin. Green Sustain. Chem.* 14 (2018) 26–32. <https://doi.org/10.1016/j.cogsc.2018.05.002>.

5 * J. Liu, S. Wang, Y. Peng, J. Zhu, W. Zhao, X. Liu, Advances in sustainable thermosetting resins: From renewable feedstock to high performance and recyclability, *Prog. Polym. Sci.* 113 (2021) 101353. <https://doi.org/10.1016/j.progpolymsci.2020.101353>

This contribution reviews the thermosets from renewable resources, including eugenol based-ones. Here, the focus is made on benzoxazines, epoxy resins and unsaturated polyesters. The performance of such thermosets is compared between building blocks produced by treatment of renewable feedstocks, *i.e.*, carbohydrates (itaconic acid, furans, ...), lignins (vanillin, eugenol) and vegetable oils.

6 H. Dodiuk, S.H. Goodman, Handbook of thermoset plastics Third Edition, 2014. [https://doi.org/10.1016/S0140-6736\(02\)29551-3](https://doi.org/10.1016/S0140-6736(02)29551-3).

7**R. Morales-Cerrada, S. Molina-Gutierrez, P. Lacroix-Desmazes, S. Caillol, Eugenol, a Promising Building Block for Biobased Polymers with Cutting-Edge Properties, *Biomacromolecules* 22 (2021) 3625–3648. <https://doi.org/10.1021/acs.biomac.1c00837>.

An extensive review of the means to functionalize eugenol and the polymers achievable starting from eugenol. This review covers the reactive sites of eugenol and reactions available to obtain functionalized eugenol. Then after, the polymers achievable from functionalized eugenol are reported and classified by polymerization routes.

8 ** W. Yang, H. Ding, D. Puglia, J.M. Kenny, T. Liu, J. Guo, Q. Wang, R. Ou, P. Xu, P. Ma, P.J. Lemstra, Bio- renewable polymers based on lignin- derived phenol monomers: Synthesis, applications, and perspectives, *SusMat* 2 (2022) 535–568. <https://doi.org/10.1002/sus2.87>.

This contribution provides an overview of the polymers achievable from lignin-based building blocks, including eugenol. The polymerization method and the main properties (T_g , moduli, ...) of the resulting polymers are reviewed.

9 D. Matykiewicz, K. Skórczewska, Characteristics and Application of Eugenol in the Production of Epoxy and Thermosetting Resin Composites: A Review, *Materials*. 15 (2022) 4824. <https://doi.org/10.3390/ma15144824>.

10 B. Kumar, D.O. Agumba, D.H. Pham, H.C. Kim, J. Kim, Recent progress in bio-based eugenol resins: From synthetic strategies to structural properties and coating applications, *J. Appl. Polym. Sci.* 139 (2022) 51532. <https://doi.org/10.1002/app.51532>.

11 * S. Caillol, B. Boutevin, R. Auvergne, Eugenol, a developing asset in biobased epoxy resins, *Polymer*. 223 (2021) 123663. <https://doi.org/10.1016/j.polymer.2021.123663>.

This contribution provides an overview of epoxy-functionalized eugenol and the resulting thermosets. Here, the means to epoxidize eugenol are reviewed as well as the properties of the resulting thermosets.

12 R. Sonnier, C. Negrell, S. Pourchet, G. Boni, Biobased flame-retardant technology for polymeric materials, in: *Anal. Biochem.*, 2018; pp. 227–254. <https://doi.org/10.1016/B978-0-323-90771-2.00007-9>

13 P. Danthu, R. Simanjuntak, F. Fawbush, J.M. Leong Pock Tsy, G. Razafimamonjison, M.M. Abdillahi, M. Jahiel, E. Penot, The clove tree and its products (clove bud, clove oil, eugenol): Prosperous today but what of tomorrow's restrictions?, *Fruits* 75 (2020) 224–242. <https://doi.org/10.17660/th2020/75.5.5>.

14 M. Ulanowska, B. Olas, Biological properties and prospects for the application of eugenol—a review, *Int. J. Mol. Sci.* 22 (2021) 3671. <https://doi.org/10.3390/ijms22073671>.

15 Eugenol, EC N°: 100.002.355, <https://echa.europa.eu/fr/substance-information/-/substanceinfo/100.002.355>
Last accessed 15 July 2024

16 M.T. Alhaffar, M.N. Akhtar, S.A. Ali, Utilization of catecholic functionality in natural safrole and eugenol to synthesize mussel-inspired polymers, *RSC Adv.* 9 (2019) 21265–21277. <https://doi.org/10.1039/c9ra04719k>.

17 M.L. Shrestha, M. Ionescu, Aliphatic–Aromatic Polyols by Thiol–Ene Reactions, *J. Polym. Environ.* 26 (2018) 2257–2267. <https://doi.org/10.1007/s10924-017-1123-1>.

18 C.H. Chen, C.M. Lin, T.Y. Juang, M.M. Abu-Omar, C.H. Lin, The reaction of activated esters with epoxides for self-curable, highly flexible, A2B2- and A3B3-type epoxy compounds, *Polym. Chem.* 10 (2019) 3983–3995. <https://doi.org/10.1039/c9py00377k>.

19 M.A. Lucherelli, A. Duval, L. Avérous, Biobased vitrimers: Towards sustainable and adaptable performing polymer materials, *Prog. Polym. Sci.* 127 (2022) 101515 . <https://doi.org/10.1016/j.progpolymsci.2022.101515>.

20* J. Zhong, Y. Huang, Y. Chen, L. Li, C. Guo, Synthesis of eugenol-modified epoxy resin and application on wood flame retardant coating, *Ind. Crops Prod.* 183 (2022) 114979. <https://doi.org/10.1016/j.indcrop.2022.114979>.
This article covers the synthesis of a diepoxybiseugenolphenylphosphate through a two-step synthesis. This epoxy precursor is cured with diaminodiphenylmethane and the fire-retardancy of the resulting coating is demonstrated.

21 M. Biron, The Plastics Industry: Economic Overview, in: *Thermosets and composites* 2014. <https://doi.org/10.1016/b978-1-4557-3124-4.00002-x>.

22 E. Zago, E. Dubreucq, J. Lecomte, P. Villeneuve, F. Fine, H. Fulcrand, C. Aouf, Synthesis of bio-based epoxy monomers from natural allyl- and vinyl phenols and the estimation of their affinity to the estrogen receptor α by molecular docking, *New J. Chem.* 40 (2016) 7701–7710. <https://doi.org/10.1039/c6nj00782a>.

23 Epichlorohidrin EC N°: 100.003.128 <https://echa.europa.eu/fr/substance-information/-/substanceinfo/100.003.128>, Last accessed 15 July 2024

24 M. Neda, K. Okinaga, M. Shibata, High-performance bio-based thermosetting resins based on bismaleimide and allyl-etherified eugenol derivatives, *Mater. Chem. Phys.* 148 (2014) 319–327. <https://doi.org/10.1016/j.matchemphys.2014.07.050>.

-
- 25 L. Pezzana, E. Malmström, M. Johansson, M. Sangermano, UV-curable bio-based polymers derived from industrial pulp and paper processes, *Polymers*. 13 (2021) 1530. <https://doi.org/10.3390/polym13091530>.
- 26 C.E. Hoyle, C.N. Bowman, Thiol-ene click chemistry, *Angew. Chemie - Int. Ed.* 49 (2010) 1540–1573. <https://doi.org/10.1002/anie.200903924>.
- 27 X. Zhang, Y. Cai, X. Zhang, T. Aziz, H. Fan, C. Bittencourt, Synthesis and characterization of eugenol-based silicone modified waterborne polyurethane with excellent properties, *J. Appl. Polym. Sci.* 138 (2021) 50515. <https://doi.org/10.1002/app.50515>.
- 28 J. Ji, X. Ge, W. Liang, R. Liang, X. Pang, R. Liu, S. Wen, J. Sun, X. Chen, J. Ge, A simple preparation route for Bio-Phenol MQ silicone resin via the hydrosilylation method and its autonomic antibacterial property, *Polymers*. 11 (2019) 1389. <https://doi.org/10.3390/polym11091389>.
- 29 M. Yi, X. Chen, P.S. Shuttleworth, L. Tan, Y. Ruan, Y. Xu, J. Zheng, S. Wu, S. Hu, S. Xie, Z. Guan, G. Yin, Y. Cui, Facile fabrication of eugenol-containing polysiloxane films with good optical properties and excellent thermal stability via Si–H chemistry, *J. Mater. Chem. C* 9 (2021) 8020–8028. <https://doi.org/10.1039/d0tc05279e>.
- 30 D. Guzmán, A. Serra, X. Ramis, X. Fernández-Francos, S. De la Flor, Fully renewable thermosets based on bis-eugenol prepared by thiol-click chemistry, *React. Funct. Polym.* 136 (2019) 153–166. <https://doi.org/10.1016/j.reactfunctpolym.2018.12.024>.
- 31 H. Cramail, B. Bizet, O. Lamarzelle, P. Durand, E. Grau, H. Cramail, B. Bizet, O. Lamarzelle, P. Durand, G. Hibert, *Bio-Sourced Polymers: Recent Advances*, 2020. https://doi.org/10.1142/9789811210587_0005.
- 32 A. Llevot, E. Grau, S. Carlotti, S. Grelier, A. Llevot, E. Grau, S. Carlotti, S. Grelier, H.C. Admet, ADMET polymerization of bio-based biphenyl compounds, *Polym. Chem.* 6 (2015) 7693–7700. <https://doi.org/10.1039/C5PY01232E>.
- 33 G.H.M. De Kruijff, T. Goschler, N. Beiser, A. Stenglein, O.M. Türk, S.R. Waldvogel, Sustainable access to biobased biphenol epoxy resins by electrochemical dehydrogenative dimerization of eugenol, *Green Chem.* 21 (2019) 4815–4823. <https://doi.org/10.1039/c9gc02068c>.
- 34 N. Amarnath, S. Shukla, B. Lochab, Harvesting the Benefits of Inherent Reactive Functionalities in Fully Biosourced Isomeric Benzoxazines, *ACS Sustain. Chem. Eng.* 6 (2018) 15151–15161. <https://doi.org/10.1021/acssuschemeng.8b03631>.
- 35 C. Chen, Y. Cao, X. Lu, X. Li, H. Yao, Z. Xin, Copolymer of eugenol-based and pyrogallol-based benzoxazines: Low curing temperature and enhanced corrosion resistance, *Colloids Surfaces A Physicochem. Eng. Asp.* 609 (2021) 125605. <https://doi.org/10.1016/j.colsurfa.2020.125605>
- 36 J. Qin, H. Liu, P. Zhang, M. Wolcott, J. Zhang, Use of eugenol and rosin as feedstocks for biobased epoxy resins and study of curing and performance properties, *Polym. Int.* 63 (2014) 760–765. <https://doi.org/10.1002/pi.4588>.
- 37 S. Li, C., C. Chen, H. Lin, T. Liu, Heat-resistant underfill epoxy adhesive, preparation method and application, CN116836664, 2023
- 38 L. Liu, Y. Qian, Eugenol-based non-isocyanate polyurethane and preparation method thereof, CN116731311, 2023
- 39 K. Deng, D. Sun, Preparation method of nanometer super antifouling coating, CN116063891, 2023
- 40 B. Li, Z. Hui, Preparation of bio-based phenolic amine epoxy curing agent, CN117720423, 2023

41 S. Dai, F. Xiong, G. Chen, Preparation of environmentally friendly jointing composition for ceramic tiles, CN116904152, 2023

42 C.H. Chen, S.H. Tung, R.J. Jeng, M.M. Abu-Omar, C.H. Lin, A facile strategy to achieve fully bio-based epoxy thermosets from eugenol, *Green Chem.* 21 (2019) 4475–4488. <https://doi.org/10.1039/c9gc01184f>.

43 J.T. Miao, L. Yuan, Q. Guan, G. Liang, A. Gu, Biobased Heat Resistant Epoxy Resin with Extremely High Biomass Content from 2,5-Furandicarboxylic Acid and Eugenol, *ACS Sustain. Chem. Eng.* 5 (2017) 7003–7011. <https://doi.org/10.1021/acssuschemeng.7b01222>.

44 B. Lochab, V. Duhan, S. Mukherjee, A green process for synthesis of 4th generation benzoxazine monomers IN202311028812, 2023

45 S. Xu, Y. Chen, S. Huo, X. Yang, Preparation of bio-based main chain benzoxazine resin with excellent mechanical properties, dielectric properties and anti-hygroscopicity, CN117777441, 2024

46 M. Shibata, N. Tetramoto, A. Imada, M. Neda, S. Sugimoto, Bio-based thermosetting bismaleimide resins using eugenol, bieugenol and eugenol novolac, *React. Funct. Polym.* 73 (2013) 1086–1095. <https://doi.org/10.1016/j.reactfunctpolym.2013.05.002>.

47 M. Decostanzi, R. Tavernier, G. Fontaine, S. Bourbigot, C. Negrell, S. Caillol, Eugenol-based thermally stable thermosets by Alder-ene reaction: From synthesis to thermal degradation, *Eur. Polym. J.* 117 (2019) 337–346. <https://doi.org/10.1016/j.eurpolymj.2019.05.018>.

48 Y. Ning, D. sen Li, M. cun Wang, Y. chi Chen, L. Jiang, Bio-based hydroxymethylated eugenol modified bismaleimide resin and its high-temperature composites, *J. Appl. Polym. Sci.* 138 (2020) 49631. <https://doi.org/10.1002/app.49631>.

49 Z. Zhang, Y. Zhou, L. Cai, L. Xuan, X. Wu, X. Ma, Synthesis of eugenol-functionalized polyhedral oligomer silsesquioxane for low-k bismaleimide resin combined with excellent mechanical and thermal properties as well as its composite reinforced by silicon fiber, *Chem. Eng. J.* 439 (2022) 135740. <https://doi.org/10.1016/j.cej.2022.135740>.

50 K. Xie, Z. Zhang, K. Zhang, X. Li, Y. Bao, J. Huang, X. Li, J. Liu, W. Wei, Bismaleimide resin co-modified by allyl ether of resveratrol and allyl ether of eugenol-grafted polysiloxane with enhanced toughness, heat resistance, and flame retardancy, *Polym. Adv. Technol.* 35 (2024) e6191. <https://doi.org/10.1002/pat.6191>.

51 Flame Retardant Market Size, Share & Trends Analysis By Product, By Application, By End-use, By Region, And Segment Forecasts, 2023 – 2030, Grand Viwe Research, 2023

52 A.U.R. Shah, M.N. Prabhakar, J. Il Song, Current advances in the fire retardancy of natural fiber and bio-based composites – A review, *Int. J. Precis. Eng. Manuf. - Green Technol.* 4 (2017) 247–262. <https://doi.org/10.1007/s40684-017-0030-1>.

53 M.S. Özer, S. Gaan, Recent developments in phosphorus based flame retardant coatings for textiles: Synthesis, applications and performance, *Prog. Org. Coatings* 171 (2022). <https://doi.org/10.1016/j.porgcoat.2022.107027>.

54 W. Wei, J. Huang, J. Liu, X. Li, Self-flame-retardant thermosetting resin composition for packaging third-generation semiconductor device, CN117362914, 2023

55 C. Miao, H. Zhang, W. Zhenwei, W. Wang, Copolycarbonate and preparation method thereof CN117534823, 2023

56 H. Lu, Z. Jiang, Q. Yuan, J. Liu, X. Yang, X. Gan, Z. Guo, Z. Yang, Y. Wanf, L. Wu, Silicone-modified polycarbonate film with salt spray resistance for salt spray-resistant anti-corrosion coating, CN117534953, 2023

57 W. Wei, Z. Zhang, X. Li, X. Liu, Toughening agent for bismaleimide resin composition and preparation method thereof, CN116444796, 2022

58 L. Jiang, C.G. Wang, P.L. Chee, C. Qu, A.Z. Fok, F.H. Yong, Z.L. Ong, D. Kai, Strategies for lignin depolymerization and reconstruction towards functional polymers, *Sustain. Energy Fuels* 7 (2023) 2953–2973. <https://doi.org/10.1039/d3se00173c>.

59 N. Ramdani, H. Zaimeche, M. Derradji, Biobased thermally-stable aromatic cyanate ester thermosets: A review, *React. Funct. Polym.* 168 (2021) 105037. <https://doi.org/10.1016/j.reactfunctpolym.2021.105037>.

60 Y. Ning, D. sen Li, M. cun Wang, L. Jiang, Bio-resourced eugenol derived phthalonitrile resin for high temperature composite, *J. Appl. Polym. Sci.* 138 (2021) 50721. <https://doi.org/10.1002/app.50721>.

61 J. Wan, J. Zhao, B. Gan, C. Li, J. Molina-Aldareguia, Y. Zhao, Y.T. Pan, D.Y. Wang, Ultrastiff Biobased Epoxy Resin with High T_g and Low Permittivity: From Synthesis to Properties, *ACS Sustain. Chem. Eng.* 4 (2016) 2869–2880. <https://doi.org/10.1021/acssuschemeng.6b00479>.

62 T. Liu, L. Sun, R. Ou, Q. Fan, L. Li, C. Guo, Z. Liu, Q. Wang, Flame retardant eugenol-based thiol-ene polymer networks with high mechanical strength and transparency, *Chem. Eng. J.* 368 (2019) 359–368. <https://doi.org/10.1016/j.cej.2019.02.200>.

63 D. Appavoo, N. Amarnath, B. Lochab, Cardanol and Eugenol Sourced Sustainable Non-halogen Flame Retardants for Enhanced Stability of Renewable Polybenzoxazines, *Front. Chem.* 8 (2020) 711. <https://doi.org/10.3389/fchem.2020.00711>

64 J. Liu, Z. He, G. Wu, X. Zhang, C. Zhao, C. Lei, Synthesis of a novel nonflammable eugenol-based phosphazene epoxy resin with unique burned intumescent char, *Chem. Eng. J.* 390 (2020) 124620. <https://doi.org/10.1016/j.cej.2020.124620>.

65 * L.X. Fang, Y.G. Feng, L. Li, G.W. Yin, H. Wang, Z. Xu, L.W. Xu, Cyclotriphosphazene-Centered Six-Arm Eugenol-Linked Low-Dielectric Materials with High Thermostability and Transparency, *ACS Sustain. Chem. Eng.* 10 (2022) 13133–13144. <https://doi.org/10.1021/acssuschemeng.2c03951>

This article combines eugenol-based cyclophosphazenes and silylated benzocyclo- butene to reach high-performance and transparent resins. The resulting polymers exhibit T_a between 111 and 216 °C as well as T_{5%} above 400 °C (in both inter and oxidative atmospheres)