

#### Porous Scintillating architecture for radioactive gaz detection

Christophe Dujardin, Fréderic Chaput, Benoit Sabot, Pavlo Mai, Raphaël Marie-Luce, Sylvie Pierre

#### ► To cite this version:

Christophe Dujardin, Fréderic Chaput, Benoit Sabot, Pavlo Mai, Raphaël Marie-Luce, et al.. Porous Scintillating architecture for radioactive gaz detection. OPTIQUE, Jul 2021, Dijon (FR), France. . hal-04863477

#### HAL Id: hal-04863477 https://hal.science/hal-04863477v1

Submitted on 6 Jan 2025

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers. L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

# **Porous scintillating architechtures for radioactive gaz detection**

https://www.sparte-project.eu

# Christophe Dujardin<sup>1</sup> on behalf of the SPARTE consortium

RadioacTivE gas detection <sup>1</sup> Institut lumière matière (iLM), UMR5306 Université Lyon 1-CNRS, Université de Lyon 69622 Villeurbanne, France <sup>-</sup>Laboratoire de Chimie, CNRS UMR 5182, Universite de Lyon, Ecole Normale Superieure de Lyon,, F69364 Lyon, France <sup>3</sup>Department of Materials Science, University of Milano-Bicocca, Via Cozzi 55, 20125 Milano, Italy <sup>4</sup>Czech Technical University in Prague, Faculty of Nuclear Sciences and Physical Engineering, Prague 1, Czech Republic <sup>5</sup>CEA-LIST, Laboratoire National Henry Becquerel, LNE-LNHB, Gif-sur-Yvette, F-91191, France <sup>6</sup>CEA,-List, Laboratoire Capteurs et Architectures Électroniques, F-91120 Palaiseau, France <sup>7</sup>ICOHUP SAS, Limoges, France <sup>8</sup>Nano Active Film Srl, Salerno, Italy

Context: The SPARTE project aims to propose a solution based on highly efficient porous scintillators enabling the detection and the quantification of several critical radioactive rare gas isotopes of primary importance. Radionuclides are instable and naturally lead to the emission of ionizing radiations at a certain decay rate stated as half-life (from ns to billions of years). These ionizing radiations are photons or particles such as g, X-ray, b, a particles. While technologies to detect g and X-rays is mature and commercially available, b and a particles are trickier to detect because of their short mean free path in the

matter. This short mean free path strongly depends on the energy of the particle, in the case of  $\beta$  it can be some  $\mu m$  in water up to some cm for higher energy one and become some cm up to a meter in air. When their energy is reduced, their detection becomes critical because they have to be almost in contact with the sensor to be detected. Beyond detecting the presence of radioactive elements, metrology requires to quantify the activity which involves the modelling of the matter radiation, and for most of the b-active critical elements, reliable and widely deployable technology does not exist.

The penetration depth of electrons in matter and the energy distribution of emitted  $\beta$  from the targeted radionucleide

SPARTF



The scintillating nanoparticle aerogel approach



The scintillating sponge concept: the radioactive fluid has to penetrate the scintillator to enchance the interaction probability



Scintillating properties requirement:

High scintillation yield since low energy electron have to be detected Fast decay time since double & triple coincidence will used Visible emission for PMTs (UV accepted) No requirement on the density

The Metal-Organic Framework The MOFs show an intrinsic porosity, demonstrate some scintillating properties and are therefore good candidates

### Nanocrystal and aerogel approach

Linkers: highly efficient emitters

DPA(COOH)

Diphenylanthracene moiet

Hafnium metal-oxo cluste

Hf<sub>6</sub>O<sub>4</sub>(OH)<sub>4</sub>(COO<sup>-</sup>)









## Typical aerogel (not from that one)



# MOF single crystal approachl approach



 Large and highly pure mm-sized MOF-5 single crystal • N<sub>2</sub> glovebox – preserve from moisture







They are sensitive to the water They give a scintillation signal





Good scintillation yield and fast decay The issue: the transparency

and demonstrate a gaz uptake (see below)

Real use condition: gaz loaded with <sup>85</sup>Kr Liquid scintillator set-up with triple to double coincidence technique.

Adapted with cap for gaz flow





#### Conclusion

**Left:** The YAG:Ce aerogel demonstrate a very good sensitivity (D) and a efficiency similar to (T/D) liquid scintillator (ultimate gold), despite its geometry is not optimized. No gaz uptake is observed. The measurement confirms the better efficiency of Ce<sup>4+</sup> doped YAG

**Right:** Measured on MOF powder, MOF demonstrate a gaz uptake which is an advantage for very low dose measurements

# Some MOFs experience uptake of the gaz





This project has received funding from the European Union's Horizon 2020 research and innovation programme under grant agreement No 899293