



SiC for Sensing in Harsh Environment

Marc Portail, Sylvain Kern, Clément Berger, Cécile Ghouila-Houri, Vincent Guigoz, Daniel Alquier, Ileana Florea, Isabelle Dufour, Abdelkrim Talbi, Philippe Pernod, et al.

► To cite this version:

Marc Portail, Sylvain Kern, Clément Berger, Cécile Ghouila-Houri, Vincent Guigoz, et al.. SiC for Sensing in Harsh Environment. International Conference on Silicon Carbide and Related Materials, Sep 2024, Rayleigh, North Carolina, United States. hal-04922976

HAL Id: hal-04922976

<https://hal.science/hal-04922976v1>

Submitted on 31 Jan 2025

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

SiC for Sensing in Harsh Environment



Marc Portail¹, Sylvain Kern², Clément Berger³, Cécile Ghouila-Houri², Vincent Guigoz¹, Daniel Alquier³, Illeana Florea¹, Isabelle Dufour⁴, Abdelkrim Talbi², Philippe Pernod² and Jean-François Michaud³

¹ CRHEA, Université Côte d'Azur, CNRS, UMR 7073, F-06560 Valbonne, France

² IEMN – Centrale Lille, Université de Lille, CNRS, Univ. Polytechnique Hauts-de-France, UMR 8520, F-59000 Lille, France

³ GREMAN, Université de Tours, CNRS, INSA, UMR 7347, F-37000 Tours, France

⁴ IMS, Université de Bordeaux, CNRS – F-33405 Talence, France



Motivations

- Growing needs for sensors for use under high temperatures, radiative atmospheres, high gas velocities: aerospace, automotive, nuclear...
- Multiple approaches for the design of sensors : junctions, resonating or fixed micro / nano structures (MEMS, NEMS) ...
- Specific issues for harsh environments : chemical or physical approach ? which material ?
- RESISTE project : French national consortium to develop SiC based sensors, from epitaxy to demonstrators. (ANR funding ANR-22-PEEL-0002)

SiC for Sensing ?


- Large band gap semiconductor (2,3 – 3,2eV for 3C- and 4H- polype)
- High thermal conductivity
- Large Temperature Coefficient of Resistivity (TCR)
- High Young Modulus (> 400 GPa)
- Existing know-how for processing (etching, metalization...)

M. Mehregany, C. A. Zorman *Thin Solid Films* 355 (1999) 518-524


P.M. Sarro, *Sensors and Actuators* 82 (2000) 210

3C-SiC / Si Epitaxy



- 3C-SiC grown on Si for benefiting from surface micromachining (@CRHEA).
- CVD process using $\text{SiH}_4 - \text{C}_3\text{H}_8 - \text{HCl}$ chemistry.
- Monocrystalline and textured 3C-SiC films deposited on semi insulating silicon wafers,






STEM cross section views of monocrystalline 3C-SiC(100) film (left) and textured 3C-SiC film (right)



- Low resistivity required for hot wire fabrication : nitrogen doped growth process.
- Variation of the resistivity over two orders of magnitude.
- Lower doping levels for textured 3C-SiC epilayers.





- Post epitaxy : CMP process (@NOVASIC s.a)
- $R_q < 0.3\text{nm}$ after CMP
- Mechanical properties of epilayers assessed by fabrication of cantilevers (@GREMAN).






Thermal Measurements of Gas Flow

- Realisation of SiC suspended hot wires for measurement of turbulent air flow (@IEMN).
- Design based on a bonding approach of SiC/Si on glass to suppress the leakage of Si substrate.
- SiC etching : ICP-RIE $\text{CHF}_3 / \text{O}_2 / \text{Ar}$ mixture. Si release with XeF_2 .
- I(V) characterizations on a temperature controlled probing station.




- Integration of chip on PCB and adjustment on a NACA008 airfoil.
- Characterization in a tabletop wind tunnel in air.
- Response of SiC chip up to 15m/sec.






Hydrogen Detection

- Fabrication of SiC-based gas sensor without functionalized layer (@GREMAN / IMS)
- Resonating millimeter sized cantilevers.
- Targetting a discriminating method : both frequency and damping monitoring.



- Proof of concept for low detection limit of H_2 in atmosphere.
- Discrimination between gases demonstrated.



Change in resonance frequency of 3C-SiC cantilevers, as a function of the surrounding gas concentration, for H_2 in N_2 (left) and CO_2 in N_2 (right). Detections as low as 0.2 % for H_2 and 0.25 % for CO_2 , in nitrogen, have been achieved