



HAL
open science

Porous biochar for improving the CO₂ uptake capacities and kinetics of concrete

Matthieu Mesnage, Rachelle Omnée, Johan Colin, Hamidreza Ramezani, Jena Jeong, Encarnacion Raymundo-Piñero

► To cite this version:

Matthieu Mesnage, Rachelle Omnée, Johan Colin, Hamidreza Ramezani, Jena Jeong, et al.. Porous biochar for improving the CO₂ uptake capacities and kinetics of concrete. *Cement and Concrete Composites*, 2025, 157, pp.105932. 10.1016/j.cemconcomp.2025.105932 . hal-04935666

HAL Id: hal-04935666

<https://hal.science/hal-04935666v1>


Submitted on 7 Feb 2025

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.


L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.



Distributed under a Creative Commons Attribution 4.0 International License



Porous biochar for improving the CO₂ uptake capacities and kinetics of concrete

Matthieu Mesnage^a, Rachele Omnée^a, Johan Colin^b, Hamidreza Ramezani^c, Jena Jeong^{b,**}, Encarnacion Raymundo-Piñero^{a,*} 

^a CNRS, CEMHTI UPR3079, Univ. Orléans, 1D Avenue de La Recherche Scientifique, 45071, Orléans, France

^b IRC (Institut de Recherche en Constructibilité), ESTP, 94230, Cachan, France

^c ICMN (Interfaces, Confinement, Matériaux, Nanostructures), CNRS, Université D'Orléans, 45071, Orléans, France

ARTICLE INFO

Keywords:

CO₂ uptake
Concrete
Biochar
Carbonation kinetics
Porosity
CO₂ diffusivity

ABSTRACT

Carbonation is a natural process in concrete where atmospheric CO₂ diffuses into the pores of the material and reacts with cement hydrates to form calcium carbonate. Although this process can help to sequester atmospheric CO₂ and mitigate rising levels in urban areas, it slows down over time, resulting in low CO₂ uptake over the service life of concrete. This study proposes a sustainable method to improve carbonation kinetics and CO₂ capture in cement materials by incorporating highly porous biochar. The biochar, derived from seaweed pyrolysis, has a highly developed surface area, including micropores optimised for CO₂ adsorption, mesopores and macropores, as well as oxygen-rich surface groups. These properties allow the biochar to efficiently adsorb CO₂ and retain water. The biochar particles embedded in the cement matrix act as reservoirs for water and CO₂, influencing hydration and carbonation. The addition of biochar increases water retention in the composite, which promotes the formation of capillary pores and enhances the carbonation process. Experimental data and numerical simulations show that the adsorption of CO₂ in the micropores of biochar facilitates the flow of CO₂ through the composite, allowing deeper carbonation. The interaction between biochar and cement matrix enhances CO₂ diffusion and promotes calcium carbonate formation both within the biochar and at the biochar-cement interface, further improving CO₂ uptake. The study demonstrates that the incorporation of porous biochar into cement materials significantly increases their potential for CO₂ capture, offering a promising approach to sustainable construction and carbon sequestration.

1. Introduction

Since the beginning of the 20th century, the expansion of industries worldwide, coupled with the proliferation of individual transportation powered by fossil fuels, has dramatically increased global CO₂ emissions [1]. Locally, these heightened anthropogenic CO₂ emissions contribute to rising atmospheric CO₂ concentrations. Currently, typical outdoor concentrations range between 400 and 500 ppm; however, in urban environments—such as underground parking lots or tunnels—concentrations frequently exceed 500 ppm and can reach up to 1000 ppm, depending on factors such as time, weather, and traffic density [2]. In indoor spaces, CO₂ concentrations can easily surpass 1000 ppm, raising concerns about health issues, particularly among vulnerable groups like

young children [3–5]. Consequently, in addition to the ecological challenges posed by rising CO₂ emissions, there are significant health implications in indoor environments, as the efficiency of air ventilation is heavily reliant on the quality of outdoor air [6].

In parallel with efforts to reduce CO₂ emissions, capturing and storing CO₂ in urban areas could be effectively achieved using concrete materials. Indeed, concrete—the most widely used construction material—has a natural capacity to capture CO₂ within its intrinsic porosity and to store it through a natural carbonation process. Traditionally, carbonation of concrete has been viewed as a detrimental process that adversely affects the durability of reinforced concrete structures [7–10]. However, several studies have demonstrated through kinetic models that concrete possesses the potential for CO₂ storage throughout its life

* Corresponding author. Encarnación RAYMUNDO-PIÑERO CEMHTI-CNRS Orleans, Site Haute Température, 1D avenue de la Recherche Scientifique, Orléans cedex 2, CS 90055 45071, France.

** Corresponding author.

E-mail address: raymundo@cnrs-orleans.fr (E. Raymundo-Piñero).

<https://doi.org/10.1016/j.cemconcomp.2025.105932>

Received 11 December 2023; Received in revised form 30 October 2024; Accepted 7 January 2025

Available online 9 January 2025

0958-9465/© 2025 The Authors. Published by Elsevier Ltd. This is an open access article under the CC BY license (<http://creativecommons.org/licenses/by/4.0/>).

cycle [11–13]. Nonetheless, the carbonation process tends to slow over time. The primary driving force behind this phenomenon is the diffusion of CO₂ into the porous capillary network of concrete [14]. The CO₂ gas combines with the condensed water layer surrounding the pore walls [15] to form carbonate ions (CO₃²⁻), releasing H⁺ ions. These CO₃²⁻ ions and H⁺ then react with cement hydrates, leading to the precipitation of calcium carbonate (CaCO₃) and the release of water [11,16]. Since CaCO₃ has a greater molar volume than hydrates [17,18], its precipitation results in progressive clogging of capillary pores, reducing pore diameters [15,17,19] and consequently lowering CO₂ diffusivity, which in turn adversely affects carbonation kinetics [15,20,21].

At the end of service life of concrete building, the material can be reused as Recycled Concrete Aggregate (RCA) following demolition. Recent findings indicate that RCA exhibits higher CO₂ uptake capacities due to its increased exposed surface area after crushing and grinding [22]. Research has shown that CO₂ capture in RCA can reach between 2 % and 5 % by weight. Additionally, the size of the RCA and its degree of water saturation significantly influence its carbonation. Although carbonated RCA demonstrates improved mechanical strength [23], its reuse in practical engineering applications remains limited due to the management and energy demands associated with CO₂ carbonation processes on an industrial scale.

Thus, the present study aims to address the limitations of CO₂ uptake capacity in concrete materials by developing composite materials that incorporate RCA alongside a new component: porous carbon with high CO₂ uptake capacities. Porous carbons are versatile materials characterized by high specific surface areas and nanometric pore dimensions, which can be tailored through the selection of precursor materials and synthesis methods. This highly developed porous structure, encompassing microporosity (diameter ≤2 nm), mesoporosity (2 nm ≤ diameter ≤50 nm), and macroporosity (diameter ≥50 nm), enables the adsorption of a wide range of gas molecules, including CO₂ [24]. The adsorption of gas molecules in the porosity of carbon is driven by the high internal energy of the carbon atoms at the pore surfaces, which facilitates the retention of gas adsorbate molecules via van der Waals forces within the porous structure [25]. Additionally, the presence of surface functional groups, particularly heteroatoms like oxygen at the edges of the carbon graphene layers, enhances adsorption of polar adsorbate molecules such as water. While sedimentary rocks, including bituminous coal [26] and lignite [27], can be utilized, biomass waste currently represents the primary feedstock, allowing for the recycling of various low-cost carbonaceous organic materials on a large scale [28]. Furthermore, the production of carbon materials from waste biomass may yield a negative carbon footprint, as the CO₂ sequestered during the photosynthesis of biomass exceeds the emissions produced during synthesis [29,30]. Biochars are normally produced through the thermal treatment (pyrolysis) in an inert atmosphere of carbon-rich precursors. Biochar typically exhibits specific surface areas below 350 m² g⁻¹ [31, 32]. The production of porous carbons from a biochar requires an additional so-called activation process to increase porosity and CO₂ uptakes capacities [24,31].

In recent years, the incorporation of biomass-based carbon materials, such as biochar, as additives in cementitious materials has been proposed as a mitigation strategy to reduce CO₂ emissions while simultaneously enhancing certain mechanical or thermal properties. Substituting a portion of cement with a material that has a negative carbon footprint could contribute to reducing CO₂ emissions within the construction sector. Studies have demonstrated that incorporating biochar powders into concrete can enhance mechanical strength through filler effects and increased densification of the cement matrix during carbonation curing [32–40]. The porous characteristics of biochars also positively influence the thermal insulation properties of cement by enhancing thermal resistance [41]. However, the use of highly porous carbon materials to improve the CO₂ uptake capacity of concrete has been infrequently reported. Horgnies et al. have published several reports evaluating the beneficial effects of adding porous carbon to fresh

concrete to increase NO₂ adsorption in the hardened product [42–44]. Nevertheless, no studies have specifically focused on enhancing concrete carbonation during its service life for atmospheric CO₂ removal through the incorporation of a high surface area biochar, due to the presence of a large amount of micropores with sizes ~0.65–0.8 nm adapted to CO₂ adsorption [24]. In this study, we propose such a highly porous biochar with a large volume of micropores, taking advantage of the fact that direct pyrolysis of seaweed biomass has been shown to be a promising method for producing high surface area carbon without additional activation processes. Specifically, pyrolysis of seaweeds rich in carrageenan or sodium alginate has resulted in porous biochars with specific surface areas exceeding 1000 m²/g [45].

Therefore, the purpose of this study is to develop a functional composite material with enhanced CO₂ storage capacities compared to conventional cementitious materials. The limitations of CO₂ uptake capacity in concrete will be addressed by formulating composite materials that incorporate both porous biochar and RCA. The CO₂ uptake capacity of these composite materials will be evaluated using a controlled CO₂ chamber, with regulated temperature and humidity over several days. The quantification of CO₂ uptake during carbonation will facilitate kinetic tracking to study the role of porous carbon in CO₂ capture. In addition to CO₂ quantification, physicochemical characterizations will be conducted at various carbonation intervals to gain deeper insights into the synergistic effects of biochar on concrete carbonation. To further investigate the influence of carbon particles on CO₂ uptake in the composite materials, numerical simulations modelling the passage of CO₂ through the cement matrix into the carbon porosity will also be performed.

2. Materials and methods

2.1. Materials manufacturing

2.1.1. Porous biochar

The biomass selected for the preparation of biochar (LN 750) was *Lessonia Negrescens*, a type of brown seaweed. The stems and leaves were cut into approximately 5–7 mm particles, and pyrolysis was conducted using a Carbolite Gero HST 12/200 horizontal split tube furnace at 750 °C for 3 h, with a heating rate of 10 °C/min under an argon atmosphere to prevent oxidation. Following pyrolysis, the resulting biochar particles were washed with distilled water and dried at 100 °C. As previously mentioned, no activation steps were necessary to create a porous material, as self-activation occurred due to the chemical composition of the seaweed during thermal decomposition [45,46].

2.1.2. Composite materials

Composite materials, consisting of a cement matrix and recycled concrete aggregates (RCA) sourced from BONNA SABLA, France, were prepared according to two formulations. The first formulation served as a reference material without porous biochar (composite Type I), while the second included LN 750 biochar particles (composite Type II). Ordinary Portland cement (CEM I 52.5) was used as the matrix in both formulations. Type I contained only RCA, whereas Type II included both RCA and LN 750. The volume of biochar added was equivalent to the volume of RCA replaced, ensuring that the (aggregates + carbon)/cement volumetric ratio in Type II was equal to the aggregates/cement volumetric ratio in Type I. Both the RCA and biochar particles had a granulation size ranging from 5 to 7 mm. After mixing with a water/cement ratio of 0.45, the composite materials were cast in silicon molds measuring 7 × 3 × 2.5 cm³. Nine molds were filled for each formulation and placed in a desiccator filled with water to maintain a moisture-saturated atmosphere (RH ≈ 100 %). Hydration was allowed to continue for a minimum of 28 days.

2.2. Physico-chemical characterization of materials and composites

The characterization of porous texture of the biochar was conducted through gas adsorption using nitrogen at 77 K and carbon dioxide at 273 K with a Quadrasorb Evo Analyser. Nitrogen was utilized as the adsorbate to assess microporosity ($0.7 \text{ nm} < \text{pore diameter} < 2 \text{ nm}$) and mesoporosity ($2 \text{ nm} < \text{pore diameter} < 50 \text{ nm}$), while carbon dioxide was employed to evaluate small microporosity (i.e., pore diameter $< 0.7 \text{ nm}$). Specific surface areas were calculated from the nitrogen adsorption isotherm using the Brunauer-Emmett-Teller (BET) model, and pore size distributions were determined using Non-Local Density Functional Theory (NLDFT). The specific surface area and volume of the micropores were calculated by applying the Dubinin-Radushkevich (DR) model to the carbon dioxide adsorption isotherm at 273 K. The carbon dioxide adsorption capacity of LN 750 biochar at room temperature was determined by performing a carbon dioxide adsorption isotherm at 298 K.

Characterization of the large mesopore and macropore ranges was performed on both the materials and composites using Mercury Intrusion Porosimetry (MIP) with a Micromeritics Autopore IV porosimeter. The contact angle (θ) was set to 130° , and the mercury surface tension (γ) was set to 485 mN/m . Applied pressures ranging from 1.46 kPa to 206.8 MPa enabled the assessment of pore sizes from 6 nm to $854 \mu\text{m}$, using the Washburn equation [47]. For LN 750, samples were first dried in an oven at 100°C for 24 h to remove any moisture. In contrast, composite materials and RCA samples were dried at a maximum of 70°C for 24 h to avoid the removal of bound water contained within the cement hydrates.

Open porosity, density, and water sorption were determined using hydrostatic weighing, applied to the composite materials, LN 750, and RCA. After drying the samples, air was evacuated from the pores under vacuum. Subsequently, the out-gassed materials were immersed in water to monitor water uptake. Open porosity, bulk and skeletal densities, and the water sorption coefficient were calculated from the scaled masses according to the following equations:

$$\Phi = \frac{m_h - m_s}{m_h - m_i} \times 100 \quad (1)$$

$$\rho_b = \frac{m_s}{m_h - m_i} \quad (2)$$

$$\rho_s = \frac{m_s}{m_s - m_i} \quad (3)$$

$$WA = \frac{m_h - m_s}{m_s} \quad (4)$$

With:

- Φ : the open porosity in % of the sample volume.
- ρ_b : the bulk density of the sample in $\text{g}\cdot\text{cm}^{-3}$.
- ρ_s : the skeletal density of the sample in $\text{g}\cdot\text{cm}^{-3}$.
- WA: the water sorption coefficient by mass in the sample.
- m_s , m_i and m_h : respectively, the dry mass, the immersed mass and the saturated surface dried mass of the sample.

2.3. Accelerated carbonation experiments

Samples measuring $3.5 \times 3 \times 2.5 \text{ cm}^3$ were first pre-conditioned in a desiccator filled with NH_4NO_3 salt to achieve a relative humidity (RH) of 63%. NH_4NO_3 was selected to maintain the RH within the optimal range of 50–75%, ensuring the ideal condensed water content in the cement matrix for carbonation. The carbonation experiments on the mortar samples were conducted under accelerated conditions at atmospheric pressure and ambient temperature using a BINDER CB 150 CO_2 chamber, with the CO_2 concentration set to 1%. The experiment lasted for 30 days over several composites of each formulation carbonated in parallel.

Two or three samples were taken at the same time at 0, 7, 14, 20, and 30 days of carbonation and split into two pieces in order to collect the maximum amount of data to provide reliable averages of CO_2 uptake and different textural and chemical properties. The samples carbonated for 30 days were also used for post-mortem characterizations via MIP measurements, and the biochar particles were extracted for characterization through TPD-MS measurements.

2.4. Quantification of CO_2 uptake

To evaluate carbonation evolution, carbonation depth analysis was performed on the carbonated composite samples. The samples were split in half, and the exposed surfaces were sprayed with a phenolphthalein solution. The carbonation front was revealed as colorless ($\text{pH} \leq 10$), while the uncarbonated front appeared purple ($\text{pH} \geq 12.5$). Since one side of the composites was in contact with the carbonation chamber, CO_2 penetration on that side was hindered, resulting in slower advancement of the carbonation front. A digital processing of the images using ImageJ v1.53 software has been done for accurately assessing the percentage of carbonated areas [48]. The carbon-cement matrix interface was examined using optical microscopy with an Olympus BX51.

Quantification of the CO_2 uptake was accomplished through Temperature Programmed Desorption coupled with Mass Spectrometry (TPD-MS). Samples weighing 10–20 mg were placed in a thermobalance and heated up to 1000°C at a rate of $10^\circ\text{C}/\text{min}$ under an inert atmosphere (Argon, $100 \text{ mL}/\text{min}$). The decomposition products (gases evolved) were monitored in real-time using an online mass spectrometer (Skimmer, Netzsch).

2.5. Numerical modelling approaches

To understand the interface between the porous biochar and the cement matrix under CO_2 diffusion, numerical modelling was conducted across two scales: macro and atomistic. The macro-scale study was based on a two-phase model consisting of a biochar particle and the cement matrix. Utilizing a multi-reactional and time-dependent carbonation model [18], numerical simulations were performed using the Finite Element Method with the commercial software ComsolMP. The model considered a two-phase medium comprising one porous biochar particle and its surrounding cementitious matrix. CO_2 diffusion was assumed to occur only within the porous grain, while the cementitious matrix underwent carbonation. To more accurately reflect the surface roughness of the porous grain and its complex geometry, a 3D laser scan was performed to model the biochar particle, which was then incorporated into a rectangular cement prism measuring $2 \text{ cm} \times 1 \text{ cm} \times 0.5 \text{ cm}$. The mesh contained over 1 million elements, and the computation time lasted for 30 min using 121 processors and 512 GB of RAM.

The atomistic-scale study employed the Grand Canonical Monte Carlo algorithm [49,50]. The structure of the porous biochar was constructed based on experimental results from the structure factor and radial distribution function of a commercial carbon [51]. The 3D reconstruction was achieved using the Hybrid Reverse Monte Carlo method [52–55], incorporating a multi-staging process that included energy minimization, structure factor fitting, and constraints for three-membered rings [56]. Two layers of calcium silicate were generated using the Wollastonite structure through custom-written C++ code [57], which were then positioned adjacent to the activated carbon structure within periodic simulation boxes. Binary CO_2 /water adsorption simulations were conducted using the Grand Canonical Monte Carlo algorithm [49,50].

3. Results and discussion

3.1. Composite materials preparation

Fig. 1a summarizes the steps involved in manufacturing the




Fig. 1. Composite materials preparation (a). Sections of the composite materials Type I (left) and Type II (right) after hydration (b).

composites. A detailed formulation of the composite materials is presented in Table 1. Type I was prepared as a reference material using recycled concrete aggregates (RCA). For Type II, 40 % of the RCA volume was replaced with biochar particles of similar size, approximately 6 mm. Table 1 indicates that the amount of cement used is the same for both composites. However, to maintain an equivalent amount of effective water and the water-to-cement (w/c) ratio, an additional volume of water was incorporated during the mixing process for the preparation of Type II.

LN 750 is a highly porous and hydrophilic biochar [58] that can sorb up to 746 % of its weight in water (as shown in Table 2). Consequently, 68 mL of water was added during the preparation of the Type II composite to compensate for the water uptake by the porous biochar. As a result, the porous carbon does not absorb any additional water from the cement matrix and the rheology of the mix is maintained. Since the density of the biochar is lower than that of the RCA (see Table 2), the aggregate-to-cement (a/c) ratio is smaller for Type II, even though the volume of aggregates remains the same in both composites. After hydration, Fig. 1 illustrates that the aggregates in both Type I and Type II are homogeneously distributed within the cement matrix.

3.2. Physico-chemical characterizations of materials and composites

The physicochemical characterization of the porous biochar particles

Table 1
Formulations for Type I and Type II composite materials expressed in $\text{g}\cdot\text{cm}^{-3}$.

Composition ($\text{g}\cdot\text{cm}^{-3}$)	Type I	Type II
CEM I 52.5	0.508	0.509
RCA	0.623	0.406
Porous carbon	–	0.013
Effective water	0.201	0.201
w/c ^a	0.45	0.45
a/c ^b	1.22	0.79

^a water/cement weight ratio.

^b aggregate(+carbon)/cement weight ratio.

was performed before their incorporation into the concrete formulation. From the point of view of porosity, the pyrolysis of seaweed stems and leaves results in the development of various pore size ranges, from microporosity to macroporosity. The porous texture of the biochar particles was analyzed using nitrogen (N_2) and carbon dioxide (CO_2) gas adsorption to evaluate the micro- and mesoporosity, and mercury intrusion porosimetry (MIP) for assessing meso- and macroporosity. As illustrated in Fig. 2a, the nitrogen adsorption isotherm for LN 750 exhibited a Type IV isotherm shape, characterized by a hysteresis loop between the adsorption and desorption curves. The gradual gas adsorption observed at a relative pressure (P/P_0) of less than 0.1 is associated with volume filling in micropores, while the hysteresis at higher pressures corresponds to gas condensation in mesopores [25,59]. The BET specific surface area calculated was $1324 \text{ m}^2/\text{g}$, and the NLDFT pore size distribution (Fig. 2b) revealed a significant portion of pores within the micropore range ($d < 2 \text{ nm}$), with a pore volume of $0.4 \text{ cm}^3/\text{g}$. Additionally, another peak was detected in the mesopore range between 2 and 10 nm, corresponding to a pore volume of $0.35 \text{ cm}^3/\text{g}$.

From the CO_2 adsorption isotherm obtained on LN 750 at 273 K, the volume of micropore with diameters smaller than 0.7 nm, as determined by the Dubinin-Radushkevich equation, was equal to $0.4 \text{ cm}^3/\text{g}$. These results indicate that microporosity under 0.7 nm is even more developed than the larger microporosity and mesoporosity present in the biochar. This porosity was developed during the pyrolysis in reason of the presence of alkaline earth metals in the seaweed promoting a process of so-called self-activation [45]. This kind of microporosity with pore diameters of ca. $\sim 0.65\text{--}0.8 \text{ nm}$ were reported as optimal for CO_2 storage [24].

The larger mesoporosity and macroporosity of the biochar were determined using MIP. The pore size distribution shown in Fig. 2c reveals a broad peak in the pore range between 300 nm and 3 μm , with a maximum around 1 μm . The macropore volume was measured at $2.42 \text{ cm}^3/\text{g}$. This macroporosity is attributed to the parent cellular structure of the seaweed prior to pyrolysis. Table 2 indicates that the biochar exhibits a total open porosity of 49 %, as determined by mercury intrusion, along with a low bulk density of $0.15 \text{ g}/\text{cm}^3$. The apparent

Table 2

Mercury Intrusion porosimetry (MIP) and hydro-static weighing (HW) results obtained on LN750, RCA and Type I and Type II composite materials after hydration: Open porosity Φ , bulk density ρ_b , skeletal density ρ_s , average pore diameter and water sorption (WA).

		LN 750	RCA	Type I - NC	Type II - NC
MIP	Φ (%)	–	7.0 ± 1.6	9.5 ± 0.6	14.9 ± 0.2
	$0.006 < d < 0.3 \mu\text{m}$				
	Φ (%)	35.9 ± 0.7	4.0 ± 0.9	1.8 ± 0.2	10.2 ± 1.1
	$0.3 < d < 4 \mu\text{m}$				
	Φ_{tot} (%)	49.2 ± 0.1	16.4 ± 2.2	13.3 ± 0.2	30.5 ± 1.3
ρ_b ($\text{g}\cdot\text{cm}^{-3}$)		0.15 ± 0.00	2.01 ± 0.04	1.96 ± 0.02	1.56 ± 0.03
HW	Φ_{tot} (%)	92.6 ± 0.6	10.9 ± 0.6	18.2 ± 1.1	35.5 ± 1.1
	ρ_b ($\text{g}\cdot\text{cm}^{-3}$)	0.12 ± 0.01	2.41 ± 0.02	2.15 ± 0.05	1.65 ± 0.03
	ρ_s ($\text{g}\cdot\text{cm}^{-3}$)	1.69 ± 0.23	2.70 ± 0.02	2.63 ± 0.02	2.56 ± 0.01
	WA (%)	746 ± 38	4.5 ± 0.3	8.5 ± 0.7	21.5 ± 1.1




Fig. 2. Textural characterization. N_2 adsorption isotherm for LN750 at 77K (a) and NLDFT pore size distribution (b). MIP pore size distribution (c) and associated intruded volumes (d) for RCA, LN750 and composites Type I and Type II.

porosity and bulk density can also be assessed through water sorption. As mentioned in the previous section, LN 750 particles can sorb approximately 750 wt% of water due to their highly developed porosity, which is further enhanced by their hydrophilic nature. In fact, LN 750 contains a significant amount of oxygen surface functional groups (see TPD-MS in Fig. S1 of the supporting information), providing an hydrophilic character to the carbon surface [58]. Table 2 demonstrates that the open porosity for water sorption in LN 750 reached as high as 92.6 wt%, corresponding to a bulk density of 0.12 g/cm^3 and a low skeletal density of 1.69 g/cm^3 .

Fig. 2c illustrates the pore size distribution obtained through MIP for Type I and Type II samples after hydration, assessing the impact of LN 750 on composite porosity. Cement materials typically exhibit various pore types, ranging from approximately $0.001 \mu\text{m}$ to over $1000 \mu\text{m}$ [60, 61]. The smallest pores, known as gel pores, range roughly from 0.001 to $0.01 \mu\text{m}$ and correspond to voids created during hydration by the formation of colloidal Calcium Silicate Hydrates (CSH) particles. These are followed by capillary pores, which range from 0.01 to $1 \mu\text{m}$, corresponding to the spaces originally occupied by water among the anhydrous cement particles. These spaces become vacant as cement hydrates

form during hydration [62]. As hydration progresses, capillary pores tend to decrease in volume and size as more spaces are filled with cement hydrates, particularly CSH, while the overall volume of gel pores increases. Additionally, a small fraction of porosity can be attributed to air voids that become entrapped in the paste during mixing and casting, typically ranging from $10 \mu\text{m}$ to over $10000 \mu\text{m}$. Unlike gel and capillary pores, which form an interconnected network with channels linking them, air voids are generally isolated from each other and thus cannot be detected by MIP; they do not contribute to liquid or gas transport.

In cement paste, cement particles are usually packed randomly during mixing, creating a homogeneous pore size distribution throughout the structure during hydration. For mortars and concrete materials, the introduction of millimetre-scale aggregates in the mix induces “wall effects,” resulting in a rearrangement of the cement particles. In this arrangement, smaller particles tend to pack closely against the aggregate surfaces, while larger ones are located further away [63]. Some researchers have suggested that micro-bleeding effects occur during mixing [64,65], which refer to the accumulation or entrapment of mixing water around the aggregate surfaces. The combination of wall effects and micro-bleeding creates interfaces between the cement matrix

and the aggregate surfaces, leading to a higher water-to-cement (W/C) ratio than that of the bulk paste. This results in increased porosity, as a lower cement content combined with higher water content expands and enlarges the capillary voids formed during hydration. According to Elsharief et al. [66], both the size of the aggregates and the initial W/C ratio influence this interface porosity: smaller aggregates and lower W/C ratios correlate with reduced porosity at the interface. The width of these interfaces typically matches the size of the cement particles, usually not exceeding 20–50 μm [63].

Fig. 2c indicates that the pore sizes for Type I and Type II are primarily distributed within the range of 0.006–0.3 μm . Some of the porosity in these materials appears to be attributed to the recycled concrete aggregates (RCA), as shown in Fig. 2c, which also displays pores in the 0.006–0.3 μm range. This porosity is associated with the capillary porosity of the old hardened cement paste remaining on the aggregates, exhibiting a significant distribution in the 0.006–0.01 μm range compared to the 0.02–0.3 μm range. This may suggest that the old hardened cement paste has undergone partial carbonation, as clogging in some areas of the capillary porosity could lead to a reduction in pore size (see quantification in Table 2). Indeed, hydrostatic weighing revealed that the RCA had bulk densities and water sorption of 2.41 g cm^{-3} and 4.5 %, respectively (Table 2). These results align closely with those obtained by Zhang et al. [67] on carbonated RCA and are comparable to findings on natural aggregates, confirming that the RCA used in the formulations was already significantly carbonated. Consequently, the capillary porosity observed in Type I material was derived from both the RCA and the cement used to prepare the composite.

For the Type II materials, which contain the same amount of cement as Type I but have part of the RCA aggregates replaced with biochar particles, Fig. 2c shows that the pores in the range of 0.006–0.3 μm are distinctly more developed, leading to increased capillary porosity (Table 2). The capillary porosity in the Type II composite reached 14.9 %, compared to 9.5 % for Type I. Furthermore, Fig. 2c reveals an additional peak in the 0.3–4 μm range for Type II. By comparing this with the pore size distribution of LN 750, it is clear that this peak corresponds to the porosity of the added carbon. Thus, incorporating porous biochar into the formulation significantly influences material porosity. The increase in capillary porosity, coupled with the emergence of new porosity in Type II, results in a total porosity of 30.5 %, as opposed to 13.3 % for the material without carbon. Table 2 also indicates that adding low-density biochar reduces the density of the composites.

The results obtained from hydrostatic weighing (HW) experiments on the Type I and Type II composites reveal a notable effect of biochar addition on open porosity (Φ), bulk density (ρ_b), skeletal density (ρ_s), and water sorption capacity (WA). The open porosity obtained through water sorption shows an increase similar to that observed with mercury intrusion upon adding the porous carbon. The open porosity percentage for Type II reached 35.5 %, compared to 18.2 % for Type I. Such an increase in porosity cannot be solely attributed to the addition of porous carbon material with 92.6 % porosity, as the weight percentage of biochar in the composite is only 1.2 % of the total weight (Table 1). Therefore, a more developed capillary porosity will also contribute to the higher open porosity in Type II. Considering that LN 750 can sorb over 700 wt% of water, additional water was introduced during the preparation of Type II to maintain the same W/C ratio as Type I. However, it is possible that some of the added water is desorbed from the biochar into the cement matrix during hydration [68,69]. Compared to Type I, these bleeding effects, could lead to a local increase in the W/C ratio at the interface with the cement matrix, similar to the interactions at the aggregate-cement interfaces. Such phenomena could explain the more developed network of capillary pores observed in Type II after hydration (Fig. 2c–Table 2). This factor, along with the addition of low-density biochar, reduces both the bulk density and skeletal density of the material. The creation of new porosity in the composite materials also significantly influences water uptake, as shown in Table 2. The Type

II composite could sorb 21.5 % of water, more than double the amount sorbed by Type I. In summary, the incorporation of porous biochar has a substantial effect on the textural properties of the composite and its water sorption capacity. Consequently, the carbonation process is likely to be affected.

To determine whether the presence of biochar affects the amount of carbonatable compounds during the mixing and hydration of the composites, Temperature-Programmed Desorption coupled to Mass Spectrometry (TPD-MS) was conducted to investigate and quantify their chemical composition. Fig. 3 illustrates the weight losses and the gases released from room temperature up to 900 $^{\circ}\text{C}$.

From room temperature to approximately 300 $^{\circ}\text{C}$, a significant weight loss occurs, associated with the release of H_2O . This H_2O release results from both sorbed water and the thermal decomposition of Calcium Silicate Hydrates (CSH) and tri- or mono-substituted aluminat ferrite phases (Aft/AFm), such as ettringite. The weight loss for Type I in this temperature range was 8.4 wt%, while for Type II, it averaged 12.8 wt%, corresponding to 4669 $\mu\text{mol H}_2\text{O}\cdot\text{g}^{-1}$ and 7113 $\mu\text{mol H}_2\text{O}\cdot\text{g}^{-1}$, respectively. Given the higher water sorption capacity of the Type II composite (as shown in Table 2), these differences likely arise from the desorption of sorbed H_2O within the porosity of the composite.

The weight loss observed in the range of 400–550 $^{\circ}\text{C}$ is also associated with H_2O release, corresponding to the dehydration of $\text{Ca}(\text{OH})_2$. The weight loss linked to H_2O evolution was 3.8 wt% for Type I and 4.4 wt% for Type II, indicating a higher amount of the $\text{Ca}(\text{OH})_2$ phase in Type II, likely located at the cement/biochar interface due to its preferential precipitation in the carbon-cement interfaces [65].

Finally, the weight loss in the range of 600–900 $^{\circ}\text{C}$ corresponds to CO_2 release from the thermal decomposition of CaCO_3 . The weight loss associated with CaCO_3 indicated that the Type I composite contained 2.6 wt% of CO_2 , while the amount in Type II was approximately 3.7 wt%. These small amounts correspond to the carbonation of recycled concrete aggregates (RCA) and the composite itself. The differences observed by TPD-MS on hydrated and carbonated phases in the Type I and II composites has been confirmed by XRD (Fig. S2a). The evolution of these different phases during carbonation will be monitored by TPD-MS.

3.3. Accelerated carbonation of composites

Composite material samples were carbonated under accelerated conditions using an incubator with 1 % CO_2 and 65 % relative humidity (RH) for up to 30 days. Multiple sample batches were carbonated




Fig. 3. TPD-MS results combining weight losses and desorbed gas profiles obtained for Type I and Type II composites. Heating rate = 10 $^{\circ}\text{C}\cdot\text{min}^{-1}$ under 100 ml min^{-1} Ar flow.

simultaneously to conduct carbonation depth analysis and quantify CO₂ uptake using TPD-MS.

Fig. 4 illustrates the carbonation depths of samples subjected to varying time intervals, determined by spraying a phenolphthalein solution, which allowed for monitoring pH changes following CO₂ gas penetration and the carbonation of hydrates. The figure indicates that the extent of the carbonated surface of the composite—represented by the uncolored regions—increases more rapidly over time for the sample containing biochar. Specifically, the depth measurements reveal that the carbonation reaction appears to be enhanced in the vicinity of the porous biochar particles. These observations clearly demonstrate that biochar positively influences CO₂ diffusion within the cement matrix. After 30 days of carbonation, the carbonated surface of the Type I composite was estimated through the analysis of several specimens for each material carbonated in parallel, to cover approximately 78 % of the total surface, compared to around 95 % for Type II.

The evolution of the cement phases during carbonation was analyzed using TPD-MS, which combined data obtained from weight loss and the gases released during heat treatment. From the H₂O and CO₂ released as the temperature rises, the contributions to weight loss due to the thermal decomposition of the hydrates and carbonates can be quantified and separated, as shown in the previous section for the composites after hydration. The interest in the use of TPD-MS instead of thermogravimetric analysis (TG or DTG) alone is more evident in the analysis of carbonated materials. TPD-MS allows to quantify the cement phases more accurately, since hydrates such as Ca(OH)₂ and some amorphous carbonates can decompose in similar temperature ranges, contributing together to the same TG-DTG peak. Fig. 5 shows the loss of weight in % and the evolution of the H₂O and CO₂ gas in μmol/g/s in relation to the respective loss of mass. Fig. 5a present the TPD-MS at different carbonation times for the Type I material and Fig. 5b for the Type II material containing the biochar. Fig. 5a and b depict a general trend characterized by a decrease in H₂O evolution alongside an increase in CO₂ release throughout the carbonation process. This aligns with the transformation of hydrated phases into carbonated ones. The gas evolution profiles for both materials indicate that at the onset of carbonation, there is primarily the consumption of Ca(OH)₂, correlating with the H₂O peak observed between 400 and 500 °C, which produces crystallized CaCO₃ in its calcite polymorph, corresponding to the CO₂ peak detected between 700 and 800 °C. As carbonation progresses, CO₂ evolution shifts to lower temperatures due to the carbonation of C-S-H (calcium silicate hydrate) and Afm/Aft phases, leading to the formation

of amorphous or poorly crystallized CaCO₃ [70,71] that decomposes between 400 and 700 °C [72–74]. The carbonation of C-S-H also results in the emergence of vaterite and aragonite CaCO₃ polymorphs [70], which decompose in the same temperature range as amorphous and poorly crystallized calcite as described by Vogler et al. [72]. The presence of the different CaCO₃ polymorphs has been confirmed by XRD (Fig. S2b).

A closer examination of the CO₂ evolution peaks, comparing those from the reference material and the composite containing biochar (Fig. 6a), reveals that for a given number of carbonation days, the amount of CO₂ evolved is consistently higher for the composite with biochar. Over the first seven days of carbonation, both materials exhibit a predominant increase in the peak at 700–800 °C associated with the formation of calcite-like CaCO₃, with a more significant increase noted for the material containing biochar. As carbonation days increase, the reference Type I material (dotted lines in Fig. 6a) shows a steady evolution of CO₂ related to the formation of calcite-like CaCO₃, with further carbonation only resulting in an increase of amorphous or less crystalline CaCO₃ decomposing between 400 and 700 °C. In contrast, for the Type II composite material with biochar, the amount of all carbonated phases—both crystallized and more amorphous—continuously increases throughout the carbonation process. Thus, the presence of porous biochar also influences the chemical composition of the carbonated phases.

After quantifying the H₂O and CO₂ evolved from the thermal treatment of the composites over different carbonation durations, Fig. 6b confirms that the decrease of hydrated phases and the CO₂ uptake, expressed as mass percentage considering the total mass of material, are more pronounced in the Type II composite containing the porous biochar. To demonstrate that this enhanced CO₂ uptake is not related to a decrease in the density of the material due to the inclusion of low-density biochar (see Table 2), Fig. 6c and d illustrate the evolution of CO₂ uptake through carbonation based on exposed surface area (Fig. 6c) and material volume (Fig. 6d), respectively. It was observed that both materials exhibited roughly similar CO₂ uptake per material volume or accessible surface at seven days; however, the CO₂ uptake progressed more rapidly for the porous biochar Type II composite compared to the reference Type I composite as carbonation days increased.

The results clearly indicate that the addition of porous biochar positively influences both carbonation kinetics and the amount of CO₂ uptake. These findings align with the carbonation fronts shown in Fig. 4. Carbonation phenomena in concrete materials primarily depend on CO₂




Fig. 4. Cross sections of the composite materials after different carbonation days, sprayed with phenolphthalein solution (pink areas correspond to non-carbonated material). (For interpretation of the references to color in this figure legend, the reader is referred to the Web version of this article.)




Fig. 5. TPD-MS results combining weight losses and desorbed gas profiles obtained for Type I (a) and Type II (b) composites at different accelerated carbonation days. Heating rate = 10 °C.min⁻¹ under 100 ml min⁻¹ Ar flow.




Fig. 6. Detail on CO₂ evolution obtained for Type I and Type II composites at different accelerated carbonation days by TPD-MS (a). Quantification of the H₂O and CO₂ evolved from the thermal treatment of the composites at different carbonation days evolution in wt% of the total mass sample (b). CO₂ uptake given as gCO₂ evolved by cm² of the total accessible surface (c) and as gCO₂ evolved by cm³ of the total sample volume (d).

gas diffusion, followed by solubilisation in condensed water and subsequent reaction with the cement hydrates. As previously reported, the Type II composite with biochar exhibits a different porosity compared to the Type I reference composite. Indeed, different types of diffusion regimes occur within the cement's porosity based on pore sizes. For gel pores with a diameter of $d < 0.008 \mu\text{m}$, the Knudsen diffusion regime is dominant, as the pore diameter is significantly smaller than the mean free path (λ) of CO₂ molecules, which is approximately 84 nm ($d < \frac{\lambda}{10}$). In these conditions, CO₂ diffusivity is proportional to the average molecular speed of CO₂ and the pore radius. Additionally, surface diffusion may also occur in the smallest gel pores, where CO₂ molecules diffuse along the pore through successive adsorption-desorption reactions on adjacent active sites via van der Waals interactions [14,75]. Conversely, molecular diffusion prevails for pores with diameters greater than 0.8

μm , as the diameter exceeds the mean free path of CO₂ molecules by a factor of ten. In this case, CO₂ diffusivity depends solely on molecular speed and the mean free path of CO₂ molecules. For pores ranging between 0.008 and 0.8 μm , both Knudsen and molecular diffusion regimes coexist. Overall, the effective diffusivity of a cement paste can be estimated as the sum of the various diffusion regimes occurring in proportion to their respective porosity fractions [76]. As indicated by the mercury intrusion porosimetry (MIP) measurements, the incorporation of porous biochar into the cement matrix significantly increases the capillary pore volumes between 0.006 and 0.3 μm , along with the additional macropore volumes introduced by the own macroporosity of the biochar. The increase in these pore volumes likely enhances the contributions of the mixed Knudsen and molecular diffusion regime in the capillary range, as well as the molecular diffusion regime in the

macroporous range, leading to higher effective diffusivity in the composite compared to the reference material, which has a lower capillary porosity fraction and minimal porosity beyond 0.4 μm.

It is also important to note that carbonation itself impacts pore connectivity and CO₂ gas diffusion in cement-based materials. The change in porosity during carbonation depends on the composition of the material, specifically the type of cement and the inclusion of supplementary cementitious materials [17,77]. If the C-S-H content is high, carbonation can induce an increase in porosity as porous silica gel is generated [77]. However, in our case, the high content of Ca(OH)₂ in Portland cement generally leads to a reduction in pore size and porosity during carbonation [17]. The decalcification of Ca(OH)₂ to produce CaCO₃, which precipitates in the pores, results in an increase in solid volume, as the molar volume of CaCO₃ is greater than that of Ca(OH)₂. In this context, Type I and Type II composites were characterized after 30 days of carbonation using MIP, and the results were compared to those obtained from the uncarbonated samples. Fig. 7 confirms that, compared to the uncarbonated samples, pore distribution after carbonation evolves towards a reduction in larger capillary pores while an increase in smaller capillary pores is observed in both Type I and Type II composites. As discussed earlier, this result may be linked to the formation of CaCO₃ during carbonation, which precipitates over the pore walls and reduces pore diameters, thereby shifting the distribution towards smaller capillary pores. The increased mercury volume obtained from the 30-day carbonated Type II sample also indicates a significant reduction of the porosity with approximately 1 μm pore size corresponding to the biochar macroporosity. This may suggest a clogging effect of the pore walls caused by carbonated products diffusing into the biochar particles and obstructing porosity. Overall, the reduction in capillary porosity due to carbonation was notably more pronounced in the Type II composite. Fig. 7b presents capillary porosities calculated from the mercury-intruded volumes in the range of 5–300 nm relative to the total intruded mercury volumes in the samples. Results indicate that capillary porosity in Type I decreased from an average of 9.5 % to 8.2 %, while it decreased from 14.9 % to 11.1 % in Type II. This indicates that the relative porosity reduction for Type II is approximately three times higher than that for Type I, suggesting that carbonation was more effective in the Type II composite, consistent with the observations of carbonation depths in the 30-day carbonated samples. Nevertheless, the porosity of the composite containing porous biochar remains significantly higher than that of the reference Type I composite, even after carbonation. Thus, the improved carbonation efficiency observed for the composite with biochar (Fig. 6) can also be attributed to the more developed capillary pore network, which facilitates enhanced CO₂

diffusion rates.

To investigate the effect of biochar addition on CO₂ diffusion within the cement matrix, the CO₂ diffusivity (DCO₂) was calculated from the experimental data on CO₂ uptake presented in Fig. 6c. According to Yang et al. [78], the CO₂ uptake during cement matrix carbonation in concrete structures can be correlated with the total amount of absorbable CO₂ through carbonation in the cement and the carbonation depth at time t, expressed by the following equation:

$$U_{CO_2}(t) = a_{CO_2} \bullet x_c(t) \tag{5}$$

With:

- $U_{CO_2}(t)$ (g.cm⁻²), the CO₂ uptake in the concrete at carbonation time t
- a_{CO_2} (g.cm⁻³) the total amount of CO₂ fixed in the concrete by CaCO₃ formation
- $x_c(t)$ (cm), the carbonation depth at carbonation time t

According to the authors, $x_{CO_2}(t)$ can be theoretically calculated from a_{CO_2} , the CO₂ gas diffusion coefficient in the concrete and the atmospheric CO₂ concentration with the following equation:

$$x_{CO_2}(t) = \sqrt{\frac{2D_{CO_2} \bullet C_{CO_2}}{a_{CO_2}} \bullet t} \tag{6}$$

Incorporating equation (6) in (5), $U_{CO_2}(t)$ can be expressed as a time square root equation including a slope A, such as:

$$U_{CO_2}(t) = a_{CO_2} \bullet \sqrt{\frac{2D_{CO_2} \bullet C_{CO_2}}{a_{CO_2}} \bullet t} = A \bullet \sqrt{t} \tag{7}$$

As illustrated in Fig. 8a, the experimental CO₂ uptake for both Type I and Type II composites (from Fig. 6c) was fitted to the square root of carbonation time, represented by solid blue and red lines for Type I and Type II, respectively. This fitting allowed for the determination of the slopes for both composites (denoted as AT-I and AT-II). The experimental CO₂ diffusivity (DCO₂) was calculated using equation (7), while the theoretical a_{CO_2} was derived from the water-to-cement (W/C) ratio, hydration time, and cement content in the composite materials, following the equations provided by Yang et al. [78]. Detailed calculations can be found in the Supplementary Information. The experimental DCO₂(t) for Type I was measured at 3.2 × 10⁻⁸ m²/s, aligning with literature values for similar test conditions and compositions [21,79]. For Type II, the experimental DCO₂ was 6.2 × 10⁻⁸ m²/s. This higher diffusivity coefficient in Type II, confirms that the presence of biochar




Fig. 7. Evolution of the pore size distribution obtained by MIP on Type I and II composites after 30 days of carbonation (a). Effect of 30 carbonation days on the capillary porosity percentage (b).




Fig. 8. Fitting of the experimental CO₂ uptake in the Type I and Type II composites with the kinetic model (a). Scanned biochar particle (b) and numerical composite material (c). CO₂ concentration distribution on the cutting plane at 10 h (d) and detail around biochar particle (e). Comparison of CO₂ concentration distribution through the sample thickness for a numerical material composed by a cement matrix and for a material composed by the cement matrix and a porous biochar particle at 1 s, 10 s and 10 h (f).

particles enhances effective CO₂ diffusivity within the cement matrix.

To gain understanding on such a positive effect of biochar addition on CO₂ diffusion within the cement matrix, numerical simulations were conducted with a CO₂ gas flow passing through a composite sample, which was reconstructed digitally and included a scanned biochar particle (Fig. 8b) embedded in a cement matrix (Fig. 8c). In this model, unidirectional CO₂ gas flow diffusion was utilized, necessitating the application of symmetry boundary conditions around the specimen. The Dirichlet boundary condition was imposed solely on the external surface exposed to a 1 vol% concentration of CO₂, while the opposite side of the outer surface was left free, allowing the CO₂ gradient to influence the flow direction.

The time-dependent evolution of the CO₂ concentration gradient was calculated every second for up to 10 h. For comparison, simulations were also performed on a numerical sample devoid of biochar, with the porosity of the cement matrices in both numerical samples set to match those observed in the uncarbonated samples of Types I and II. Fig. 8d and e illustrate the CO₂ flow (represented as arrows) traversing the Type II composite after 10 h and the CO₂ concentration (represented in by colours from hot to cold when reducing concentration).

The numerical simulation reveals that the presence of the biochar particle in the cement matrix influences the CO₂ flow velocity and direction. As shown in Fig. 8d and more clearly in the zoom of Fig. 8e, the simulation reveals that the direction of the diffusing CO₂ gas flow changes dramatically, suggesting that the gas is adsorbed by the biochar particle. Specifically, the LN 750 biochar exhibits a CO₂ storage capacity (determined from the CO₂ adsorption isotherm at room temperature,

Fig. S3) as high as 158 mgCO₂.g⁻¹, in reason of its highly developed microporosity presenting the optimal pore size for CO₂ adsorption. This value is much higher than that obtained with other raw biochars, or even with biochars that have undergone additional post-treatment to modify their surface and/or porous texture to increase their capacity to adsorb CO₂ [31]. Due to such important adsorption of CO₂ into the microporosity of the biochar, the CO₂ flow originating from the surface decelerates more rapidly as it approaches the biochar, which reduces the concentration at the entrance of the pores. The flow then accelerates significantly within the biochar, owing to its high meso- and macroporosity. Consequently, the flow emerges on the opposite side with a velocity exceeding that in the cement matrix, as the elevated CO₂ concentration within the porosity of the biochar would establish a new gradient towards the bulk. The vector of the entering flow is directed toward the biochar and distributed in a homogeneous manner around the particle. Ultimately, the flow direction shifts from unidirectional to perpendicular to the grain, i.e., a circumferential direction for enhanced diffusion. Therefore, when the gas flow passes through such a highly porous medium, it subsequently diffuses in all directions around the particle (see "vector" arrows in Fig. 8d and e), resulting in an increase in the CO₂ concentration in the vicinity of the biochar particle. The last is illustrated in Fig. 8f presenting the distribution of the CO₂ concentration gradient on the cutting plane through the centre of the numerical composite sample (0 mm stands for the composite surface) at 1 s, 10 s, and 10 h for the Type II composite in comparison to the Type I. For the Type I the CO₂ concentration decrease continuously from the surface to the bulk of the material because the CO₂-hydrates reaction. However,

for Type II, the concentration decreases more rapidly in the vicinity of the carbon particle because the adsorption of CO_2 at the biochar microporosity, tends to diffuse rapidly through the carbon porosity and exit the particle at a higher concentration than for the Type I composite at the same carbonation time (10 s or 10 h).

This influence of biochar particles on CO_2 flow velocity and direction, which enhances CO_2 concentration at the interface with the cement matrix, was further corroborated by optical microscopy analysis. Fig. 9 shows images of the biochar-cement interface in the Type II composite before and after 30 days of carbonation. Fig. 9a indicates that the biochar particles are well integrated into the cement matrix, exhibiting good adhesion. The surface properties of the porous biochar, which contain a significant number of polar functional groups, promote the epitaxial growth of cement hydration products on the biochar surface, thus enhancing adhesion between the matrix and aggregates [80]. In Fig. 9b, a milky-colored layer was observed at the biochar interface in the 30-day carbonated sample, contrasting sharply with the rest of the cement matrix. This layer corresponds to the carbonation front depicted in Fig. 4, where carbonation initiates around biochar particles as the carbonation front reaches them. Thus, considering previous studies [35], the milky layer in Fig. 9b is attributed to the formation of CaCO_3 ,

which creates a highly carbonated layer around the biochar particles. This observation aligns with the numerical simulations, suggesting that the CO_2 concentration gradient generated by CO_2 diffusion through the biochar towards the cement matrix fosters the formation of a dense CaCO_3 layer in the vicinity of the biochar, as more CO_2 becomes available for carbonation.

Optical microscopy, as shown in Fig. 9b, also reveals the same milky solid deposition within the macroporosity of the biochar. The biochar particles were extracted from the composite after 30 days of carbonation and the core of the particle was sampled to perform a TPD-MS analysis. Fig. 9c presents the weight loss and the amount of H_2O and CO_2 gases evolved during the thermal treatment in an inert atmosphere of the biochar extracted from the composite after 30 carbonation days compared to the raw biochar. The biochar from the carbonated composite presents a weight loss in the 700–800 °C range associated with CO_2 evolution, which was not present in the raw biochar. These results suggest the presence of amorphous or poorly crystallized CaCO_3 within the porosity of the biochar. The precipitation of CaCO_3 in the porosity of the biochar is supported by a reduction in porosity in the 0.3–1 μm range, associated with the presence of the biochar in the composite, as observed through mercury intrusion porosimetry (MIP) (Fig. 7a). After 30 days of carbonation, porosity decreased from 10.2 % to 3.8 % in this




Fig. 9. Optical microscopy on biochar-cement interface over the initial Type II composite (a) and after 30 days of accelerated carbonation (b). TPD-MS results combining weight losses and desorbed CO_2 and H_2O gas profiles obtained for raw LN750 biochar (full lines) and on LN750 biochar extracted from a 30 days carbonated Type II composite (dashed lines) (c). Comparison of the desorbed CO_2 profiles after 30 carbonation days for the Type II composite and for the porous biochar extracted of that Type II composite.

range (Table 3). These findings confirm that biochar provides a suitable environment for the deposition of carbonation products. The contribution of CaCO_3 deposited inside the porosity of the biochar to the total carbonation products accounts for the pronounced shoulder seen in the CO_2 evolution profile of Type II composite after carbonation between 600 and 700 °C (Fig. 9d), which is nearly absent during the carbonation of the Type I composite without biochar (Fig. 6a).


Grand Canonical Monte Carlo (GCMC) simulations were conducted to further investigate the cement matrix/carbon interface during carbonation. Fig. 10a illustrates the interface between cement, predominantly containing CSH, and carbon. In the presence of 1 % CO_2 (10,000 ppm) and 65 % relative humidity, Fig. 10b shows that CO_2 molecules preferentially occupy the inter-layer spaces between CSH layers and the interface zone between CSH and carbon. Simultaneously, a large number of water molecules are adsorbed into the porosity of the carbon, and an interfacial water layer forms between the CSH and carbon, as depicted in Fig. 10b. Thus, in addition to the substantial amount of water near the biochar particles, which affects hydration and matrix porosity development through bleeding effects, the biochar porosity also contains a significant amount of water.

Consequently, the high concentration of water and CO_2 at the cement/biochar interface and within the porous network can explain the presence of CaCO_3 inside the porosity of the biochar and the dense CaCO_3 layer surrounding the biochar particles. This phenomenon can be paralleled with CO_2 geological sequestration [81]. It is well established that carbonate chemical weathering in aquatic ecosystems, including oceans, consumes atmospheric CO_2 . Specifically, the dissolution of calcite in CO_2 -containing water is crucial in many geological processes and serves as a significant atmospheric CO_2 mitigation strategy. The sculpting of karst landscapes and caves in limestone terrains or the formation of stalactites, stalagmites, columns, and other speleothems in caves are among the most remarkable examples [82]. In nature, when a high concentration of dissolved CO_2 interacts with rocks containing CaCO_3 , the following reactions have been extensively studied and documented [83–87]:



Under conditions of high CO_2 concentrations, Reaction (8) will proceed in the forward direction, leading to the dissolution of solid CaCO_3 . Conversely, when the amount of dissolved CO_2 in water decreases, the backward reaction will generate solid CaCO_3 , facilitating the formation of speleothems, as previously described.

During the carbonation process in composites, in addition to the presence of CO_2 , the conditions are also characterised by a high water content in the porosity, which would allow reaction (8) to take place over the calcite produced during carbonation. Notably, in cementitious materials containing portlandite, Reaction (8) would be predominantly forward. This could happen because the calcium bicarbonate solution can react with $\text{Ca}(\text{OH})_2$ to regenerate calcite, as shown by the following reaction:



Reaction 8 will be particularly favored in the vicinity of biochar particles where there is a high local water content, as determined by molecular dynamics (MD) simulations (Fig. 10). This reaction is also promoted by high CO_2 concentrations, as indicated by modelling

Table 3

Mercury Intrusion porosimetry (MIP) over Type I and Type II composites after 30 accelerated carbonation days.

	Φ (%) 0.006 < d < 0.3 μm	Φ (%) 0.3 < d < 4 μm	Φ_{tot} %	ρ_b g.cm ⁻³
Type I	8.2 ± 0.6	1.8 ± 0.0	12.0 ± 0.3	1.97 ± 0.01
Type II	11.1 ± 0.7	3.8 ± 0.7	17.7 ± 0.8	1.81 ± 0.09

(Fig. 8), and elevated levels of $\text{Ca}(\text{OH})_2$, confirmed by TPD-MS analysis (Fig. 5). Consequently, reaction (8) will lead to an increased consumption of $\text{Ca}(\text{OH})_2$, since the formation of CaCO_3 on the surface of portlandite inhibits further diffusion of CO_2 , significantly impacting the kinetics of carbonation. The weathering of CaCO_3 results in a greater conversion of $\text{Ca}(\text{OH})_2$ to CaCO_3 because the higher solubility of $\text{Ca}(\text{HCO}_3)_2$ and its diffusion in the water present at the cement/biochar interface enhances CO_2 diffusion throughout the bulk of the particle. This assertion is supported by quantifying the $\text{Ca}(\text{OH})_2$ consumption during carbonation, as demonstrated by integrating the H_2O gas evolution between 400 and 700 °C in the TPD-MS measurements presented in Fig. 5. For the composite containing biochar, the amount of consumed $\text{Ca}(\text{OH})_2$ consistently increases over the carbonation period (Fig. 5b), whereas for the Type I composite, the amount of $\text{Ca}(\text{OH})_2$ consumed shows minimal change after 7 days of carbonation (Fig. 5a). These results align with the observations in Fig. 6a, where the products of $\text{Ca}(\text{OH})_2$ carbonation—specifically, crystallized CaCO_3 that decomposes to release CO_2 gas around 700–800 °C—increased for the Type II composite during carbonation, while no significant growth was observed for Type I after 7 days.

Moreover, the presence of CaCO_3 within the porosity of the biochar particles suggests that they play a critical role in the aqueous diffusion of species through the water layer at the biochar-cement interface. The precipitation of CaCO_3 within the biochar could indicate that hydration products and calcite weathering products are diffusing into the porosity to react according to the reaction (9). The reaction nature-inspired mechanism that we propose here is illustrated in the scheme in Fig. 11. All the results presented above confirm that, in addition to influencing the matrix microstructure and CO_2 diffusion, highly porous biochar particles actively participate in CO_2 uptake through both physical and chemical mechanisms. Beyond the physisorption of CO_2 in the micropores, evidence exists for the precipitation of CaCO_3 within the meso- and macroporosity as it has been previously observed by Gupta et al. when using biochars with small surface areas presenting mainly macroporosity [35].

Overall, the biochar particles distributed within the cement matrix act as reservoirs for water and CO_2 , significantly impacting material hydration and carbonation. The incorporation of biochar into a cement-based material enhances both the kinetics of carbonation and the degree of carbonation of carbonatable hydrates.

Nevertheless, those results should be confirmed by using formulations of construction materials and in natural carbonation conditions.

4. Conclusions

This study presents an effective and sustainable strategy to address the slow carbonation kinetics of cement-based materials while simultaneously increasing CO_2 uptake capacity. The introduction of highly porous biochar particles into the formulation facilitates the valorisation of recycled concrete aggregates (RCA) into a composite material that efficiently captures CO_2 .

The porous biochar obtained from the pyrolysis of seaweeds exhibits interesting textural properties, characterized by a highly developed specific surface area, including micropores with optimal pore size for CO_2 adsorption together with mesopores and macropores, along with a significant presence of oxygen surface functionalities. These features confer both gas adsorption and hydrophilic properties to the biochar, promoting the adsorption of substantial amounts of CO_2 and the uptake of important amounts of liquid water. As a result, the carbon particles dispersed within the cement matrix, in conjunction with the RCA, serve as effective reservoirs for water and CO_2 , having a main role during material hydration and carbonation.

The porous nature of biochar significantly impacts porosity development during hydration. It can uptake over 700 wt% of water, and Grand Canonical Monte Carlo (GCMC) simulations indicate that this water is primarily located within the porosity of the biochar and at the




Fig. 10. (a) GCMC simulations performed at the interface between CSH and carbon (b) zooming images at the interface between CSH and carbon of separated adsorption of H₂O and CO₂.




Fig. 11. Scheme of the dual carbonation mechanism occurring close to the biochar-cement interface. Grey dialog boxes correspond to initial carbonation since orange dialog boxes correspond to the additional CaCO₃ precipitation by weathering of calcite and further reaction with Ca(OH)₂ and CO₂ at the carbon/cement interface. (For interpretation of the references to color in this figure legend, the reader is referred to the Web version of this article.)

carbon/cement interface. This substantial volume of water adjacent to the biochar particles affects hydration and matrix porosity development through bleeding effects, leading to the enhanced formation of capillary pores. The combination of this capillary porosity and the macropores of the biochar results in an open porosity of 30.5 %, compared to only 12.3 % for the composite without biochar. Furthermore, the introduction of biochar increases water uptake from 8.5 wt% to 21.5 wt%.

These physico-chemical changes induced by the addition of porous biochar to the cement matrix, in addition to the intrinsic porosity of the biochar, have a significant positive impact on both carbonation kinetics and CO₂ uptake. Employing a combined experimental and simulation approach, the observed faster kinetics for the biochar-enhanced composite can be attributed to a higher effective CO₂ diffusivity. The greater porosity of the Type II composite increases both Knudsen and molecular

diffusion rates. In addition, the CO₂ adsorption properties of the biochar conferred by its microporosity acted as a driving force to redirect the flow of CO₂ traversing the biochar from the sample surface to around the biochar surface, allowing deeper penetration into the concrete thickness.

The increased CO₂ uptake exhibited by the composites with biochar is associated with the formation of a dense carbonated layer at the carbon-cement interface and the presence of CaCO₃ within the biochar porosity. Indeed, the CO₂ and H₂O-rich environment at the carbon/cement interface enhances the carbonation degree of the carbonatable hydrates by solubilizing the CaCO₃ layer formed during carbonation, which limits further CO₂ diffusion through the bulk of the particle. The weathering of CaCO₃ leads to the formation of highly soluble Ca(HCO₃)₂, which diffuses in the water contained in the cement/biochar

interface to react with additional $\text{Ca}(\text{OH})_2$ and CO_2 . This secondary carbonation reaction could explain the production of additional CaCO_3 that precipitates within the matrix and inside the biochar porosity. This specific mechanism shifts the carbonation equilibrium toward deeper carbonation of the bulk cement hydrates, explaining the increase of both the carbonation rate and CO_2 uptake in the presence of a highly porous biochar.

In conclusion, the incorporation of a biochar with a porous texture adapted to high CO_2 and H_2O uptake into cement-based materials improves the carbonation kinetics and increases the degree of conversion of carbonatable hydrates, thus positioning concrete as a viable material for CO_2 capture.

CRedit authorship contribution statement

Matthieu Mesnage: Writing – original draft, Investigation, Formal analysis. **Rachelle Omnée:** Investigation, Formal analysis. **Johan Colin:** Resources, Investigation. **Hamidreza Ramezani:** Software, Investigation, Formal analysis. **Jena Jeong:** Writing – original draft, Visualization, Validation, Supervision, Project administration, Funding acquisition, Conceptualization. **Encarnacion Raymundo-Piñero:** Writing – review & editing, Validation, Supervision, Project administration, Funding acquisition, Conceptualization.

Declaration of competing interest

The authors declare the following financial interests/personal relationships which may be considered as potential competing interests: Encarnacion Raymundo-Piñero reports financial support was provided by Centre-Val de Loire Region. Encarnacion Raymundo-Piñero has patent pending to Assignee. If there are other authors, they declare that they have no known competing financial interests or personal relationships that could have appeared to influence the work reported in this paper.

Acknowledgements

The authors thank the Région Centre val de Loire (Project APR-IA PRESERVE convention n°2019 00134933 and co-financement bourses doctorales 2020) and the ESTP-IR for financial support.

Appendix A. Supplementary data

Supplementary data to this article can be found online at <https://doi.org/10.1016/j.cemconcomp.2025.105932>.

Data availability

Data will be made available on request.

References

- [1] H. Ritchie, M. Roser, P. Rosado, CO_2 and greenhouse gas emissions, Our World in Data (2020). <https://ourworldindata.org/co2-and-greenhouse-gas-emissions>.
- [2] I. Pigliautile, G. Marsaglia, A.L. Pisello, Investigation of CO_2 variation and mapping through wearable sensing techniques for measuring pedestrians' exposure in urban areas, *Sustainability* 12 (2020) 3936, <https://doi.org/10.3390/su12093936>.
- [3] P. Carreiro-Martins, A.L. Papoila, I. Caires, S. Azevedo, M.M. Cano, D. Virella, P. Leiria-Pinto, J.P. Teixeira, J. Rosado-Pinto, I. Annesi-Maesano, N. Neuparth, Effect of indoor air quality of day care centers in children with different predisposition for asthma, *Pediatr. Allergy Immunol.* 27 (2016) 299–306, <https://doi.org/10.1111/pai.12521>.
- [4] C. Kim, D. Choi, Y.G. Lee, K. Kim, Diagnosis of indoor air contaminants in a daycare center using a long-term monitoring, *Build. Environ.* 204 (2021) 108–124, <https://doi.org/10.1016/j.buildenv.2021.108124>.
- [5] M. Simoni, I. Annesi-Maesano, T. Sigsgaard, D. Norback, G. Wieslander, W. Nystad, M. Canciani, P. Sestini, G. Viegi, School air quality related to dry cough, rhinitis and nasal patency in children, *Eur. Respir. J.* 35 (2010) 742–749, <https://doi.org/10.1183/09031936.00016309>.
- [6] M.K. Kim, J.-H. Choi, Can increased outdoor CO_2 concentrations impact on the ventilation and energy in buildings? A case study in Shanghai, China, *Atmos. Environ.* 210 (2019) 220–230, <https://doi.org/10.1016/j.atmosenv.2019.04.015>.
- [7] J.A. Gonzalez, S. Algaba, C. Andrade, Corrosion of reinforcing bars in carbonated concrete, *Br. Corrosion J.* 15 (1980) 135–139, <https://doi.org/10.1179/bcj.1980.15.3.135>.
- [8] A. Steffens, D. Dinkler, H. Ahrens, Modeling carbonation for corrosion risk prediction of concrete structures, *Cement Concr. Res.* 32 (2002) 935–941, [https://doi.org/10.1016/S0008-8846\(02\)00728-7](https://doi.org/10.1016/S0008-8846(02)00728-7).
- [9] U. Angst, B. Elsener, A. Jamali, B. Adey, Concrete cover cracking owing to reinforcement corrosion - theoretical considerations and practical experience: concrete cover cracking owing to reinforcement corrosion, *Mater. Corros.* 63 (2012) 1069–1077, <https://doi.org/10.1002/maco.201206669>.
- [10] V.G. Papadakis, C.G. Vayenas, M.N. Fardis, A reaction engineering approach to the problem of concrete carbonation, *AIChE J.* 35 (1989) 1639–1650, <https://doi.org/10.1002/aic.690351008>.
- [11] B. Lagerblad, *Carbon Dioxide Uptake during Concrete Life Cycle – State of the Art*, Stockholm, Swedish Cement and Concrete Research Institute, 2005.
- [12] C. Pade, M. Guimaraes, The CO_2 uptake of concrete in a 100 year perspective, *Cement Concr. Res.* 37 (2007) 1348–1356, <https://doi.org/10.1016/j.cemconres.2007.06.009>.
- [13] Z. Cao, R.J. Myers, R.C. Lupton, H. Duan, R. Sacchi, N. Zhou, T. Reed Miller, J. M. Cullen, Q. Ge, G. Liu, The sponge effect and carbon emission mitigation potentials of the global cement cycle, *Nat. Commun.* 11 (2020) 3777, <https://doi.org/10.1038/s41467-020-17583-w>.
- [14] J. Sercombe, R. Vidal, C. Gallé, F. Adenot, Experimental study of gas diffusion in cement paste, *Cement Concr. Res.* 37 (2007) 579–588, <https://doi.org/10.1016/j.cemconres.2006.12.003>.
- [15] Y. Houst, The role of moisture in the carbonation of cementitious materials, *Restor. Build. Monum.* 2 (1996) 49–66, <https://doi.org/10.1515/rbm-1996-5083>.
- [16] B. Bary, A. Sellier, Coupled moisture–carbon dioxide–calcium transfer model for carbonation of concrete, *Cement Concr. Res.* 34 (2004) 1859–1872, <https://doi.org/10.1016/j.cemconres.2004.01.025>.
- [17] A. Morandea, M. Thiéry, P. Dangla, Investigation of the carbonation mechanism of CH and C-S-H in terms of kinetics, microstructure changes and moisture properties, *Cement Concr. Res.* 56 (2014) 153–170, <https://doi.org/10.1016/j.cemconres.2013.11.015>.
- [18] J. Jeong, A.S. Alemu, S. Park, H.K. Lee, G. Liyew, H. Ramézani, V.G. Papadakis, H.-K. Kim, Phase profiling of carbonated cement paste: quantitative X-ray diffraction analysis and numerical modeling, *Case Stud. Constr. Mater.* 16 (2022) e00890, <https://doi.org/10.1016/j.cscm.2022.e00890>.
- [19] V. Shah, K. Scrivener, B. Bhattacharjee, S. Bishnoi, Changes in microstructure characteristics of cement paste on carbonation, *Cement Concr. Res.* 109 (2018) 184–197, <https://doi.org/10.1016/j.cemconres.2018.04.016>.
- [20] H. Cui, W. Tang, W. Liu, Z. Dong, F. Xing, Experimental study on effects of CO_2 concentrations on concrete carbonation and diffusion mechanisms, *Construct. Build. Mater.* 93 (2015) 522–527, <https://doi.org/10.1016/j.conbuildmat.2015.06.007>.
- [21] J. Sang-Hwa, L. Myung-Kue, K. Jee-Sang, Experimental study on CO_2 diffusivity in cementitious materials, *Corros. Sci. Technol.* 4 (2005) 69–74.
- [22] J.M. Torrenti, O. Amiri, L. Barnes-Davin, F. Bougrain, S. Braymand, B. Cazacliu, J. Colin, A. Cudeville, P. Dangla, A. Djerbi, M. Doutreleau, A. Feraïlle, M. Gueguen, X. Guillot, Y. Hou, L. Izoret, Y.-P. Jacob, J. Jeong, J.D.L. Hiu Hoong, P.-Y. Mahieux, J. Mai-Nhu, H. Martinez, V. Meyer, V. Morin, T. Pernin, J.-M. Potier, L. Poulizac, P. Rougeau, M. Saadé, L. Schmitt, T. Sedran, M. Sereng, A. Soive, G.S. Dos Reys, P. Turcry, The FastCarb project: taking advantage of the accelerated carbonation of recycled concrete aggregates, *Case Stud. Constr. Mater.* 17 (2022) e01349, <https://doi.org/10.1016/j.cscm.2022.e01349>.
- [23] B. Lu, C. Shi, Z. Cao, M. Guo, J. Zheng, Effect of carbonated coarse recycled concrete aggregate on the properties and microstructure of recycled concrete, *J. Clean. Prod.* 233 (2019) 421–428, <https://doi.org/10.1016/j.jclepro.2019.05.350>.
- [24] C.O. Ania, E. Raymundo-Piñero, Nanoporous carbons with tuned porosity, in: K. Kaneko, F. Rodríguez-Reinoso (Eds.), *Nanoporous Materials for Gas Storage*, Springer, Singapore, 2019, pp. 91–135, https://doi.org/10.1007/978-981-13-3504-4_5.
- [25] R.C. Bansal, M. Goyal, Adsorption energetics, models and isotherm equation, in: *Activated Carbon Adsorption*, Taylor & Francis, 2005, pp. 67–143, <https://doi.org/10.1201/9781420028812>.
- [26] B. Akash, W. O'Brien, The production of activated carbon from a bituminous coal, *Int. J. Energy Res.* 20 (1996) 913–922, [https://doi.org/10.1002/\(SICI\)1099-114X\(199610\)20:10<913::AID-ER205>3.0.CO;2-7](https://doi.org/10.1002/(SICI)1099-114X(199610)20:10<913::AID-ER205>3.0.CO;2-7).
- [27] O. Duggan, S.J. Allen, Study of the physical and chemical characteristics of a range of chemically treated, lignite based carbons, *Water Sci. Technol.* 35 (1997) 21–27, [https://doi.org/10.1016/S0273-1223\(97\)00110-8](https://doi.org/10.1016/S0273-1223(97)00110-8).
- [28] G. Singh, K.S. Lakhii, S. Sil, S.V. Bhosale, I. Kim, K. Albahily, A. Vinu, Biomass derived porous carbon for CO_2 capture, *Carbon* 148 (2019) 164–186, <https://doi.org/10.1016/j.carbon.2019.03.050>.
- [29] D. Woolf, J.E. Amonette, F.A. Street-Perrott, J. Lehmann, S. Joseph, Sustainable biochar to mitigate global climate change, *Nat. Commun.* 1 (2010) 56, <https://doi.org/10.1038/ncomms1053>.
- [30] R. Renner, *Rethinking biochar*, *Environ. Sci. Technol.* (2007) 5932–5933.
- [31] P.D. Dissanayake, S. You, A.D. Igalavithana, Y. Xia, A. Bhatnagar, S. Gupta, H. W. Kua, S. Kim, J.-H. Kwon, D.C.W. Tsang, Y.S. Ok, Biochar-based adsorbents for

- carbon dioxide capture: a critical review, *Renew. Sustain. Energy Rev.* 119 (2020) 109582, <https://doi.org/10.1016/j.rser.2019.109582>.
- [32] S.S. Senadheera, S. Gupta, H.W. Kua, D. Hou, S. Kim, D.C.W. Tsang, Y.S. Ok, Application of biochar in concrete – a review, *Cem. Concr. Compos.* 143 (2023) 105204, <https://doi.org/10.1016/j.cemconcomp.2023.105204>.
- [33] S. Praneeth, R. Guo, T. Wang, B.K. Dubey, A.K. Sarmah, Accelerated carbonation of biochar reinforced cement-fly ash composites: enhancing and sequestering CO₂ in building materials, *Construct. Build. Mater.* 244 (2020) 118363, <https://doi.org/10.1016/j.conbuildmat.2020.118363>.
- [34] S. Gupta, S. Muthukrishnan, H.W. Kua, Comparing influence of inert biochar and silica rich biochar on cement mortar – hydration kinetics and durability under chloride and sulfate environment, *Construct. Build. Mater.* 268 (2021) 121142, <https://doi.org/10.1016/j.conbuildmat.2020.121142>.
- [35] S. Gupta, H.W. Kua, C.Y. Low, Use of biochar as carbon sequestering additive in cement mortar, *Cem. Concr. Compos.* 87 (2018) 110–129, <https://doi.org/10.1016/j.cemconcomp.2017.12.009>.
- [36] X. Yang, X.-Y. Wang, Strength and durability improvements of biochar-blended mortar or paste using accelerated carbonation curing, *J. CO₂ Util.* 54 (2021) 101766, <https://doi.org/10.1016/j.jcou.2021.101766>.
- [37] T. Chen, L. Zhao, X. Gao, L. Li, L. Qin, Modification of carbonation-cured cement mortar using biochar and its environmental evaluation, *Cem. Concr. Compos.* 134 (2022) 104764, <https://doi.org/10.1016/j.cemconcomp.2022.104764>.
- [38] P.F.E. Gunn, C.C. Onn, K.H. Mo, H.V. Lee, Enhancing carbon sequestration in cement mortar using high volume local rice husk biochar coupled with carbonation curing, *Case Stud. Constr. Mater.* 21 (2024) e03591, <https://doi.org/10.1016/j.cscm.2024.e03591>.
- [39] H.W. Kua, Biochar as building and road materials, in: *Biochar for Environmental Management: Science, Technology and Implementation*, third ed., Routledge, London, 2024 <https://doi.org/10.4324/9781003297673>.
- [40] H.W. Kua, S.M.H. Tan, Novel typology of accelerated carbonation curing: using dry and pre-soaked biochar to tune carbon capture and mechanical properties of cementitious mortar, *Biochar* 5 (2023) 36, <https://doi.org/10.1007/s42773-023-00234-w>.
- [41] S. Gupta, H.W. Kua, S.D. Pang, Effect of biochar on mechanical and permeability properties of concrete exposed to elevated temperature, *Construct. Build. Mater.* 234 (2020) 117338, <https://doi.org/10.1016/j.conbuildmat.2019.117338>.
- [42] M. Horgnien, I. Dubois-Brugger, N.J. Krou, I. Batonneau-Gener, T. Belin, S. Mignard, Reactivity of NO₂ and CO₂ with hardened cement paste containing activated carbon, *Eur. Phys. J. Spec. Top.* 224 (2015) 1985–1994, <https://doi.org/10.1140/epjst/e2015-02515-7>.
- [43] M. Horgnien, I. Dubois-Brugger, E.M. Gartner, NO_x de-pollution by hardened concrete and the influence of activated charcoal additions, *Cement Concr. Res.* 42 (2012) 1348–1355, <https://doi.org/10.1016/j.cemconres.2012.06.007>.
- [44] M. Horgnien, F. Serre, I. Dubois-Brugger, E. Gartner, NO_x De-pollution using activated charcoal concrete—from laboratory experiments to tests with prototype garages, *Cement Concr. Res.* 42 (2014) 1348–1355.
- [45] E. Raymundo-Piñero, M. Cadek, F. Béguin, Tuning carbon materials for supercapacitors by direct pyrolysis of seaweeds, *Adv. Funct. Mater.* 19 (2009) 1032–1039, <https://doi.org/10.1002/adfm.200801057>.
- [46] E. Raymundo-Piñero, M. Cadek, M. Wachtler, F. Béguin, Carbon nanotubes as nanotexturing agents for high power supercapacitors based on seaweed carbons, *ChemSusChem* 4 (2011) 943–949, <https://doi.org/10.1002/cssc.201000376>.
- [47] H. Giesche, Mercury porosimetry: a general (practical) overview, *Part. Part. Syst. Char.* 23 (2006) 9–19, <https://doi.org/10.1002/ppsc.200601009>.
- [48] A. Rita Damasceno Costa, J. Pereira Gonçalves, Accelerated carbonation of ternary cements containing waste materials, *Construct. Build. Mater.* 302 (2021) 124159, <https://doi.org/10.1016/j.conbuildmat.2021.124159>.
- [49] D. Frenkel, B. Smit, Monte Carlo simulations, in: *Understanding Molecular Simulation: from Algorithms to Applications*, Academic Press, San Diego, 2002, pp. 23–65, <https://doi.org/10.1063/1.881812>.
- [50] M.P. Allen, D.J. Tildesley, Monte Carlo methods, in: *Computer Simulation of Liquids*, Oxford university press, 2017, pp. 147–184, <https://doi.org/10.1093/oso/9780198803195.001.0001>.
- [51] T.X. Nguyen, S.K. Bhatia, Characterization of accessible and inaccessible pores in microporous carbons by a combination of adsorption and small angle neutron scattering, *Carbon* 50 (2012) 3045–3054, <https://doi.org/10.1016/j.carbon.2012.02.091>.
- [52] G. Opletal, T.C. Petersen, S.P. Russo, HRMC 2. 1: Hybrid Reverse Monte Carlo method with silicon, carbon, germanium and silicon carbide potentials, *Comput. Phys. Commun.* 185 (2014) 1854–1855, <https://doi.org/10.1016/j.cpc.2014.02.025>.
- [53] G. Opletal, T. Petersen, B. O'Malley, I. Snook, D.G. McCulloch, N.A. Marks, I. Yarovsky, Hybrid approach for generating realistic amorphous carbon structure using metropolis and reverse Monte Carlo, *Mol. Simulat.* 28 (2002) 927–938, <https://doi.org/10.1080/089270204000002584>.
- [54] Z. El Oufir, H. Ramezani, N. Mathieu, S. Delpoux, Impact of adsorbent carbons and carbon surface conductivity on adsorption capacity of CO₂, CH₄, N₂ and gas separation, *Comput. Mater. Sci.* 199 (2021) 110572, <https://doi.org/10.1016/j.commatsci.2021.110572>.
- [55] Z. El Oufir, H. Ramezani, N. Mathieu, S. Delpoux, S.K. Bhatia, Influence of force field used in carbon nanostructure reconstruction on simulated phenol adsorption isotherms in aqueous medium, *J. Mol. Liq.* 344 (2021) 117548, <https://doi.org/10.1016/j.molliq.2021.117548>.
- [56] A.H. Farmahini, S.K. Bhatia, Hybrid Reverse Monte Carlo simulation of amorphous carbon: distinguishing between competing structures obtained using different modeling protocols, *Carbon* 83 (2015) 53–70, <https://doi.org/10.1016/j.carbon.2014.11.013>.
- [57] H. Ramezani, J. Jeong, S.K. Bhatia, V.G. Papadakis, Assessment of CO₂ adsorption capacity in Wollastonite using atomistic simulation, *J. CO₂ Util.* 50 (2021) 101564, <https://doi.org/10.1016/j.jcou.2021.101564>.
- [58] M.P. Bichat, E. Raymundo-Piñero, F. Béguin, High voltage supercapacitor built with seaweed carbons in neutral aqueous electrolyte, *Carbon* 48 (2010) 4351–4361, <https://doi.org/10.1016/j.carbon.2010.07.049>.
- [59] H. Marsh, F. Rodríguez-Reinoso, Characterization of activated carbon, in: *Activated Carbon*, first ed., Elsevier, Amsterdam Boston, 2006, pp. 143–242, <https://doi.org/10.1016/B978-0-08-044463-5.X5013-4>.
- [60] A.A. Hilal, Microstructure of concrete, in: S. Yilmaz, H.B. Ozmen (Eds.), *High Performance Concrete Technology and Applications*, InTech, Rijeka, 2016, pp. 3–24, <https://doi.org/10.5772/64574>.
- [61] K. Aligizaki, Introduction, in: *Pore Structure of Cement-Based Materials: Testing, Interpretation and Requirements*, Taylor & Francis, Abingdon, 2006, pp. 1–32, <https://doi.org/10.1201/9781482271959>.
- [62] M.G. Richardson, Permeability and transport processes, in: *Fundamentals of Durable Reinforced Concrete*, Spon Press, London; New York, 2002, pp. 38–50, <https://doi.org/10.1201/9781482272109>.
- [63] K.L. Scrivener, A.K. Crumbie, P. Laugesen, The interfacial transition zone (ITZ) between cement paste and aggregate in concrete, *Interface Sci.* 12 (2004) 411–421, <https://doi.org/10.1023/B:INTS.0000042339.92990.4c>.
- [64] R. Zimbelmann, A method for strengthening the bond between cement stone and aggregates, *Cement Concr. Res.* 17 (1987) 651–660, [https://doi.org/10.1016/0008-8846\(87\)90138-4](https://doi.org/10.1016/0008-8846(87)90138-4).
- [65] J. Olivier, J. Maso, B. Bourdette, Interfacial transition zone in concrete, *Adv. Cement Base Mater.* 2 (1995) 30–38, [https://doi.org/10.1016/1065-7355\(95\)90037-3](https://doi.org/10.1016/1065-7355(95)90037-3).
- [66] A. Elsharief, M.D. Cohen, J. Olek, Influence of aggregate size, water cement ratio and age on the microstructure of the interfacial transition zone, *Cement Concr. Res.* 33 (2003) 1837–1849, [https://doi.org/10.1016/S0008-8846\(03\)00205-9](https://doi.org/10.1016/S0008-8846(03)00205-9).
- [67] J. Zhang, C. Shi, Y. Li, X. Pan, C.-S. Poon, Z. Xie, Performance enhancement of recycled concrete aggregates through carbonation, *J. Mater. Civ. Eng.* 27 (2015) 04015029, [https://doi.org/10.1061/\(ASCE\)MT.1943-5533.0001296](https://doi.org/10.1061/(ASCE)MT.1943-5533.0001296).
- [68] S. Gupta, H.W. Kua, Effect of water entrainment by pre-soaked biochar particles on strength and permeability of cement mortar, *Construct. Build. Mater.* 159 (2018) 107–125, <https://doi.org/10.1016/j.conbuildmat.2017.10.095>.
- [69] A. Sirico, P. Bernardi, B. Belletti, A. Malvezzi, E. Dalcanale, I. Domenichelli, P. Fornoni, E. Moretti, Mechanical characterization of cement-based materials containing biochar from gasification, *Construct. Build. Mater.* 246 (2020) 118490, <https://doi.org/10.1016/j.conbuildmat.2020.118490>.
- [70] T. Nishikawa, K. Suzuki, Chemical conversion of C-S-H in concrete, *Cement Concr. Res.* 24 (1994) 176–182, [https://doi.org/10.1016/0008-8846\(94\)90099-X](https://doi.org/10.1016/0008-8846(94)90099-X).
- [71] T. Nishikawa, K. Suzuki, S. Ito, K. Sato, T. Takebe, Decomposition of synthesized ettringite by carbonation, *Cement Concr. Res.* 22 (1992) 6–14, [https://doi.org/10.1016/0008-8846\(92\)90130-N](https://doi.org/10.1016/0008-8846(92)90130-N).
- [72] N. Vogler, P. Drabetzki, M. Lindemann, H.-C. Kühne, Description of the concrete carbonation process with adjusted depth-resolved thermogravimetric analysis, *J. Therm. Anal. Calorim.* 147 (2022) 6167–6180, <https://doi.org/10.1007/s10973-021-10966-1>.
- [73] D. Torrén-Martín, L. Fernández-Carrasco, M.T. Blanco-Varela, Thermal analysis of blended cements, *J. Therm. Anal. Calorim.* 121 (2015) 1197–1204, <https://doi.org/10.1007/s10973-015-4569-1>.
- [74] M. Thiery, G. Villain, P. Dangla, G. Platret, Investigation of the carbonation front shape on cementitious materials: effects of the chemical kinetics, *Cement Concr. Res.* 37 (2007) 1047–1058, <https://doi.org/10.1016/j.cemconres.2007.04.002>.
- [75] C. Liu, Z. Liu, Y. Zhang, A multi-scale framework for modelling effective gas diffusivity in dry cement paste: combined effects of surface, Knudsen and molecular diffusion, *Cement Concr. Res.* 131 (2020) 106035, <https://doi.org/10.1016/j.cemconres.2020.106035>.
- [76] Y.F. Houst, F.H. Wittmann, Influence of porosity and water content on the diffusivity of CO₂ and O₂ through hydrated cement paste, *Cement Concr. Res.* 24 (1994) 1165–1176.
- [77] J.J. Chen, J.J. Thomas, H.M. Jennings, Decalcification shrinkage of cement paste, *Cement Concr. Res.* 36 (2006) 801–809, <https://doi.org/10.1016/j.cemconres.2005.11.003>.
- [78] K.-H. Yang, E.-A. Seo, S.-H. Tae, Carbonation and CO₂ uptake of concrete, *Environ. Impact Assess. Rev.* 46 (2014) 43–52, <https://doi.org/10.1016/j.eiar.2014.01.004>.
- [79] S. Steiner, T. Proske, F. Winnefeld, B. Lothenbach, Effect of limestone fillers on CO₂ and water vapour diffusion in carbonated concrete, *Cemento* 8 (2022) 100027, <https://doi.org/10.1016/j.cement.2022.100027>.
- [80] M. Jebli, F. Jamin, E. Malachanne, E. Garcia-Diaz, M.S. El Yousoufi, Experimental characterization of mechanical properties of the cement-aggregate interface in concrete, *Construct. Build. Mater.* 161 (2018) 16–25, <https://doi.org/10.1016/j.conbuildmat.2017.11.100>.
- [81] R.A. Berner, A.C. Lasaga, R.M. Garrels, Carbonate-silicate geochemical cycle and its effect on atmospheric carbon dioxide over the past 100 million years, *Am. J. Sci.* 283 (1983) 641–683, <https://doi.org/10.2475/ajs.283.7.641>.
- [82] W. Dreybrodt, J. Lauckner, L. Zaihua, U. Svensson, D. Buhmann, The kinetics of the reaction CO₂ + H₂O → H⁺ + HCO₃⁻ as one of the rate limiting steps for the dissolution of calcite in the system H₂O-CO₂-CaCO₃, *Geochem. Cosmochim. Acta* 60 (1996) 3375–3381, [https://doi.org/10.1016/0016-7037\(96\)00181-0](https://doi.org/10.1016/0016-7037(96)00181-0).
- [83] G.H. Rau, K. Caldeira, Enhanced carbonate dissolution: a means of sequestering waste CO₂ as ocean bicarbonate, *Energy Convers. Manag.* 40 (1999) 1803–1813.

- [84] G.H. Rau, CO₂ mitigation via capture and chemical conversion in seawater, *Environ. Sci. Technol.* 45 (2011) 1088–1092, <https://doi.org/10.1021/es102671x>.
- [85] M. Samari, F. Ridha, V. Manovic, A. Macchi, E.J. Anthony, Direct capture of carbon dioxide from air via lime-based sorbents, *Mitig. Adapt. Strategies Glob. Change* 25 (2020) 25–41, <https://doi.org/10.1007/s11027-019-9845-0>.
- [86] Z. Liu, W. Dreybrodt, Significance of the carbon sink produced by H₂O–carbonate–CO₂–aquatic phototroph interaction on land, *Sci. Bull.* 60 (2015) 182–191, <https://doi.org/10.1007/s11434-014-0682-y>.
- [87] F. Pontiga, J.M. Valverde, H. Moreno, F.J. Duran-Olivencia, Dry gas–solid carbonation in fluidized beds of Ca(OH)₂ and nanosilica/Ca(OH)₂ at ambient temperature and low CO₂ pressure, *Chem. Eng. J.* 222 (2013) 546–552, <https://doi.org/10.1016/j.cej.2013.02.067>.