



HAL
open science

Deformation behaviour of 304 stainless steel - experimental and modelling

Bertrand Petit, Nathalie Gey, Farid Abed-Meraim, Michel Humbert, Tarak Ben Zineb, Bernard Bolle, Mohamed Cherkaoui

► To cite this version:

Bertrand Petit, Nathalie Gey, Farid Abed-Meraim, Michel Humbert, Tarak Ben Zineb, et al.. Deformation behaviour of 304 stainless steel - experimental and modelling. EUROMAT'05, Sep 2005, Prague, Czech Republic. <hal-05120381>

HAL Id: hal-05120381

<https://hal.science/hal-05120381v1>

Submitted on 19 Jun 2025

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.



HAL Authorization

DEFORMATION BEHAVIOUR OF 304 STAINLESS STEEL

EXPERIMENTAL AND MODELLING

B. Petit* **, N. Gey*, F. Abed-Meraim**, M. Humbert*, T. Ben Zineb**, B. Bolle*, M. Cherkaoui**

* LETAM CNRS - Université de Metz, Ile du Saulcy, F-57045 Metz Cedex

** LPMM ENSAM - CNRS - Université de Metz, Ile du Saulcy, F-57045 Metz Cedex

The austenitic stainless steels are characterised by remarkable mechanical properties, combining high ductility and high strength. Their plastic deformation involves a wide variety of strain induced deformation mechanisms, strongly related to the alloy stacking fault energy. With increasing SFE, martensitic transformation sequences ($\gamma \rightarrow \alpha'$, $\gamma \rightarrow \varepsilon \rightarrow \alpha'$), deformation twinning, glide of dissociated or perfect dislocations can occur.

A quantitative modelling of such a deformation behaviour, with real predictive capabilities, has been developed recently. It is formulated in terms of finite strains and takes the various inelastic strains encountered in the material into account. In particular, two inelastic deformations are considered, either ε martensite transformation strain or twinning strain, depending on the testing temperature, and the α' transformation strain. Thermomechanical couplings are realised between these two inelastic deformation modes. The model which uses a self-consistent method for the scale transition, allows us to calculate the global behaviour of the polycrystal.

In this contribution, this new model is applied to foresee the behaviour of a 304 stainless steel, tensile tested in a temperature range of -60°C to room temperature. Besides, large experimental investigations were performed on various 304 specimens. In particular, X-ray diffraction was used to quantify the volume fraction of the α' and ε martensite and to determine the texture evolution of the parent and the product phases. The local microtextures were analysed with the EBSD technique in a SEM FEG. The predictions obtained with the micromechanical model are compared to the different experimental results, notably the mechanical behaviour and associated deformation mechanisms, the transformation kinetic as well as the texture evolution.